

MasterSeal[®] 920 and 921

Joint filler and backing material for
Master Builders Solution sealants

FORMERLY CLOSED-CELL BACKER-ROD AND SOFT BACKER-ROD

PACKAGING

MASTERSEAL 920

Sizes ¼–1¼" (6–32 mm) are wound on reels and packaged in cartons, weighing about 15 lbs (6.8 kg) per carton.

The 1½–4" (38–102 mm) sizes are packaged in 7 ft (2.1 m) lengths and packaged in cartons, weighing about 35 lbs (15.89 kg) per carton.

MASTERSEAL 921

Sizes ⅜–1½" (10–29 mm) are wound on reels and packaged in cartons, weighing about 15 lbs (6.8 kg) per carton.

The 1½–4" (38–102 mm) sizes are packaged in 6 ft (1.8 m) lengths and packaged in cartons, weighing about 18 lbs (8.1 kg) per carton.

COLOR

Gray

YIELD

See page 2 for charts

DESCRIPTION

MasterSeal 920 is a closed-cell, polyethylene foam joint-filler and backing for elastomeric sealants. Its resilience accommodates dynamic joints. MasterSeal 921 is a reticulated closed-cell polyethylene foam joint-filler and backing for sealants. It compresses easily to accommodate joints of varying widths.

PRODUCT HIGHLIGHTS

MASTERSEAL 920

- Closed-cell polyethylene foam for low moisture absorption
- Lightweight, installs easily and quickly
- Resilient—accepts joint movement
- Nonimpregnated, nonstaining, and nonbleeding, will not discolor sealants or substrates
- Inert for compatibility with cold-applied sealants
- Round to give proper shape to sealant for effective function
- Nonadhering to sealants, requiring no additional bondbreaker

MASTERSEAL 921

- Nongassing when punctured to eliminate bubbling of sealant
- Reticulated closed-cell polyethylene foam for low moisture absorption
- Nonimpregnated, nonstaining, and nonbleeding, will not discolor sealants or substrates
- Highly resilient to conform to irregular joints; installs easily and quickly
- Nonadhering to sealants, requiring no additional bondbreaker

APPLICATIONS

- Backing for sealants
- Precast panel joints
- Expansion joints
- Window-and door-frame perimeters
- Coping joints
- Glazing joints
- Isolation joints
- Control joints

Technical Data

MASTERSEAL 920

Composition

MasterSeal 920 is closed-cell polyethylene foam.

Compliances

- ASTM C 1330, Type C

MASTERSEAL 921

Composition

MasterSeal 921 is reticulated polyethylene foam with a continuous outer skin.

Compliances

- ASTM C 1330, Type B

Test Data

MASTERSEAL 920

PROPERTY	RESULTS	TEST METHOD
Water absorption, oz/in³ (g/cc)	< 0.017 (< 0.03)	ASTM C 1016
Density, lb/ft³ (kg/m³)	1.50–3.0 (24–48)	ASTM D 1622
Compression recovery, %	> 90	ASTM D 5249
Compression deflection, psi (KPa)	> 2.97 (>20.5)	ASTM D 5249
Tensile strength, psi (KPa)	> 29.0 (>200)	ASTM D 1623
Service temperature, ° F (° C)	-45 to 160 (-43 to 71)	

Test results are typical values obtained under laboratory conditions. Reasonable variations can be expected.

MASTERSEAL 921

PROPERTY	RESULTS	TEST METHOD
Water absorption, oz/in³ (g/cc)	0.058 (0.10)	ASTM C 1016
Density, lb/ft ³ (kg/m ³)	1.50–3.0 (24–48)	ASTM D 1622
Compression recovery, %	> 90	ASTM D 5249
Compression deflection, psi (KPa)	> 2.97 (> 20.5)	ASTM D 5249
Tensile strength, psi (KPa)	> 29.0 (>200)	ASTM D 1623
Service temperature, ° F (° C)	-45 to 160 (-43 to 71)	

Test results are typical values obtained under laboratory conditions. Reasonable variations can be expected.

Yield

ESTIMATING MASTERSEAL 920 REQUIREMENTS

ROD DIAMETER IN (MM)	LINEAR FT PER CARTON (METERS PER CARTON)
1/4 (6)	6,400 (1,951)*
3/8 (10)	3,600 (1,097)**
1/2 (13)	2,500 (762)
5/8 (16)	1,550 (472)
3/4 (19)	1,100 (335)
1 (25)	550 (168)
1-1/4 (32)	400 (122)
1-1/2 (38)	552 (168)***
2 (51)	360 (110)***
2-1/2 (64)	240 (73)***
3 (76)	144 (43.9)***
4 (102)	90 (27.4)***

* Supplied as two 3,200 ft (975 m) reels

** Supplied as two 1,800 ft (549 m) reels

*** Supplied as 7 ft (2.1 m) lengths

ESTIMATING MASTERSEAL 921 REQUIREMENTS

ROD DIAMETER IN (MM)	LINEAR FT PER CARTON (METERS PER CARTON)
3/8 (10)	3,600 (1097.3)*
5/8 (16)	1,550 (472)
7/8 (22)	850 (259.1)
1-1/8 (29)	500 (152.4)
1-1/2 (38)	552 (168.2)**
2 (51)	360 (109.7)**
2-1/2 (64)	240 (73.2)**
3 (76)	144 (43.9)**
4 (102)	90 (27.4)**

* Supplied as two 1,800 ft (549 m) reels

** Supplied as 6 ft (1.8 m) lengths

HOW TO APPLY

APPLICATION

1. Joint fillers have three major functions:
 - to control the depth of the sealant in proper relation to joint width
 - to provide a backing against which the sealant is applied, forcing the sealant to the sides of the joint
 - to prevent 3-sided bonding, ensuring proper functioning of the joint sealant
2. To install, compress backer-rod into the joint before sealants are applied.
3. Install backer-rod using a blunt probe or a plain-faced roller to force the rod to the desired depth.
4. A template or roller gauge may be used to control the depth at which the rod is placed.
5. DO NOT stretch backer-rod during installation but gently force into the joint so that the backer-rod fits tight against the sides of the joint.

APPROPRIATE BACKER-ROD SIZE

SIZING MASTERSEAL 920

1. For joint widths up to $\frac{3}{4}$ " (19 mm), the diameter of the rod should be $\frac{1}{8}$ " (3 mm) larger than the width of the joint.
2. For $\frac{3}{4}$ " (19 mm) wide joints, use 1" (25 mm) diameter rod.

SIZING MASTERSEAL 921

Select a backer-rod diameter that is approximately 25% larger than the width of the joint. See the yield table on the next page for both MasterSeal 920 and MasterSeal 921.

JOINT SEALING

1. Follow suggestions for joint-sealant application as directed by sealant manufacturer.
2. Where priming of the joint is necessary, primer should be applied only to the joint surfaces and allowed to dry before backer rod is placed. DO NOT prime backer rod.

FOR BEST PERFORMANCE

- Do not puncture, fold, stretch, or crease MasterSeal 920 / MasterSeal 921.
- Follow sealant manufacturer's suggestions for joint sealant width-to-depth ratio.
- Do not use with hot applied sealants.
- For joints subject to puncture by high heels or umbrella points, a stiffer or higher density backup material is required. Cork or non-impregnated cane-fiber joint fillers are suitable. Separate materials from the sealant by a nonadhering, bondbreaker (polyethylene tape).
- Make certain the most current versions of product data sheet and SDS are being used; visit master-builders-solutions.basf.us to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.basf.us, e-mailing your request to basfbcst@basf.com or calling 1(800)433-9517. Use only as directed.

**For medical emergencies only,
call ChemTrec® 1(800)424-9300.**

LIMITED WARRANTY NOTICE

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

