

MasterRoc[®] MP 800

Fast setting ultrafine Portland cement for rock and soil injection

Product description

MasterRoc MP 800 is a well graded cement milled from pure Portland cement clinker with a Blaine value of 800 m²/kg. Due to its small particle size it penetrates tight joints, fissures and pores very well to provide a water-tight grouted rock or soil mass.

It achieves initial and final setting faster than standard micro and ultrafine cements. This increases the productivity in injection operations. The short open time of 1 to 1½ hours and a very short setting time of 2½ hours (at about 20°C) reduces the waiting time for the next excavation round to a minimum.

Fields of application

- Pre-injection in underground structures
- Post injection
- Water ingress reduction
- Ground stabilization
- Contact injection

Features and benefits

- Excellent penetration in tight joints, fissures and pores
- Fast setting
- Durable
- Better working environment - no hazardous components
- Economical solution
- Standard cement injection equipment can be used

Packaging

MasterRoc MP 800 is supplied in 20 kg plastic bags and 1000 kg bags.

Technical data

Fineness (Blaine) > 800 m²/kg

Particle size distribution:

<40 micron	100 %
<30 micron	99 %
<20 micron	99 %
<15 micron	98 %
<10 micron	92 %
< 5 micron	58 %
< 2 micron	20 %

Setting Times

The setting times, at a 1:1 w/c ratio (by weight) and at 20° C are as follows:

Initial set: 60-120 min (measured by Vicat needle)

Final set: 120-150 min (1 mm penetration by Vicat needle)

Injection grout properties indicated below, relate to a mix containing 1.5% MasterGlenium 151C:

Water/Cement ratio	1.0
Mud balance	1.48 - 1.50 kg/l
Flow cone	32 - 34 s
Bleeding maximum	2 %

Application procedure

Mixing

MasterRoc MP 800 should always be used with MasterGlenium 151C water reducing admixture (1.0 - 1.5 % of the cement weight.) The w/c ratio (by weight) should normally be between 0.6 and 1.0.

- Fill the mixer with water
- Add MasterGlenium 151C
- Add cement and mix for 2 minutes
- Transfer to agitator

It is very important to use an efficient mixer. Colloidal mixers give the best result. Minimum rpm for colloidal mixers are 1500.



We create chemistry

MasterRoc[®] MP 800

NB: Do not over mix. Mixing longer than recommended may cause the grout temperature to increase and set in the pump and/or hoses.

Pot life

The mix should be kept under constant agitation prior to injection. Do not keep the grout in the agitator longer than 30 – 40 minutes.

Injection

High-pressure piston pumps are normally used to pump the suspension into the rock. The grout should be injected within 30 - 40 minutes after mixing to ensure that it keeps spreading into the fissures. Longer open times can be achieved by using MasterRoc HCA 10 hydration control admixture.

For much longer open times MasterRoc MP 800 is a real alternative. This product is available upon special request.

Hardening

MasterRoc MP 800 will have set sufficiently after 2 - 2½ hours to allow drilling for control or blast holes.

Storage

MasterRoc MP 800 has a shelf life of 9 months when stored in the original closed bags in ventilated dry areas.

Safety precautions

Any physical contact (e.g. skin or eyes) with the product should be avoided, as it may cause irritation or burns.

If such a contact occurs, the affected area should be washed with plenty of clean water. In case of eye contact, seek immediate medical advice.

For further information please refer to the Material Safety Data Sheet or contact your local UGC representative.

The information given here is true, represents our best knowledge and is based not only on laboratory work but also on field experience. However, because of numerous factors affecting results, we offer this information without guarantee and no patent liability is assumed. For additional information or questions, please contact your local representative.

Headquarters:

BASF SE
Underground Construction
Salzachstr. 2-12
68199 Mannheim
Germany

Phone: +49 621 60 91013

For more information: Visit us: www.master-builders-solutions.basf.com