

# MasterBrace P 3500®

Epoxy primer for MasterBrace Laminate system

## DESCRIPTION

**MasterBrace P 3500** is a two component solvent-less epoxy penetrating medium viscosity primer.

## RECOMMENDED USES

For use as a primer for the concrete prior to the use of the **MasterBrace 4000** adhesive when used in conjunction with **MasterBrace Laminates** and for MasterBrace sheets and MasterBrace 4500 saturant.

## FEATURES AND BENEFITS

- **Excellent adhesion to concrete substrate** – ensures transfer of loads.
- **Solvent free** – low VOC and non-shrink.
- **Pre-packaged** – avoids on site errors ensuring quality control.
- **Cures at low temperatures** – suitable for a range of climates.

## PROPERTIES

Bonding to concrete, pr EN 1542 (direct)	> 3.5 MPa (concrete failure)
Ultimate elongation, ASTM D638	3%
Tensile strength:	
direct, ASTM D638	>12 MPa
by flexing, ASTM D790	>24 MPa
Modulus of elasticity:	
tensile, ASTM D638	>700 MPa
flexural, ASTM D790	>580 MPa
Composition	Two-part Epoxy resin
Solids by volume	100%
Mixing ratio by volume:	3 ; 1 (A:B)
Specific gravity (mixed)	1.08 ± 0.024 kg/L
Colour	Transparent
Overall thickness	150 micron
coverage approximately-	6m <sup>2</sup> /L
Recommended layers	1
Pot life	
7°C;	1 hour
23°C;	35 min
32°C;	25 min
Tack-free	
7°C;	9 hours
23°C;	5 hours
32°C;	3 hours

## APPLICATION

### Surface preparation

Remove all grease, oil, dust residual curing compound, mould release agent or other contaminants that could impair adhesion.

Spalled concrete should be cut back to sound concrete and made good suitable

**MasterEmaco** repair products.

Laitance should be removed preferably by captive shotblasting or hydro-jetting. Mechanical wire brushing may be appropriate for small areas. A surface profile of CSP 3-4 is desired

### Mixing

Mechanically mix Part A before adding Part B. When component B has been added, mix for approximately 2 minutes until a homogenous mix has been obtained.

### Application of MasterBrace P 3500

Apply **MasterBrace P 3500** by brush or roller to the prepared substrate at a coverage of 6m<sup>2</sup>/L. If using as a primer for the **MasterBrace** sheet system apply the **MasterBrace 4500** whilst the **MasterBrace P 3500** is still tacky.

**MasterBrace 4000** laminate adhesive should be applied to the **MasterBrace P 3500** while it is still tacky. Do not allow to become tack free before application of the **MasterBrace 4000**. Otherwise, sand seed the MasterBrace P 3500 whilst wet and apply **MasterBrace 4000** within 48 hours.

For further details see the Application Guide.

## ESTIMATING DATA

Typical consumption of 4-6 m<sup>2</sup> per L.

MasterBrace P 3500 wet film thickness				
L	Thickness in mm /m <sup>2</sup>	m <sup>3</sup>	pails /m <sup>3</sup>	m <sup>2</sup> /mm thickness
5	5mm	(0.005)	200	5 m <sup>2</sup>

## PACKAGING

**MasterBrace P 3500** is available in a 5L packs of 3.75L Part A and 1.25L Part B.



We create chemistry

# MasterBrace P 3500®

## SHELF LIFE

MasterBrace P 3500 can be stored in tightly closed original containers for 12 months at a moderate temperature.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from BASF office or website.

MasterBrace-P3500-ANZ-V12-0417

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

#### BASF Australia Ltd

ABN 62008437867  
Level 12  
28 Freshwater Place  
Southbank VIC 3006

**Freecall: 1300 227 300**

[www.master-builders-solutions.basf.com.au](http://www.master-builders-solutions.basf.com.au)

#### BASF New Zealand Ltd

Level 4, 4 Leonard Isitt Drive  
Auckland Airport 2022  
Auckland, New Zealand

**Freecall: 0800 334 877**

[www.master-builders-solutions.basf.co.nz](http://www.master-builders-solutions.basf.co.nz)

#### BASF Emergency Advice:

1800 803 440 within Australia (24hr)  
0800 944 955 within New Zealand