



We create chemistry

**Specification
for
MasterEmaco® S 5300CI**

MasterEmaco S 5300CI Repair Mortar

NOTES TO SPECIFIERS:

THE PURPOSE OF THIS GUIDE SPECIFICATION IS TO ASSIST THE SPECIFIER IN DEVELOPING A PROJECT SPECIFICATION FOR THE USE OF BASF BUILDING SYSTEMS' PRODUCTS. THIS GUIDE SPECIFICATION WILL NEED TO BE CAREFULLY REVIEWED FOR APPROPRIATENESS FOR THE GIVEN PROJECT AND EDITED ACCORDINGLY TO COMPLY WITH PROJECT-SPECIFIC REQUIREMENTS.

GENERAL

1.1 SUMMARY

A. Section Includes:

1. Application of non-sag concrete repair mortar with integral corrosion inhibitor for vertical and overhead applications.

1.2 SUBMITTALS

A. Product Data: Submit manufacturer's technical data sheets and Safety Datasheet product information for each product.

B. Quality Control Submittals:

1. Provide protection plan of surrounding areas and non-cementitious surfaces.

1.3 QUALITY ASSURANCE

A. Qualifications:

1. Manufacturer Qualifications: Company with minimum 15 years of experience in manufacturing of specified products.
2. Manufacturer Qualifications: Company shall be ISO 9001:2000 Certified.

3. Applicator Qualifications: Company with minimum of 5 years' experience in application of specified products on projects of similar size and scope, and is acceptable to product manufacturer.
 - a. Successful completion of a minimum of 5 projects of similar size and complexity to specified Work.

1.4 DELIVERY, STORAGE, AND HANDLING

- A. Comply with manufacturer's ordering instructions and lead-time requirements to avoid construction delays.
- B. Deliver materials in manufacturer's original, unopened, undamaged containers with identification labels intact.
- C. Store tightly sealed materials off ground and away from moisture, direct sunlight, extreme heat, and freezing temperatures.
- D. Precondition materials to 21 degrees C plus or minus 3 degrees C before mixing.

1.5 PROJECT CONDITIONS

- A. Environmental Requirements:
 1. Do not use products under conditions of precipitation or freezing weather. Do not apply material at temperatures below 5 degrees C or above 35 degrees C. Use appropriate measures for protection and supplementary heating to ensure proper curing conditions per manufacturer's recommendations if application during inclement weather occurs.

PRODUCTS

1.6 MANUFACTURERS

- A. Subject to compliance with requirements, provide products from the following manufacturer:

BASF Australia

Construction Chemicals

11 Stanton Road

Seven Hills 2147

Customer Service: 1300227300

Internet: www.master-builders-solutions.basf.com.au

- B. Specifications and Drawings are based on manufacturer's proprietary literature from BASF Construction Chemicals

1.7 MATERIALS

- A. Non-sag, Structural, 1-component, high-strength, silica-fume-enhanced repair mortar with integral corrosion inhibitor for vertical and overhead applications.
1. Manufactured to be placed from 5 mm to 75 mm per lift vertically and 5 mm to 30 mm overhead.
 2. Acceptable Product: MasterEmaco S 5300CI by BASF.
- B. Properties of mixed cementitious repair materials:
1. Working Time, 21 degrees C: 45 to 60 minutes.
 2. Color: Concrete grey
- C. Properties of cured cementitious repair materials:

Compressive strength - after 1 day - after 7 days - after 28 days	AS 1478.2 Appendix A (Restrained)	≥15 MPa ≥ 30 MPa ≥ 45 MPa
E-Modulus (28 days)	prEN13412	≥ 1.0 GPa
Adhesion (28 days)	EN 1542	≥ 1.5 MPa
Cracking tendency (I)	Coutinho type ring	No cracking after 180 days
VOC Content	SCAQMD 304-91	21g/L

Hardening times are measured at 21°C ± 2°C and 60% ± 10% relative humidity. Higher temperatures will reduce these times and lower temperatures will extend them. Technical data shown are statistical results and do not correspond to guaranteed minimal. Tolerances are those described in appropriate performance standards

EXECUTION

1.8 EXAMINATION

1.9 SURFACE PREPARATION

- A. Protection: Protect adjacent Work areas and finish surfaces from damage during repair mortar application.
- B. Prepare surfaces in accordance with manufacturer's instructions.
- C. Ensure surfaces are clean, sound, and free of laitance, standing water, dirt, oil, efflorescence, paint, curing compounds, form oils, and other surface contaminants.
- D. Prepare concrete substrate to surface profile CSP 5 or greater for proper adhesion.
- E. Clean exposed steel reinforcement to white-metal finish SA 2.5 or better and prime with MasterEmaco P 5000 AP anti-corrosion coating.
- F. Saw-cut straight edges along repair area perimeters minimum of 10 mm deep to avoid feathered edges.
- G. Repair cracks that appear in interface area of patch or overlay as directed.
- H. Continue expansion and control joints through repair or as directed by Architect.

1.10 MIXING

- A. Mix materials in accordance with manufacturer's instructions.
- B. Only full bags are mixed. Damaged or opened bags should not be used.
- C. Mix **MasterEmaco S 5300CI** with a helical paddle attached to a slow speed (300-600 rpm) helical mixer or in a forced action pan mixer for 3 minutes until a lump free, plastic consistency is achieved. Only use clean water.
- D. Mixing water needed: 3.8 to 4.2 litres per 20kg bag depending upon consistency required.
- E. Allow the mortar to rest for 2 - 3 minutes and then remix briefly, adjusting the consistency as required. NB: Never exceed the maximum water demand.
- F. Mix no more material than can be placed in 45 to 60 minutes at 21 degrees C and 50 percent relative humidity.

1.11 APPLICATION

- A. Apply and cure repair mortar in accordance with manufacturer's instructions.

B. Application:

1. The prepared substrate should be pre-soaked, preferably for 24 hours, but at least 2 hours before applying **MasterEmaco S 5300CI** to obtain saturated surface-dry (SSD) with no standing water.
2. For improved build thicknesses or when working on large areas, apply bond or contact layer of the **MasterEmaco S 5300CI** mortar(mixed 1:1 wit clean water). Alternatively a bonding coat of **MasterEmaco P 5000 AP** can be applied.
3. Apply mixed product directly to the prepared damp substrate, or wet on wet onto the primed surface.
4. **MasterEmaco S 5300CI** can be hand or trowel applied.
5. Place repair mortar and key-in and compact thoroughly to secure bond.
6. Apply repair mortar in lifts of 5 mm to 30 mm.
7. Avoid featheredging. For optimum mechanical bond on successive lifts, thoroughly score each lift and allow reaching initial set before next layer is applied.
8. Trowel repair mortar to desired finish after initial set. Smoothing with a trowel or finishing by float or sponge can be done as soon as the mortar has begun to stiffen, typically after approximately 45 - 60 minutes at 20°C.
9. In these environmental conditions, **MasterEmaco S 5300CI** can be over-coated, after approximately 24 hours, with **MasterProtect** water based acrylic coatings as required. NB: At lower temperatures and/or higher humidity these times will be extended

C. Curing:

1. Damp cure for 3 days.
2. Use appropriate curing compound if surface cannot be damp cured such as **MasterKure 250**.

1.12 PROTECTION

- A. Protect repair mortar from damage during construction.
- B. Protect from freezing for minimum of 24 hours after application.

END OF SECTION

Disclaimer

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.