

MasterEmaco[®] S 680

Cementitious spray applied repair mortar for aggressive environments.

DESCRIPTION

MasterEmaco S 680 is a ready-to-use, high alumina cement based shotcrete mix with reduced rebound. It is specially designed for sewer repair applications or where acid and/or abrasion resistance is required using dry shotcreting systems.

RECOMMENDED USES

- Repairs to brick, cast in place concrete and precast concrete sewers.
- Reinstating linings of sewers after repair with **MasterEmaco S 820CI**.
- Tunnel linings or other places where resistance to acidic waters is required.

FEATURES AND BENEFITS

- **High alumina clinker and cement** – all ingredients are reactive and form an acid resistant matrix.
- **Easy to use** – requires only the addition of potable water for mixing or spraying.
- **Self-healing** – long term reactivity of matrix heals surface cracks increasing repair life.
- **Good working time** – over one hour at 21°C.
- **Controlled shrinkage** – reduced cracking tendency.

PROPERTIES

Age	Compressive Strength MPa	Flexural Strength MPa
1 day	~70.0	~9.0
28 days	~100.0	~12.0
Bonding Strength (substrate failure)		>2.5Mpa
Coefficient of Thermal Expansion		8.5 X 10 ⁻⁶ /°C
Taber abrasion CS17 wheel		58g

* All performance data is determined by testing actual, in-place shotcreted specimens such as cores and beams taken from test panels.

Reasonable variations from the data shown can be expected, depending on the care taken in evaluating test specimens, and jobsite conditions such as the quality of substrate preparation, level of expertise of the nozzleman, curing procedures and weather.

APPLICATION DIRECTIONS

Prepare the surface to be shotcreted by removing all unsound concrete, dirt, dust and debris. A surface profile on old concrete should be CSP 7 or greater. If applying over recently sprayed **MasterEmaco S 820CI** ensure that the surface has been cleaned and that the surface has not been troweled smooth. For brick lined sewers ensure that all loose mortar in the joints has been removed and that the face of the bricks is clean.

Mix **MasterEmaco S 680** with approximately 1.8-2.5 litres of water per 20kg bag.

MasterEmaco S 680 can be shotcreted in depths ranging from 10 - 150mm in one pass.

CURING

Proper curing is extremely important however given the environment (moist and humid) that this product is placed in the use of curing compounds or other forms of curing are not necessary

ESTIMATING DATA

One 20kg bag of **MasterEmaco S 680** mixed with water yields approximately 10.2 litres (0.0102m³).

Allowance must be made for rebound and cut off for finishing which will reduce the coverage accordingly.

MasterEmaco S 680				
L	Thickness in mm /m ²	m ³	bags /m ³	m ² /mm thickness
10.2	10.2mm	(0.0102)	98	10.2 m ²

An allowance of 10-15% can be made for rebound which assumes an experienced nozzleman and ideal conditions. For overhead spraying the rebound allowance may be increased to 10-50%. Refer to BASF Construction Chemicals for further advice.

PACKAGING

MasterEmaco S 680 is available in 20kg bag



We create chemistry

MasterEmaco[®] S 680

SHELF LIFE

MasterEmaco S 680 has a shelf life of 6 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information, first aid measures and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from BASF office or website.

MasterEmaco-S680-ANZ-V7-0417

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd

ABN 62008437867

Level 12

28 Freshwater Place

Southbank VIC 3006

Freecall: 1300 227 300

www.master-builders-solutions.basf.com.au

BASF New Zealand Ltd

Level 4, 4 Leonard Isitt Drive

Auckland Airport 2022

Auckland, New Zealand

Freecall: 0800 334 877

www.master-builders-solutions.basf.co.nz

BASF Emergency Advice:

1800 803 440 within Australia (24hr)

0800 944 955 within New Zealand