

MasterPozzolith® 370

Non-chloride water-reducing admixture

DESCRIPTION

MasterPozzolith 370 is a ready to use liquid admixture formulated to improve the performance of concrete in both the plastic and hardened states. **MasterPozzolith 370** is a non-retarding, water reducing, strength enhancing admixture which does not contain added chloride.

RECOMMENDED USES

- All types of concrete where a non-chloride water reducing admixture is required
- Improving the performance of pumped concrete, shotcrete and conventionally placed concrete
- Improving the performance of plain, reinforced, precast, lightweight or standard weight concrete
- Concrete subject to chloride ion constraints such as in coastal environments
- Use in white or coloured concrete
- Use in architectural concrete
- Concrete placed on galvanised steel floor and roof systems which are left in place

FEATURES AND BENEFITS

MasterPozzolith 370 admixture aids in the production of concrete with these special qualities:

In the plastic state:

- Superior finishing characteristics for slab work and off-form surfaces
- Normal setting characteristics under cool conditions allowing earlier finishing of slabs
- Reduced segregation particularly in lean mixes and high slump concrete
- Improved workability
- Improved pumpability
- Reduced water content for a given workability

In the hardened concrete:

- No added chlorides, conforms to the most stringent chloride ion limits including AS3600 concrete structures code, will not initiate or promote the corrosion of reinforcing steel
- Increased strength - compressive, flexural and bond (concrete to steel)
- Superior finished appearance
- Increased density and durability
- Reduced permeability - improved watertightness
- Reduced cracking
- Compatibility with air entraining agents

QUANTITY TO USE

MasterPozzolith 370 admixture is normally used at a dose rate of 300mL per 100kg of cementitious material depending on the composition of the basic ingredients of the concrete and ambient conditions. **MasterPozzolith 370** can be used in summer at 400 to 500mL per 100kg of cementitious material resulting in increased water reduction. The correct dosage rate in each instance should be determined by correctly conducted trials under the supervision of a BASF Technical Sales Representative.

COMPATABILITY

MasterPozzolith 370 can be used with air entraining agents and other BASF admixtures to achieve cost effective customised performance. However, all admixtures should be dispensed separately and added separately to initial batching water to ensure complete distribution throughout the mix. **MasterPozzolith 370** can also be used in mix designs including flyash, slag and silica fume. **MasterPozzolith 370** should not be used in conjunction with other admixtures unless specific test information is available.

PACKAGING

MasterPozzolith 370 is available in 1000 litre pallecons and bulk delivery.



We create chemistry

MasterPozzolith[®] 370

STORAGE / SHELF LIFE

Keep only in the original container in a cool, dry, well-ventilated place away from ignition sources, heat or flame. Store protected against freezing. Protect from direct sunlight.

MasterPozzolith 370 has a shelf life of 12 months.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from BASF office or website.

MasterPozzolith-370-ANZ-V9-0217

STATEMENT OF RESPONSIBILITY The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd ABN 62008437867 Level 12 28 Freshwater Place Southbank VIC 3006 Freecall: 1300 227 300 www.master-builders-solutions.basf.com.au	BASF New Zealand Ltd Level 4, 4 Leonard Isitt Drive Auckland Airport 2022 Auckland, New Zealand Freecall: 0800 334 877 www.master-builders-solutions.basf.co.nz	BASF Emergency Advice: 1800 803 440 within Australia (24hr) 0800 944 955 within New Zealand
--	--	--