

# MasterProtect 8020CI

Surface applied Corrosion Inhibitor

## DESCRIPTION

**MasterProtect 8020CI** is a surface applied corrosion inhibitor designed to migrate through even the densest concrete structures and form a layer on the steel reinforcing bars. **MasterProtect 8020CI** also protects a multitude of other metals including carbon steel, galvanised steel and aluminium. The corrosion inhibitor will migrate through concrete until it finds steel to create a protective layer on. **MasterProtect 8020CI** will stop the further corrosion of reinforcing metals and extend the service life of the structure.

## RECOMMENDED USES

**MasterProtect 8020CI** is recommended for:

- All reinforced, precast, prestressed, post-tensioned or marine concrete structures
- Steel-reinforced concrete bridges, highways and parking decks, ramps and garages exposed to corrosive environments (carbonation, deicing salts and salt spray)
- Concrete piers, dams, offshore platforms, piles, pillars, pipe and utility poles
- Preventative maintenance, restoration and repair of all reinforced concrete commercial and civil engineered structures
- Cooling towers and potable water tanks

## FEATURES AND BENEFITS

- **Migratory** - penetrates the concrete to find and protect the reinforcing steel. Offers engineers, owners, contractors and government authorities a time proven corrosion inhibiting technology that will extend the life of all reinforced concrete structures.
- **Slows existing corrosion** – reduces corrosion rate of corroding steel not yet visible.
- **Preventative treatment** – provides protection in new structures where insufficient cover is an issue.
- **Controls incipient anodes** – stops the formation of incipient anodes at new to old concrete interface.
- **Does not interfere with bond of repair mortars or coatings** – can be used directly onto areas to be repaired.
- **Forms passive layer underneath rust on steel** – slows corrosion to allow for longer term repair strategy to be put in place.

- **Easy application** - spray, roller, squeegee or paint brush to any concrete surface.
- **Water-based** - for easy handling and application.
- **Allows concrete to breathe and vapour to diffuse** - is not a vapour barrier.
- **Dual action inhibitor** - protects both anodic and cathodic areas.
- **No cure time is required** - traffic may resume minutes after application if necessary.

## PROPERTIES

Specific Gravity Density	1.01 – 1.03
Appearance	Clear amber
pH	10.4 – 11.5

## ESTIMATING DATA

3.5m<sup>2</sup>/l, dense substrates or application overhead may require 2 coats at the rate of 5.52m<sup>2</sup>/l.

## SURFACE PREPARATION

Surface should be dry, sound, clean and free of all dirt, oil, grease efflorescence, sealers, coatings, membranes and asphalt. Cleaning may be done by steam cleaning, waterblasting or sandblasting.

The substrate and ambient temperature should be above freezing. Do not apply if temperature is expected to fall below freezing within 12 hours.

**MasterProtect 8020CI** will not penetrate film-forming sealers, coatings, paints, membranes or asphalt.

## PACKAGING

**MasterProtect 8020CI** is supplied in 20 litre pails and 208 litre drums.

## SHELF LIFE

**MasterProtect 8020CI** can be stored for up to 24 months in the sealed, airtight pails supplied.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from BASF office or website



We create chemistry

# MasterProtect 8020CI

---

MasterProtect-8020CI-ANZ-V7-1016

**STATEMENT OF RESPONSIBILITY** The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

**NOTE** Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

**BASF Australia Ltd**  
ABN 62008437867  
Level 12  
28 Freshwater Place  
Southbank VIC 3006  
**Freecall: 1300 227 300**  
[www.master-builders-solutions.basf.com.au](http://www.master-builders-solutions.basf.com.au)

**BASF New Zealand Ltd**  
Level 4, 4 Leonard Isitt Drive  
Auckland Airport 2022  
Auckland, New Zealand  
**Freecall: 0800 334 877**  
[www.master-builders-solutions.basf.co.nz](http://www.master-builders-solutions.basf.co.nz)

**BASF Emergency Advice:**  
1800 803 440 within Australia (24hr)  
0800 944 955 within New Zealand