

MasterProtect® 815CP

A variable consistency fast setting grout, for embedding discrete anodes

DESCRIPTION

MasterProtect 815CP is a cementitious grout/mortar that is specifically formulated for embedding discrete anodes used in impressed current cathodic protection installations of reinforced concrete. **MasterProtect 815CP** is especially developed for optimum life expectancy of these CP installations. **MasterProtect 815CP** is a blend of hydraulic cements, selected silica, modifying agents and special additives for pH buffering. When mixed with potable water, **MasterProtect 815CP** forms a fast-setting grout with extraordinary flow characteristics.

RECOMMENDED USES

Embedding discrete anodes used in impressed current cathodic protection installations.

FEATURES AND BENEFITS

- **Improved acid resistance compared to normal grouts against the chemicals created at the anode surface** – long life of the anode encasement.
- **Low resistivity** – enhances current flow through anode.
- **Expands during setting** - guarantees good filling of the hole and embedding of the anode.
- **Fast strength gain** – set in 30 minutes and 2.5MPa in 1 hour.

SPECIFICATIONS

Supply form	Powder
Grain size (max)	0.4mm
Water added per bag (20kg)	3 – 5 litres
Colour	Grey
Density (mixed)	2.14kg/L
Compressive Strength (@4.2 litres/20kg bag)	
- 1 hour	2.5 MPa
- 7 days	25 MPa
- 28 days	40 MPa
Flexural strength 7 days	4 MPa
Electrical Resistivity (Wenner 4 probe method)	
- 7 days	~2000 Ω.cm
- 28 days	~5000 Ω.cm
- 56 days	~8000 Ω.cm
- 90 days	~11000 Ω.cm

APPLICATION

Substrate Preparation

Loose particles in the holes should be removed. Slightly dampen the substrate if possible and remove free standing water.

Mixing

Pot life	± 12 minutes
Final set	± 25 minutes

Approximately 4.2 litres of water per 20kg powder is necessary in order to obtain a free flowing consistency. The water dose can change depending on the required consistency but should be kept between the limits of 3.0 to 5 litres clean water per 20 kg powder.

To control set time it is advised to use warm water in cold environments and cold water in warm conditions.

MasterProtect 815CP may be mixed either mechanically or manually. Gradually blend the powder into clean water. Mix until lump free consistency is obtained. Do not overmix.

Application

Do not apply **MasterProtect 815CP** if ambient temperature is below 5°C or expected to fall below 5°C within 4 hours.

All holes can simply be filled with the material. To assist complete filling of those holes, it can be necessary to move the anodes up and down, in order to release any entrapped air.

ESTIMATING DATA

A 20kg bag of **MasterProtect 815CP** mixed with 4.2 litres of water yields 11.3 litres.

L	Thickness in mm /m ²	m ³	Bags /m ³	m ² /mm thickness
11.3	11.3mm	(0.0113)	89	11.3 m ²



We create chemistry

MasterProtect® 815CP

CURING

MasterProtect 815CP is self-curing. In hot, dry or windy environments it can be necessary to cover the material with some wet cloths after the initial set.

CLEANING

MasterProtect 815CP is a cementitious product. Tools should be cleaned with water before the material hardens.

PACKAGING

MasterProtect 815CP is available in 20kg moisture resistant paper bags.

SHELF LIFE

MasterProtect 815CP is can be stored in tightly sealed original bags for 12 months if kept dry and at moderate temperature.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from our office or our website.

MasterProtect-815CP-ANZ-V5-0317

STATEMENT OF RESPONSIBILITY	The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.	
NOTE	Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.	
BASF Australia Ltd ABN 62008437867 Level 12 28 Freshwater Place Southbank VIC 3006 Freecall: 1300 227 300 www.master-builders-solutions.basf.com.au	BASF New Zealand Ltd Level 4, 4 Leonard Isitt Drive Auckland Airport 2022 Auckland, New Zealand Freecall: 0800 334 877 www.master-builders-solutions.basf.co.nz	BASF Emergency Advice: 1800 803 440 within Australia (24hr) 0800 944 955 within New Zealand