

# MasterTop<sup>®</sup> 200

Iron aggregate surface hardener

## DESCRIPTION

**MasterTop 200** is an iron-armoured, dry-shake surface hardener for industrial floors needing additional abrasion resistance and impact protection. It is designed to be applied over freshly floated concrete to provide an iron armoured monolithic floor.

**MasterTop 200** contains specially processed iron aggregate in a cementitious binder.

## RECOMMENDED USES

**MasterTop 200** is recommended for:

- Industrial installations needing extra abrasion resistance and impact armoring
- Distribution warehouses
- Mine facilities
- Aircraft hangers
- Power stations
- Loading bays
- Workshops
- Industrial floor surfaces subject to heavy or frequent traffic, steel wheels, AGV's, fork lifts

Do not use in areas where floor surfaces will be exposed to acids, their salts, or like materials, which seriously and rapidly attack cement and/or iron. Alternate solutions such as Ucrete are suitable for this application.

## FEATURES AND BENEFITS

- **Increased abrasion resistance** – up to 8 times greater than plain concrete.
- **Much greater compacted density** – increases resistance to penetration by oil, grease, hydraulic fluids, ethylene glycol and many industrial chemicals.
- **Increased surface density** – allows easier and less expensive maintenance because absorption of water and cleaning agents is reduced.
- **Finished from smooth to slip resistant** – iron aggregate makes this product a virtually non-dusting surface hardener that may be finished to meet any requirement.
- **100% iron aggregate** - specially processed for strength.
- **Available in an energy saving version** – light reflective formulation can reduce the number and intensity of the lighting needed in a warehouse.
- **Economic and fast application** – reduced construction time floor surface applied at the time of concrete placement.

## PROPERTIES

Thickness at 7.5 kg/m <sup>2</sup> :	2.8mm average
Abrasion resistance (ASTM C779):	0.20mm at 60 minutes (33MPa concrete more than 1.4mm at 60 minutes)
Impact resistance (LA Rattler):	30% weight loss (33MPa concrete has 70% loss of weight)

The performance data is typical and based on controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions.

## ESTIMATING DATA

The rate of application will depend on the service conditions that the floor will be exposed to. The following rates are provided as a guide:

Service Conditions	Rate of Application (kg per m <sup>2</sup> )
Light to Moderate	3.0 to 5.0
Moderate	5.0 to 7.5
Heavy Duty	7.5 to 9.0
Very Heavy Duty	9.0 to 11.0

MasterTop 200		
	Bag	bags /100m <sup>2</sup>
Light (5kg/m <sup>2</sup> )	4m <sup>2</sup>	25
Moderate (7.5kg/m <sup>2</sup> )	2.7m <sup>2</sup>	38
Heavy Duty (9kg/m <sup>2</sup> )	2.2m <sup>2</sup>	46
Very Heavy Duty (11kg/m <sup>2</sup> )	1.8m <sup>2</sup>	56

## APPLICATION

### Preparation of the concrete

Concrete for single course monolithic floors should be capable of achieving a 28 day compressive strength of 30MPa with a slump of 80 to 110 mm, and with no more than 3% air. Concrete should not contain calcium chloride.



We create chemistry

# MasterTop<sup>®</sup> 200

**MasterTop 200** is applied as a dry shake over freshly wooden bull floated concrete. For information about application, please obtain a copy of the BASF “*Application Guide for MasterTop 200*” from BASF.

1. Application is strongly recommended to be done after the roofing is completed. ONLY attempt modest size slabs without a roof.
2. Use only admixtures in the concrete that are approved by BASF.
3. Do not use water, burlap or polyethylene covering for curing. Use only curing compounds approved by BASF.

## COLOURS

**MasterTop 200** is available in natural (concrete colour) and light reflective. Please BASF with regard to minimum order quantities and lead times for coloured products

## IRON ARMoured JOINTS

Iron-armoured joints consisting of **MasterTop 200** mortar incorporated into the freshly placed concrete joint edges greatly prolong the life of the joints. Iron armoured joints provide a 10 to 15 times greater serviceable life than a normal concrete joint edge.

Refer to the BASF Application Guide for application details. Allow 3.3kg per lineal metre for one side of the joint.

## FIELD SERVICE

BASF Construction Chemicals recommends that the user request the free services of BASF for a pre-job conference to carefully plan each step of the installation.

## PACKAGING

**MasterTop 200** is packaged in ready-to-use 20kg moisture resistant bags. No further measuring or mixing of ingredients is required at the jobsite.

## SHELF LIFE

**MasterTop 200** can be stored in its original packaging for 12 months. Do not store in direct sunlight.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from BASF office or website.

MasterTop-200-ANZ-V6-0418

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

**BASF Australia Ltd**  
 ABN 62008437867  
 Level 12  
 28 Freshwater Place  
 Southbank VIC 3006  
**Freecall: 1300 227 300**  
[www.master-builders-solutions.basf.com.au](http://www.master-builders-solutions.basf.com.au)

**BASF New Zealand Ltd**  
 Level 4, 4 Leonard Isitt Drive  
 Auckland Airport 2022  
 Auckland, New Zealand  
  
**Freecall: 0800 334 877**  
[www.master-builders-solutions.basf.co.nz](http://www.master-builders-solutions.basf.co.nz)

**BASF Emergency Advice:**  
 1800 803 440 within Australia (24hr)  
 0800 944 955 within New Zealand