

# MasterRoc<sup>®</sup> MP 355 1K

Formerly MEYCO MP 355 1K

One component polyurethane injection foam to stop small to mid-volume water ingress

## Product description

MasterRoc MP 355 1K is a solvent free, one component polyurethane foam which reacts only in contact with humidity or water.

## Fields of application

- Stopping of small to mid-volume water ingress in underground structures
- Also suitable for filling of water bearing voids

## Features and benefits

- Reacts in moist surroundings
- Good bonding to wet surfaces

## Packaging

MasterRoc MP 355 1K: 25 kg cans  
Accelerator for MasterRoc MP 355 1K: 2.5 kg cans

## Technical data

### MasterRoc MP 355 1K

Density, 20°C	1.16 g/cm <sup>3</sup>
Viscosity, 23°C	320 mPa.s
Color	Brown
Application temperature	+ 5°C to 40°C
Maximum foam expansion rate at 10% accelerator dosage	25-30

### Accelerator for MasterRoc MP 355 1K

Density, 20°C	1.10 g/cm <sup>3</sup>
Viscosity, 23°C	70 mPa.s
Color	Clear to yellowish

## Application procedure

Wet conditions:

1. Add the accelerator to MEYCO<sup>®</sup> MP355 1K (between 2-10%, depending on the required reaction time) (See Table 1), mix quickly and thoroughly
2. Inject this mixture through a single component injection pump. The

moisture / water in the ground or structure will cause the foaming reaction.

Dry conditions:

1. For injection purposes, flush holes with water to thoroughly wet the injection area.
2. Add accelerator to MEYCO<sup>®</sup> MP355 1K (between 2-10% depending on the required reaction time) (See Table 1), mix quickly and thoroughly.
3. Inject this mix through a single component injection pump.

## Reaction Time

The reaction time depends on the ground and product temperature, as well as the accelerator dosage (see Table 1). Site trials should be performed in advance to establish the required reaction time.

Table 1:

Reaction Times with 10% water and 10% accelerator				
Initial Temperature (°C)	5	10	15	20
Start of reaction (sec)	120	60	25	10
End of reaction (sec)	300	200	110	50
Foam expansion rate (approximately)	25	25	25	30

## Cleaning of injection equipment

During short breaks in the injection procedure, the pump and hoses should be filled with non-accelerated resin to avoid blockages. After finishing the injection, pump an appropriate agent or oil which does not contain water through the pump and injection lines.

## Storage

MasterRoc MP 355 1K must be stored in airtight containers in a cool, dry place. If stored in original



The Chemical Company

# MasterRoc<sup>®</sup> MP 355 1K

---

Formerly MEYCO MP 355 1K

containers under the above mentioned conditions, it has a shelf life of 12 months. The product must be prevented from freezing.

## Safety precautions

MasterRoc MP 355 1K is not hazardous. However follow standard safety procedures when handling the product and wear gloves and safety glasses.

Avoid eye and skin contact. If skin contact occurs, wash with plenty of water and soap. In case of eye contact rinse with plenty of water and seek medical advice. For further information refer to Material Safety Data Sheet.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand, and disposed of in accordance with local regulations.

The information given here is true, represents our best knowledge and is based not only on laboratory work but also on field experience. However, because of numerous factors affecting results, we offer this information without guarantee and no patent liability is assumed. For additional information or questions, please contact your local representative.

## Headquarters:

### **BASF Construction Chemicals Europe Ltd**

Global Underground Construction

Im Tiergarten 7

8055 Zurich

Switzerland

Phone +41 58 958 22 11

Fax +41 58 958 32 46

For more information: Visit us: [www.ugc.basf.com](http://www.ugc.basf.com) Contact us: [ugc@basf.com](mailto:ugc@basf.com)

® = registered trademark of BASF group in many countries