

MasterTop 1324

Resilient, crack bridging, polyurethane flooring system

DESCRIPTION

A 1-4mm thick self smoothing resilient polyurethane flooring system provides a tough scratch resistant floor finish suitable for use on substrates subject to vibration and dynamic forces.

MasterTop 1324 is a seamless floor without joints or welds even around columns and over large open areas. Whilst being robust enough for industrial applications, the fully light stable topcoat enables light colours to be used with confidence in bright commercial and retail environments.

FIELD OF APPLICATION

MasterTop 1324 is used to provide bright durable floors for industrial and commercial applications.

- Production and assembly halls
- Pharmaceutical clean rooms
- Retail and fashion
- Warehousing
- Office, exhibition and show room floors
- Hospital and old people's homes
- Technical areas and plant rooms

In wet areas the antislip finish should be used.

FEATURES AND BENEFITS

- Flexibility enhances impact resistance and accommodates flexure of suspended substrates
- Joint free, even around columns and over large areas for maximum aesthetic freedom
- Can be installed on to old asphalt substrates
- Monolithically bonded to the substrate
- Seamless coving available without seams or welds even at external corners and columns
- Low emission to AgBB
- LEED certification
- 40 year life cycle costing

SLIP RESISTANCE

Slip resistance will vary depending upon the method and conditions of application, the nature of any polishes used and the standards of housekeeping. Typically the coefficient of friction as measured using the TRRL slip resistance tester and 4S rubber is as follows:

	Dry	Wet
Standard finish	75	-
Slip resistant finish	60	36

COLOURS

A range of colours are available contact your local BASF plc, Construction Chemicals office for further information.

CLEANING AND MAINTENANCE

Suitable trap mats should be installed at entrances open to the street. The use of acrylic polish can provide a degree of shine and help maintain the floor in a pristine condition. A wet clean with mild organic detergents will help keep the floor clean and bright. For further information consult separate cleaning and maintenance guidelines.

METHOD STATEMENT ENVIRONMENT

The applicator requires sole access to the floor area throughout the application. The area should be closed to the environment, clean and dust free. Dust from trades in adjacent areas can impair the visual appearance of the finish.

It is prudent to ensure that the floor installation is undertaken as the final operation during refurbishment works to preclude damage by other trades.

For best results, materials, substrate and air temperature should be in the range 15–20°C.

Low temperatures will reduce workability and can impair the visual appearance of the floor. High temperatures will shorten the open times and can impair the appearance of the floor.

Do not commence work if temperatures are within 3°C of the dew point or if condensation is likely to occur within 48 hours (at 20°C) of application.

SUBSTRATE

Specialist finishes should not be applied to concrete with more than 4% moisture by weight. On new concrete with a high residual moisture content use MasterTop P621, see separate data sheet. A functioning damp proof membrane must be installed under on-grade concrete and known to be effective.

MasterTop 1324 must be applied to a clean, dry substrate free from dust, dirt, oil, grease and other contaminates. A clean surface will ensure adhesion between substrate and overlay.

MasterTop 1324

Resilient, crack bridging, polyurethane flooring system

Use mechanical methods of surface preparation as dictated by the size of area to be treated, the location and degree of contamination.

The substrate should be sound with a tensile strength exceeding 1.5 MPa. Any repairs to the substrate must be undertaken in good time prior to the application.

Asphaltic substrates must be old and stable, well bonded to the substrate and prepared by captive shot blasting to expose the aggregate.

JOINTS

MasterTop 1324 is elastic enough to accommodate substrate movement. Such joints being routed out and filled with MasterTop BC375N prior to application of the floor. Structural movement joints however should be continued up through the floor.

FREE EDGES

Use metal edging strips to protect free edges including at abutments to other finishes.

PRIMING

Prime the substrate with MasterTop P617, see separate data sheet, and broadcast evenly with FILLER F5 while the primer is still wet and allow to fully cure.

Concrete substrates must be completely sealed, some substrates may require double priming.

Asphaltic substrates are primed using MasterTop BC375N, see separate data sheet.

BODY COAT

MasterTop BC375N, see separate data sheet, is applied using pinrake and trowel maintaining a wet edge throughout.

For a slip resistant finish, broadcast aggregate into the body coat. Once cured encapsulate the aggregate with a further coating of MasterTop BC375N.

TOP COAT

Apply MasterTop TC441P or MasterTop TC407W, see separate datasheet.

Optional coloured flake scatter and clear seal may be applied to produce a variety of aesthetic effects.

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.


MasterTop 1324

Resilient, crack bridging, polyurethane flooring system

CONTACT DETAILS

BASF plc,
Construction Chemicals,
19 Broad Ground Road
Lakeside
Redditch
Worcestershire
B98 8YP
Tel: +44 (0) 1527 512255
Fax +44 (0) 1527 503576
www.master-builders-solutions.basf.co.uk

© BASF plc, Construction Chemicals

	
1508	
BASF Construction Chemicals 19 Broad Ground Road Lakeside, Redditch Great Britain B98 8YP	
12	
132401	
EN 13813:2002	
Synthetic resin screed material	
Fire behaviour	Bfl-s1
Release of corrosive sub-stances	SR
Water permeability	NPD
Wear resistance	< AR 1
Bond strength	> B 1,5
Impact resistance	> IR 4
Impact sound insulation	NPD
Sound absorption	NPD
Heat insulation	NPD
Chemical resistance	NPD
Slip/Skid resistance	R9, R10
Emissions behaviour	Ü-Z: Z- 156.605-685

MasterTop 1324

Resilient, crack bridging, polyurethane flooring system

MasterTop 1324 - BASF plc, Construction Chemicals, Version 1

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"BASF plc, Construction Chemicals" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.