

MasterProtect H 303

Clear Water Repellent Based on Alkyl Alkoxysilane for the Protection of Concrete Surfaces BD 43/03 Compliant

DESCRIPTION

MasterProtect H 303 is a single component clear, deeply penetrating water repellent used to protect both vertical and horizontal concrete surfaces from deterioration by atmospheric pollution, salt attack and freeze thaw cycles etc.

FIELDS OF APPLICATION

To protect vertical and horizontal concrete surfaces such as:


- Buildings
- Bridges
- Highways
- Concrete barriers
- Car parks
- Sports stadia
- Cooling towers
- Water towers

FEATURES AND BENEFITS

- Provides a long-lasting protection: MasterProtect H 303 penetrates deep into the surface acting as a water repellent that prevents water, salts (chloride ion), atmospheric pollution and freeze/thaw cycles from deteriorating the concrete
- Improves the aesthetics by reducing efflorescence, algae growth and dirt build-up
- Surface appearance remains unchanged
- Reduces volatile organic emissions into the atmosphere in comparison with today's commonly used organic-solvent-based repellents
- Provides a safer working environment for the applicator by minimising health hazards associated with organic solvents
- Ready for use; no dilution on site, which means constant quality
- One coat, no primer
- Masking window plate glass is not necessary before spray application
- May be applied to damp substrates
- Application equipment easily cleaned with soapy water
- Virtually no product evaporates during spray application, therefore more active silane can reach its intended target, so minimising wastage and maximising coverage

TEST & APPROVALS

The following independent data is available upon request:
 CTL (USA), Protection against water absorption (NCHRP)
 TRL (UK), Chloride ion protection
 CTC (USA), Freeze/thaw protection (ASTM C672)
 CTC (USA), Accelerated weathering results (NCH RP)
 TNO (NL), Approval for bridge decks and other structures
 SINTEF (N), Chloride diffusion constant

 0749	
BASF Belgium Coordination Center Comm. V. Business Belux - Construction Chemicals Nijverheidsweg 89, B-3945 Ham	
11 BE0001/01	
EN 1504-2 Water based, alkyl alkoxy silane, hydrophobic treatment 1504-2 Principles 1.1 / 2.1 / 8.1	
Penetration depth	Class I
Water absorption and alkali resistance	Pass
Drying time	Class I
Freeze/Thaw resistance	Pass

APPLICATION PROCEDURE SUBSTRATE PREPARATION

New concrete surfaces should be cleaned of all sand, surface dust/dirt, oil, grease, chemical films/coatings and other contaminants before applications.

A complete water, sand, or shot blast may be needed to achieve the desired surface condition.

Crack control, caulking, patching and expansion joint sealants can be installed before and after application of the sealer. Cure in accordance with manufacturer's instructions.

APPLICATION METHOD

Application

Surface, air and material temperature should be between 5 and 35°C during application.

MasterProtect H 303

Clear Water Repellent Based on Alkyl Alkoxysilane for the Protection of Concrete Surfaces BD 43/03 Compliant

Surfaces to be treated can be slightly damp, but for best results a dry surface is suggested for maximum penetration. MasterProtect H 303 should not be applied if frost, ice or standing water are visible on the surface to be treated.

Note: Do not apply MasterProtect H 303 when temperatures are expected to fall below 5°C within 12 hours or rain is expected within 4 hours of completed application.

Test a small area of the concrete surface before starting general application of any clear, penetrating sealer to assure desired results and coverage rates.

While this product is far less harmful to plant life than solvent-based surface sealers, vegetation should be protected from over-spray. Equipment and incidental areas of over-spray should be cleaned immediately with soapy water to avoid permanent staining. MasterProtect H 303 will leave a visible residue on non-porous materials such as glass, metal and painted surfaces. When cured, dried materials can be removed by scraping with a metal blade.

Stir material thoroughly before and during application.

Apply to saturation. This may be done with a low-pressure spray (Knapsack Hopper-type), or by pouring, followed by brooming for even distribution on horizontal surfaces. Normal coverage rates are approximately 3 to 5m²/ltr. (On lightweight concrete or more porous concrete surfaces, the coverage may be less.)

It is recommended that horizontal surfaces treated with MasterProtect H 303 are left for a minimum of 4 hours to allow proper penetration. MasterProtect H 303 may leave temporarily a slippery surface for several hours after application. Therefore, vehicle traffic areas should not be re-opened until the treated surface is dry.

PACKAGING

MasterProtect H 303 is available in 20 litre plastic containers.

COVERAGE

Coverage rates may vary with the porosity and finish of the substrate. Typically the coverage on concrete is 3 to 5m²/ltr. A 20-litre unit will typically cover 60-100 m²

STORAGE

MasterProtect H 303 should be stored under cover, clear of the ground and stacked not more than 2 containers high. Protect from freezing.

SHELF LIFE

Rotate stock in order not to exceed the shelf life of 12 months. Storage temperature should not exceed 35°C.

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

CONTACT DETAILS

BASF plc,
Construction Chemicals,
19 Broad Ground Road
Lakeside
Redditch
Worcestershire
B98 8YP
Tel: +44 (0) 1527 512255
Fax +44 (0) 1527 503576
www.master-builders-solutions.basf.co.uk

© BASF plc, Construction Chemicals

MasterProtect H 303

Clear Water Repellent Based on Alkyl Alkoxysilane for the Protection of Concrete Surfaces BD 43/03 Compliant

Product Data			
Property	Standard	Unit	Data
Chemical Base	-	-	Water based alkyl alkoxysilane
Solid Content	-	%	20
Color	-	-	White (Clear when cured)
Density (23 °C)	-	g/cm ³	1.01
Chloride diffusion (vs. reference concrete)	-	%	7
Water absorption test (vs. reference concrete)	-	%	5.3 – 8.3
Flash Point	ASTM D 3278-82	Celcius	>93
Water vapor transmission rate	Oklahoma DOT-OHD-L-35	%	102

(a) Typical values: all tests carried out at 20°C unless otherwise stated

MasterProtect H 303 - BASF plc, Construction Chemicals, Version 2

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"BASF plc, Construction Chemicals" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.