

MasterEmaco[®] S 322

Non shrink, natural aggregate, fibre reinforced flowable repair mortar for marine environment structure and concrete repair.

DESCRIPTION

MasterEmac S 322 is non-shrink, natural aggregate repair mortar with excellent high early and ultimate strengths. It is specially formulated for marine environment, while providing extended working time even at high ambient temperatures when mixed and placed at any recommended consistency.

MasterEmaco S 322 compensates shrinkage in both plastic and hardened states and meets specification of ASTM C-1107

MasterEmaco S 322 also has an excellent impermeability against salt water and high durability due to the existence of silica fume.

RECOMMENDED USES

- All non-shrink repair application in marine environment structure with clearances of 10mm or more including:
- Maintenance of civil structures
- Extensive repair to beams, slab and other structural elements.
- Reinstatement of honeycombed or defective structural concrete
- High slump and good pumpability for formed applications.

FEATURES AND BENEFITS

- **High early strength** – ensure rapid commissioning of new structures and minimum downtime on repair work
- **Flowable long life repair mortar** – easy to fill intricate spaces normally inaccessible by conventional repair technique.
- **Extended working time** – up to 1.50 hours even at high ambient temperatures. Facilitates grouting of large or difficult placements in a single pour, often without the use of a pump.
- **Non staining** – contains no metallic aggregates and is similar in appearance to plain concrete. Suitable for the architectural finishes.
- **Easy to use** - requires no special mixing equipment. It can be mixed in a standard concrete mixer or in a pail using grout stirrer.

- **Dual expansion systems for controlled expansion** – dense and non-shrink, even in the hardened state.

PROPERTIES

Supply Form	Powder	
Colour	Cement grey	
Density (wet) Flowable	2.25	
Plastic	2.28	
Flow trough (cm) Flowable	30-50	
	Flowable	
Compressive strength	1 day	30 MPa
	3 days	50 MPa
	7 days	60 MPa
	28 days	70 MPa
Flexural strength	28 days	10.5 MPa
Tensile strength	28 days	5.5 MPa
Estimate setting time	Initial	5hrs
	Final	6 hrs

APPLICATION

Surface preparation

The substrates should be properly prepared and should be free from contamination, laitance and loose material. Thoroughly saturate the substrate with water at least 2-3 hours prior to pouring the grout. All free water ponding should be blown out of the void just before pouring the grout.

As for all cementitious materials curing is essential to prevent rapid drying out of the grout and shrinkage caused by the water loss. Curing should be effected by accepted methods such as curing compound, polythene sheet, wet hessian or water ponding.

MasterEmaco[®] S 322

Mixing

MasterEmaco S 322 is supplied in a ready to use form requiring the addition of water only. DO NOT add cement, sand, pea gravel or other materials. DO NOT use hardened or lumpy grout caused by torn or water-damaged bags.

Mix with drinkable water only. DO NOT MIX BY HAND. For small quantities use a grout stirrer and slow speed electric drill, adding all mixing water to empty pail, then add dry grout in a steady stream while mixing. Continue mixing for approximately 2 minutes.

For larger quantities a paddle type mortar mixer is preferred. Add 80% or mixing water first, then dry grout to form a stiff consistency. Continue mixing at this consistency for about 1 minute. Add remainder of water steadily until desired consistency is achieved. Total mix time should be 4 to 5 minutes.

Do not use excess water. Discard any grout that has been left so long it has stiffened. Do not re-temper

Placing

MasterEmaco S 322 has been formulated for placing by pouring or pumping to required thickness. Its extended working life properties allow sufficient time for placement to be completed without problems.

ESTIMATING DATA

A 25 kg bag of **MasterEmaco S 322**, when mixed in accordance with BASF Construction Chemicals recommended procedures, will provide the following yields:

Types	Water	Yield
Normal	4.2 litres	13 litres
With Pea Gravel	3.4 litres	12.6 litres

PACKAGING

MasterEmaco S 322 is supplied in 25kg bag

SHELF LIFE

MasterEmaco S 322 has a shelf life of 6 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

® = registered trademark of BASF group in many COUNTRIES

HK# MasterEmaco S322 v2-1217

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they and not BASF, are responsible for carrying out procedures appropriate to a specific application

BASF Construction Chemicals offices in ASEAN

Singapore

Tel :+65-6861-6766
Fax:+65-6861-3186

Malaysia

Tel :+60-3-5628-3888
Fax :+60-3-5628-3776

Indonesia

Tel: +62-21-2988-6000
Fax: +62-21-2988-5935

Thailand

Tel :+66-2769-8564
Fax :+66-2769-8584

Vietnam

Tel :+84-650-3743-100
Fax:+84-650-3743-200

Hong Kong

Tel:+852-2408-4400
Fax:+852-2408-4401