

# MasterProtect® 180

## A non-toxic solvent free high build, protective epoxy resin coating

### DESCRIPTION

**MasterProtect 180** is a protective high build epoxy resin coating specifically developed to protect concrete. Supplied as a two-component system comprising pigmented base and a hardener, it requires only on site mixing to produce an easily applied decorative and chemically resistant finish. **MasterProtect 180** can be safely used in areas where contact with foodstuffs is envisaged or for coating potable water storage tanks. It is solvent free and can be used with safety in small rooms or tanks without the need to provide special ventilation. **MasterProtect 180** coatings will not support the growth of bacteria.

### PRIMARY USES

For the internal protection of concrete tanks containing drinking water, certain chemicals, oils and fuel. Contact your BASF representative for further advice.

As an impervious, resilient and chemically resistant floor or wall coating in food manufacturing plants, breweries, canning and bottling factories. As a gas and vapour barrier.

As a protective and decorative coating in laboratories, abattoirs, etc. Other usage areas include oil refineries, paper mills, power stations, garages, hospitals, sugar refineries, hangars and most liquid containment areas.

### APPEARANCE AND FINISH

High gloss, heavy bodied, ultra dense surface. Hygienic and easily cleaned. Standard colours are light grey and dusty grey.

### ADVANTAGES

- Durable
- Non-toxic
- Waterproof and protective
- High chemical resistance
- High temperature water resistance
- Solvent free
- High build coating
- Easily applied by brush, roller or airless spraying equipment

### PACKAGING

**MasterProtect 180** is supplied in 5kg units.

### TYPICAL PROPERTIES\*

|                                |                                   |
|--------------------------------|-----------------------------------|
| Working life at 25°C           | 40 minutes                        |
| Mixed density at 25°C          | 1.5g/cm <sup>3</sup>              |
| Initial cure                   | 24 hours @ 25°C                   |
| Final cure                     | 7 days @ 25°C                     |
| Coverage                       | 0.3-0.6kg / m <sup>2</sup> / coat |
| Total dry film thickness       | Min 400 microns                   |
| Bond to concrete<br>ASTM D4541 | >1.5N/mm <sup>2</sup>             |

### APPROVALS

WRAS Approval for use with Potable Water.  
Note: For BS 6920 conformity test, product was applied in 2 coats; the first was cured @ 20°C for 36 hours and second coat cured @ 20°C for 21 days.

### APPLICATION PROCEDURE

#### SURFACE PREPARATION

The substrate should be a smooth or semi-smooth sound surface such as concrete or metal. It is most important to ensure that thorough surface preparation is undertaken prior to application of the **MasterProtect 180** coating.

#### CONCRETE

Ensure concrete is free from excessive laitance, grease, oil, curing compound, etc. Ensure concrete is sound, cutting back where necessary and making good using suitable BASF

**MasterEmaco** or **MasterBrace** repair systems. Ensure all blow holes and surface imperfections are made good prior to application of the **MasterProtect 180** coating.

Ensure concrete is at least 28 days old. Contamination by oil, grease, fats etc. must be removed before other forms of preparation begin. Remove laitance to expose blow holes, by light grit blasting.

# MasterProtect® 180

## MIXING

**MasterProtect 180** is supplied in two pre-weighed components, base and reactor. No additions or omissions are required. Add reactor contents to the base component and mix thoroughly for using a slow speed drill fitted with a suitable mixing paddle until a uniform streak free colour is achieved.

## APPLICATION

**MasterProtect 180** coating can be applied using good quality rollers or short haired brushes or by airless spray. It is recommended that **MasterProtect 180** coating be applied in two coats of contrasting colours to ensure complete coverage. Prior to the application of each coat the surface should be examined for signs of pin-holing, etc. Where pin-holing is evident these should be filled using **MasterBrace ADH 2200** thixotropic epoxy resin filler.

If the application is delayed more than 16 hours at 40°C or 36 hours at 20°C after the previous coat (the higher the ambient temperature, the shorter the maximum period), then the previous coat must be thoroughly abraded to give an adequate mechanical key and solvent wiped.

## AIRLESS SPRAY

For application by airless spray, use a 45:1 or higher ratio pump, minimum 9mm dia hoses and HD tip 19-23 thou.

## OVERCOATING

Where areas need to be overcoated due to damage etc. it is important that the areas to be treated are well abraded using a stiff rotary wire brush or coarse sand paper to give an adequate key. Completely strip off any unsound coating and proceed with overcoating as for new work.

## CHEMICAL RESISTANCE

**MasterProtect 180** is resistant to intermittent spillages of the following typically encountered chemicals:

- Formaldehyde, 40% solution
- Sulphuric Acid, 50% solution
- Hydrochloric Acid, 50% solution
- Hydrochloric Acid 5% solution
- Lactic Acid, 50% solution
- Nitric Acid, 10% solution
- Sodium Hydroxide, 50% solution
- Diesel oil
- Wine
- Sea and brackish water
- Aviation hydraulic fuels (Skydrol)
- Vegetable oils

**Note:** Higher concentration of mineral acids may cause matting of the surface and colour changes.

## EQUIPMENT CARE

All equipment must be cleaned immediately after use with **MasterTop THN 2**. Similar cleaning procedures should be adopted for break periods exceeding 15 minutes duration.

## SPECIFICATION CLAUSE

**MasterProtect 180:** Where indicated, apply **MasterProtect 180** protective epoxy coating as manufactured by BASF, or similar approved to the following specification:

|                          |                                                                             |
|--------------------------|-----------------------------------------------------------------------------|
| Composition              | Two component, non-toxic, pigmented solventless epoxy resin based compound. |
| Coverage                 | 0.3-0.6kg/m <sup>2</sup> /coat, two coats are recommended.                  |
| Total dry film thickness | Min 400 microns                                                             |



We create chemistry

# MasterProtect® 180

## STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

## SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use. For further information, refer to material safety data sheet.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF\_CC-UAE/Pr\_180\_02\_95/v3/10\_15

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

### BASF Hong Kong Limited

Unit 2, 20/F EW International Tower, 120-124 Texaco Road, Tsuen Wan, N.T., Hong Kong  
Tel: (+852) 2408 4400  
Fax: (+852) 2408 4401

