



We create chemistry

MasterSeal[®] HLM 5000

Liquid cold-applied waterproofing membrane system

DESCRIPTION

MasterSeal HLM 5000 is a single component, bitumen modified, polyurethane based waterproofing membrane that cures by reaction with atmospheric moisture to form a tough membrane. **MasterSeal HLM 5000** protects structures from water penetration while remaining flexible to handle the nominal expansion and contraction of substrates.

RECOMMENDED USES

Waterproofing exterior, below grade concrete and between concrete slab applications.

FEATURES AND BENEFITS

- **Waterproof** - Protects structure from water penetration
- **Elastomeric** - Permits nominal expansion and contraction of the structure
- **Inert when cured** - Resists bacterial attack and salts found in ground waters
- **Monolithic Single pack and one coat finish liquid-applied** - Eliminates lapping, seaming, and precutting
- **Single pack and one coat finish**
- **Tough and durable** - Long-term protection

PROPERTIES

Property	Results	Test Method
Shore OO hardness	85	ASTM C 836
Tensile strength – MPa	1.0	ASTM D 412
Average elongation %	600	ASTM D 412
100% modulus - MPa	0.6	ASTM D 412
Moisture vapor permeability, dry perms	0.1	ASTM E 96
Crack bridging test, cycled 10 times per 24 hours at -9°C	Passed @1.5mm	ASTM C 836
Extensibility after heat ageing	No cracking	ASTM C 836
Weight loss (20% max)	16%	ASTM C 836

Supply form	Liquid
-------------	--------

Colour	Black
Viscosity in poise of various grades, Brookfield	Self Level – 125, Spray – 450, Roller – 800,
Application temperature	5°C to 35°C
Minimum recovery	90%
Swelling in water	Nil
Service temp, range	-40°C to 50°C
VOC Content	Self level-183 g/L Spray- 190 g/L Roller-180 g/L

STANDARDS

- ASTM C 836
- National standard of Canada 37.58-M86 developed by CGSB

APPLICATION

Surface Preparation

For best results, all concrete deck surfaces should be lightly steel troweled to a flat, uniform surface. A light broom finish is acceptable. New concrete must be properly water cured at least 14 days. Membrane curing compounds must be mechanically removed.

For extremely porous block: Prime with a coat of MasterSeal HLM 5000 diluted up to 25% with xylene.

Remove dust, dirt and other contaminants just before or during application. Surfaces must be dry at the time of application. Air-void pockmarks or honeycombs must be opened up to allow MasterSeal HLM 5000 to fill the cavities completely.

Pre-striping

Before applying the final membrane, all joints, cracks and openings around protrusions must be sealed by caulking or pre-striping (a preliminary coating of MasterSeal HLM 5000 applied with a trowel or stiff-bristled brush). Allow to dry overnight before applying final membrane.

When the final membrane is applied, the overall thickness over joints and cracks, at coves and around penetrations should be approximately 2.5 mm on the standard system.

Static Joints and Cracks

Joints and cracks less than 1.6 mm should be filled by pre-striping. Apply material so it both fills and



We create chemistry

MasterSeal® HLM 5000

overlaps the joint or crack to a width of 100 mm on each side.

Working or Expansion Joints

All joints over 3 mm must be sealed with a Master Builders Solutions urethane sealant. Any working joint less than 3 mm should be routed to a minimum of 6 mm and filled with a sealant. Prevent the waterproofing membrane from adhering to the joint sealant by applying a coat of wax or bond breaker tape over the cured sealant and then pre-stripping.

Uncoated Metal Surfaces

Remove dust, debris, and any other contaminants from vent, drain pipe and post penetrations, reglets and other metal surfaces. Clean surfaces to near white to SAE2.5

and prime immediately with MasterSeal P 691. Provide appropriate cant with MasterSeal sealant to eliminate 90° angles.

Application

A test application is always recommended before proceeding with entire application.

Standard System

Select the grade of MasterSeal HLM 5000 that best meets individual job requirements

For horizontal applications, empty contents of pail and spread immediately to ensure workability. Best results are obtained by marking off 11.6 m² areas and evenly spreading the contents of a 18.93 L unit with a rubber-edged notched squeegee.

For vertical applications, apply by trowel, roller or spray at the rate of 0.6 m²/L.

Verify the applied thickness with a wet film gauge as the work progresses.

Curing

Appreciable properties develop within 24–48 hours at 24°C and 50% relative humidity. Protect MasterSeal HLM 5000 from traffic during curing.

Drainage and Protection

For protection during backfill and where hydrostatic pressure is anticipated, use a suitable geotextile to divert the water.

For protection during backfill only, install protection board as soon as possible following cure of MasterSeal HLM 5000.

ESTIMATING DATA

Wet Film Thickness @ 1.65mm = 0.6m²/litre
Coverage per 18.93 litres is approximately 11.6m²

PACKAGING

MasterSeal HLM 5000 comes in a variety of grades for different applications, dependent on surface profile, texture and horizontal or vertical.

- **MasterSeal HLM 5000SL** (self-leveling) is formulated for application by squeegee or trowel to horizontal areas.
- **MasterSeal HLM 5000S** (spray or roller) is a versatile formulated version for spray application and or rolled onto horizontal or vertical surfaces.

All grades are available in 18.93 litre pails.

SHELF LIFE

MasterSeal HLM 5000 has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website

® = registered trademark of BASF group in many countries

MasterSeal HLM 5000 asean-v1-0214

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals offices

Singapore Tel: +65-6861-6766 Fax: +65-6861-3186	Malaysia Tel: +60-3-5628-3888 Fax: +60-3-5628-3776	Indonesia Tel: +62-21-2988-6000 Fax: +62-21-2988-5935	Thailand T: +66-2769-8564 F: +66-2769-8584	Vietnam T: +84-650-3743-100 F: +84-650-3743-200	Philippines T: +63-2-811-8000 F: +63-2-838-1025	Hong Kong Tel: +852-2408-4400 Fax: +852-2408-4401
--	---	--	---	--	--	--

Website : www.master-builders-solutions.asia-pacific.basf.com