



We create chemistry

Ucrete MT

4 - 6 mm Heavy Duty Polyurethane Floor Finish

DESCRIPTION OF PRODUCT

Ucrete MT provides a lightly textured protective floor finish suitable for applications in wet and dry process environments. It is dense and impervious, providing the ideal floor finish for applications in the food and beverage, pharmaceutical and chemical industries and wherever a robust, long lived floor is required.

Ucrete Industrial Flooring has been widely used throughout industry for more than 40 years, many of the older floors are still in service. A detailed project reference list is available upon request

PERFORMANCE DATA

RAPID INSTALLATION

Specifications are available that enable Ucrete MT and primer to be installed and cured within a 12 hour application window. Being non tainting also, this makes it ideally suited for rapid refurbishment in the food industry

TEMPERATURE RESISTANCE

The Ucrete MT resins do not start to soften until temperatures above 130°C are exceeded. 4mm Ucrete MT floors are fully serviceable to 70°C

AIR QUALITY

Ucrete has been awarded the Indoor Air Comfort Gold Label following extensive VOC emission chamber testing and auditing of quality management and production control procedures.

This demonstrates that Ucrete is an extremely clean product without any volatile compounds that might taint food-stuff or affect the well-being of personnel.

All Ucrete grades give very low emissions and conform to all the emissions requirements for indoor flooring systems in Europe including AgBB in Germany, Afsset in France, where they are rated A+ for VOC emissions (the cleanest rating), and M1 in Finland.

For further information please contact your local BASF representative

NON TAINTING

Ucrete MT is non tainting from the end of mixing, as tested by the Campden Technology Ltd.

CHEMICAL RESISTANCE

Ucrete UD200 offers exceptional resistance to a wide range of chemical aggressors. For example Ucrete is resistant to the following commonly encountered chemicals:

Acetic Acid, 50%: As spirit vinegar widely used in the food industry, indicative of resistance to vinegar, sauces, etc.

Concentrated Lactic Acid @ 60°C: Indicative of resistance to milk and dairy products.

Oleic Acid, 100% @ 60°C: Representative of the organic acids formed by oxidation of vegetable and animal fats widely encountered in the food industry.

Concentrated Citric Acid: As found in citrus fruits and representative of the wider range of fruit acids which can rapidly degrade other resin floors.

Methanol, 100%: Representative of alcohols and the wider range of solvents used in the pharmaceutical industry.

Ucrete UD200 is also resistant to a wide range of mineral oils, salts and inorganic acids, extensive chemical resistance tables are available upon request.

Note: some staining or discolouration may occur with some chemicals, depending upon the nature of the spillage and the standards of house keeping employed.

CLEANING & HYGIENE

Ucrete flooring systems are accredited for use in facilities operating HACCP based food safety systems.

Regular cleaning and maintenance will enhance the life and appearance of any floor. Ucrete MT is readily cleaned with industry standard cleaning chemicals and equipment

Detailed cleaning guidelines are available from your local BASF Construction Chemicals office.

IMPACT RESISTANCE

With high mechanical strengths and a low elastic modulus, Ucrete MT is very resilient and able to withstand severe impact loads. While no material is indestructible and surface chipping may occur, brittle modes of failure resulting in cracking and disbondment are unknown with Ucrete floors.



We create chemistry

Ucrete MT

4 - 6 mm Heavy Duty Polyurethane Floor Finish

Typical Properties	
Density	2000 kg/m ³
Compressive strength (EN13892-2)	48 - 53 MPa
Tensile strength (BS6319 Part 7)	6 MPa
Flexural strength (EN13892-2)	14 MPa
Adhesive strength to concrete (EN13892-8)	concrete failure
Fire Testing (EN13501: Part 1)	B _{FL} – S ₁

Note:- Samples cured for 28 days at 20 °C

SUBSTRATE MOISTURE TOLERANCE

Ucrete Industrial Flooring is extremely tolerant to residual substrate moisture and can be installed directly onto 7 day old concrete, or onto old good quality concretes with high moisture contents without the use of special primers, provided there is a functioning DPM within the structure.

This enables rapid construction programmes to be maintained and facilitates refurbishment work in wet process areas.

Epoxy surface DPMs should not be used as they soften under high temperature conditions and will lead to floor failure.

PERMEABILITY

Ucrete MT exhibits zero absorption when tested to CP.BM2/67/2.

SLIP RESISTANCE

The Ucrete MT surface profile has a coefficient of friction as determined to EN 13036 Part 4 with 4S rubber on the wet floor as follows:

Ucrete MT 40 - 45

Optimum slip resistance can only be maintained with regular cleaning.

COLOURS

Ucrete MT is available in eight standard colours:

Red	Yellow	Green	Orange
Grey	Cream	Blue	Green/Brown

Ucrete floor systems have been formulated to provide the very highest chemical and heat resistance. As a direct result some yellowing of the installed floor will occur in areas of direct UV exposure. This is most apparent in lighter colours.

SPECIFICATION

The floor finish shall be Ucrete UD200 from BASF plc, Construction Chemicals of 19 Broad Ground Road, Redditch, Worcestershire, B98 8YP installed at 4/6* mm in accordance with the manufacturers' instructions *(select as required)

*A 4mm Ucrete MT floor is fully resistant to high temperature spillage and discharge up to 70°C and can be lightly steam cleaned. Suitable for freezer temperatures down to -15°C.

*A 6mm Ucrete UD200 floor is fully resistant to liquid spillage and discharge up to 80°C and can be lightly steam cleaned. Suitable for freezer temperatures down to -25°C.

In extreme thermal shock environments a well designed substrate of good quality concrete is essential.



We create chemistry

Ucrete MT

4 - 6 mm Heavy Duty Polyurethane Floor Finish

SUBSTRATE QUALITY

Concrete substrates should be visibly dry and have a minimum tensile strength of 1.5 MPa.

Refer to the guide 'The Design & Preparation of Substrates for Ucrete Industrial Flooring'

All joints in the substrate concrete subject to movement should be reflected through the Ucrete floor and sealed with a suitable sealant

COVERAGE

4mm: 10 – 11 kg/m²

6mm: 13 – 14 kg/m²

CURING

Normally Ucrete UD200 floors can be put into service within 24 hours even at 8°C. Specifications are available that can be put back into service after 5 hours at 10°C.

STORAGE

In covered warehouse conditions, above 5°C and below 30°C and out of direct sunlight. Materials must be raised off the floor and kept dry. Liquid components must be protected from frost.

DISPOSAL

Part 2 containers should be decontaminated with 5% sodium carbonate (washing soda) solution after use and disposed of as building waste in accordance with local regulations.

WARNINGS AND PRECAUTIONS

In its cured state Ucrete is physiologically non-hazardous.

For normal flooring applications Ucrete does not require the use of respiratory protective equipment during installation.

Operatives should consult the CoSHH risk assessment and their work instructions.

BASF Construction Chemicals 19 Broad Ground Road Lakeside, Redditch Great Britain B98 8YP	
04	
01040063	
EN 13813:2002	
Synthetic resin screed material	
Reaction to fire:	B _{FL} – S ₁
Release of corrosive substances:	NPD
Water permeability:	NPD
Mechanical resistance:	NPD
Wear resistance:	AR0,5
Bond strength:	B>2,0
Impact resistance:	IR>4
Sound insulation:	NPD
Sound absorption:	NPD
Thermal resistance:	NPD
Chemical resistance:	NPD
Electrical resistance:	NPD



© BASF Construction Chemicals August 2014

BASF Hong Kong Limited

Unit 2, 20/F EW International Tower, 120-124 Texaco Road, Tsuen Wan, N.T., Hong Kong

Tel: (+852) 2408 4400

Fax: (+852) 2408 4401

