

MasterAir[®] 721

Air-entraining admixture for concrete

DESCRIPTION

MasterAir 721 is an air-entraining admixture which creates ultra-stable air bubbles that are strong, small and closely spaced.

RECOMMENDED USES

Entraining controlled air content in a wide range of concrete types:

- Low slump concrete
- Flowable concrete
- High temperature concrete
- Concrete with extended working times
- Lightweight and pre-stressed concrete
- Imparting workability to lean harsh mixes
- Reducing bleeding caused by grading deficiencies in the concrete materials

FEATURES AND BENEFITS

The use of **MasterAir 721** to entrain optimum air content in concrete results in the following improvements in concrete quality:

- Improved ability to entrain and retain air in concrete
- Improved air-void system in harden concrete
- Reduced permeability - increased watertightness
- Improved plasticity and workability
- Reduced segregation and bleeding
- Increased freeze / thaw resistance
- Increased resistance to scaling
- Greatly improved stability of air entrainment

PERFORMANCE TEST DATA

| | |
|----------------------|----------------------------|
| Aspect | : Pink free flowing liquid |
| Relative Density | : 1.01 ± 0.01 at 25°C |
| pH | : ≥ 6 at 25°C |
| Chloride ion content | : < 0.2% |

TEST CERTIFICATION/APPROVALS

- ASTM C 260
- EN 934-2: T5

DOSAGE

Optimum dosage of **MasterAir 721** should be determined in trial mixes. As a guide, a dosage range of 40ml to 800ml per 100kg of cementitious material is recommended. As a starting point use

100ml / 100kg of cement and adjust in the light of results obtained.

APPLICATION

MasterAir 721 is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the damp concrete after 50 to 70% of the mixing water has been added. The addition of **MasterAir 721** to dry aggregate or cement is not recommended.

SUGGESTED SPECIFICATION

The air entrainer for concrete shall be **MasterAir 721**, pink free flowing liquid formulation free of lignosulphonate and naphthalene polymers. The product shall have specific gravity not less than 1.00 and shall comply with ASTM C260 as air entrainer.

PACKAGING

MasterAir 721 is supplied in 20 kg carboy and 210 kg drums or in bulk on request.

STORAGE /SHELF LIFE

MasterAir 721 must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely reconstitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature.

Shelf life is 12 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult your local BASF representative.

PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs (which can also be tainted with vapour until product fully cured or dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use. Do not reuse containers for storage of consumable item. For further information refer to the material



We create chemistry

MasterAir[®] 721

safety data sheet. MSDS available on demand or on BASF construction chemicals web site.

TDS Ref. no.: MasterAir721/01/0714

STATEMENT OF RESPONSIBILITY (Disclaimer)

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

® = registered trademark of BASF group in many countries

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF India Limited
Construction Chemicals Division
Plot.No.12,TTC Area
Thane BelapurRoad,Turbhe
Navi Mumbai - 400705,India
Tel: +91 22 67127600, Fax: +91 22 67917358
E-mail: construction-india@basf.com , www.master-builders-solutions.basf.in

