



We create chemistry

MasterMatrix® 102

Viscosity Modifying Admixture (VMA) for Smart Dynamic concrete

DESCRIPTION

MasterMatrix 102 is a ready-to-use, liquid, organic, viscosity-modifying admixture (VMA) specially developed for producing concrete with enhanced viscosity and controlled rheological properties. Concrete containing **MasterMatrix 102** admixture exhibits superior stability and controlled bleeding characteristics, thus increasing resistance to segregation and facilitating placement.

The new technology of smart dynamic concrete allows concretes to be compacted without vibration, even with strongly reinforced structures. A self-compacting mix should have a high workability and viscosity.

The fluidity of the mix is guaranteed provided there is no friction between the internal particles and the concrete can flow freely; segregation occurs when the components of the concrete separate out into mortar and large aggregates.

Reaching the right balance between fluidity and resistance to segregation – apparently opposing properties – is essential for this type of mix. This balance is lacking when the fluidity of the concrete is obtained by adding water. Although a superplasticiser admixture gives high fluidity, alone it does not guarantee the necessary properties to ensure a good degree of self-compacting. That is why **MasterMatrix 102** is a fundamental admixture when making Self Compacting Concrete.

RECOMMENDED USES

- Smart Dynamic Concrete
- Concrete containing gap-graded aggregates
- Lean concrete mixtures
- Concrete containing manufactured sand

FEATURES AND BENEFITS

- Increased viscosity & thixotropic properties
- Improved stability during transport & placing
- Controlled bleeding
- Reduced segregation, even with highly fluid mix
- Enhanced pumping and finishing
- Reduced sagging – dimensional stability
- Enables flexibility in mixture proportioning

Mechanism of action

MasterMatrix 102 consists of a mixture of water soluble copolymers which is adsorbed onto the surface of the cement granules, thereby changing the viscosity of the water and influencing the rheological properties of the mix.

MasterMatrix 102 is chloride-free and compatible with all cements. It is incompatible for use with naphthalene sulphonate based superplasticiser admixtures.

It is possible with **MasterMatrix 102** to:

- Refine the rheology of the mixes by increasing cohesiveness and eliminating bleeding;
- Produce concretes distinguished by their great stability and strong capacity to retain water;
- Make the mixture less sensitive to variations in sand grading, to the shape and moisture content of the aggregates and to the characteristics of the binders;
- Obtain greater flexibility of choice and type of casts because of a low risk of segregation, greater pumping speeds and distances.

Smart Dynamic Concrete

Smart Dynamic concrete is an ultra-stable form of self-compacting concrete, a very flowable concrete mixture that is able to fill every part and corner of formwork, even with low fines, due to its high fluidity and stability. Smart Dynamic Concrete is produced using a combination of MasterGlenium 8600 series, high range, water reducing admixture and, typically an organic viscosity modifying admixture such as **MasterMatrix 102**.

Smart Dynamic Concrete is different from traditional self-compacting concrete because of its enhanced stability and other unique properties that include:

- Slump flow of 500 – 800 mm
- Controlled rheology
- Mixture proportioning flexibility
- Reduced sensitivity to normal variations in aggregate gradation
- Increased resistance to segregation
- Enhanced surface appearance
- Predictable engineering properties and improved structural integrity and durability

MasterMatrix[®] 102

PERFORMANCE TEST DATA

Aspect	Colourless free flowing liquid
Relative Density	1.01 ± 0.01 at 25°C
pH	≥6 at 25°C
Chloride ion content	< 0.2%

TEST CERTIFICATION/APPROVALS

- EFNARC - VMA Guidelines 2006

DOSAGE

MasterMatrix 102 is dosed at the rate of 30 to 500 ml/100 kg of cementitious material. Other dosages may be recommended in special cases according to specific job site conditions.

APPLICATION

MasterMatrix 102 is a ready-to-use liquid admixture, which should be added to the concrete after all the other components of the mix. This is particularly important in order to obtain maximum efficacy.

For best performance it is advisable to continue mixing until the mix is completely homogeneous.

To produce Self Compacting, **MasterMatrix 102** should be used in combination with the other superplasticizer admixtures of the MasterGlenium range in order to guarantee maximum efficacy.

A slight decrease in slump or slump flow may be noted after the addition of **MasterMatrix 102** admixture due to the increase in concrete viscosity. If necessary, the slight decrease in slump or slump flow can be offset easily by a minor increase in superplasticiser dosage. Also, because of its thixotropic properties, concrete containing **MasterMatrix 102** admixture may stiffen if left in a mixing vessel or truck without agitation. Workability can be restored by simply remixing the concrete mixture.

MasterMatrix 102 admixture has little to no effect on concrete setting time, sump retention, air content and compressive strength within the recommended dosage rate.

SUGGESTED SPECIFICATION

The viscosity modifying agent (VMA) shall be **MasterMatrix 102**, an organic, ready-to-use, liquid admixture specially formulated for applications in Smart Dynamic Concrete. The product shall comply with the EFNARC VMA guidelines 2006.

PACKAGING

MasterMatrix 102 is available in 20 & 235 kg drums

STORAGE /SHELF LIFE

MasterMatrix 102 must be stored where temperatures do not drop below +5°C. If product has frozen, thaw at +5°C or above and completely reconstitute using mild mechanical agitation. Do not use pressurized air for agitation. Store under cover, out of direct sunlight and protect from extremes of temperature.

Shelf life is 12 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult your local BASF representative.

PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs (which can also be tainted with vapour until product fully cured or dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use. Do not reuse containers for storage of consumable item. For further information refer to the material safety data sheet. MSDS available on demand or on BASF construction chemicals web site.

TDS Ref. No. : **MasterMatrix102/01/0317**



We create chemistry

MasterMatrix[®] 102

STATEMENT OF RESPONSIBILITY (Disclaimer)

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

® = registered trademark of BASF group in many countries

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF India Limited
Construction Chemicals Division
Plot.No.12,TTC Area
Thane Belapur Road,Turbhe
Navi Mumbai - 400705,India
Tel: +91 22 67127600, Fax: +91 22 67917358
E-mail: construction-india@basf.com , www.master-builders-solutions.basf.in

