



We create chemistry

MasterSeal® 878 (Also known as Elastocoat CC 5033)

Rapid curing, chemical resistant, elastomeric waterproofing membrane

DESCRIPTION

MasterSeal 878 is a solvent free, two component, high performance polyurea based waterproofing membrane, with high resistance to common chemicals. Using a specially designed spraying machine, the two components are pre-heated and spray applied, to a rapid curing, elastomeric, waterproofing membrane.

RECOMMENDED USES

MasterSeal 878 is recommended for waterproofing of large structures exposed to aggressive waters, containing potable water and other containment structures..

Typical application areas include:

- Water containment areas (potable and contaminated)
- Primary & Secondary containment tanks
- Waste water treatment tanks
- Protection & waterproofing of infrastructures.

FEATURES AND BENEFITS

- **Fast reacting** - Rapid installation. Does not run when applied on vertical surfaces
- **Seamless** - No risk of leaky seams and laps.
- **Spray applied** - Fast installation on large surfaces; easy application on complex details.
- **Fully bonded** - Eliminates water collection behind membrane even if punctured.
- **High tensile strength** - Excellent ability to accept movements without rupturing.
- **Elastomeric** - Excellent crack-bridging ability.
- **High tear resistance** - Minimized risk of damage to membrane in service.
- **Low T_g of -20°C** - Remains elastomeric at very low temperatures. Performance unaffected in below freezing conditions.
- **Solvent-free** - Improved safety
- **Potable water contact approved** – suitable for tanks containing drinking water.

PROPERTIES

Shore A hardness, ASTM D 2240	>85
Tensile strength, D412	>16 N/mm ²
Elongation, ASTM D 412	>500%
Tear strength, ASTM D624, KN/m	>70
Impact Resistance ASTM D91	passes
Weathering QUV 1000 hours no cracking or delamination	passes
Suitable for contact with potable water USFDA	Passes

Mixing ratio, A : B, by volume	1:1	
Density, at 25°C, kg/L	Part A Part B	1.03 1.10
Viscosity, at 25°C, cps	Part A Part B	1000±150 1250±200
Gel time tack free		~10-15 seconds ~60-120 seconds
Application temperature of Parts A & B		65-70°C
Application temperature (ambient and substrate), °C		10 to 40
Permissible max. relative humidity during application, %		85

The performance data is typical and based upon controlled laboratory conditions. Actual performance on the job site may vary from these values based on actual site conditions.

APPLICATION

For information about application, please obtain a copy of the BASF "Application Guide for **MasterSeal 878**" from your local representative.

Tips for optimal performance

- For optimum chemical and mechanical performance thickness's greater than 1.5mm should be used.



We create chemistry

MasterSeal[®] 878 (Also known as Elastocoat CC 5033)

- Keep **MasterSeal 878** cool in hot weather and warm in cold weather.
- Repair voids, cracks and unevenness in substrates before application.
- Remove all surface contaminants and ensure substrate is dry.
- Avoid application during rain.
- Agitate Part A before application.
- Apply by spraying uniformly to recommended thickness using recommended spray machine.

ESTIMATING DATA

MasterSeal 878 is applied approximately at 1.05 – 2.1 kg/m². This corresponds to a cured film thickness of approx. 1.0 – 2.0mm. Details, corners require a higher coverage rate up to 4.0kg/m² or more.

PACKAGING

MasterSeal 878 part A and B is supplied in 200kg drums.

SHELF LIFE

MasterSeal 878 has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

MasterSeal878/02/0616

STATEMENT OF RESPONSIBILITY (Disclaimer)

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

® = registered trademark of BASF group in many countries

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF India Limited
Construction Chemicals Division
Plot.No.12,TTC Area
Thane Belapur Road,Turbhe
Navi Mumbai - 400705,India
Tel: +91 22 67127600, Fax: +91 22 67917358
E-mail: construction-india@basf.com , www.master-builders-solutions.basf.in

