



We create chemistry

# MasterTile® 500

High Performance, Polymer Modified Cementitious White Colored Tile Adhesive with Extended Open Time & Reduced Slip.

## DESCRIPTION

**MasterTile 500** is a white colored, polymer enriched, cementitious tile adhesive with extended open time and reduced slip for thin bed fixing of fully vitrified ceramic tiles and porcelain mosaic tiles in interior or exterior situations, especially those exposed to permanently wet conditions. It provides strong adhesion to cement/sand screeds, to in-situ/pre-cast and aerated concrete, and brickwork. It is also suitable for fixing Glazed tiles, Vitrified tiles & Terrazzo

## RECOMMENDED USES

- Suitable for Ceramic tiles conforming to IS13712(2006) type Ia, Ib, IIa, IIb tiles
- Wet areas including kitchen, bathrooms & Showers in domestic, institutional, commercial and industrial location
- Tile on tile application
- For internal & external applications
- For Floors, Walls, Podium decks, roofs including large format tiles.
- For Laying Ceramic, Porcelain Mosaic, Fully vitrified tiles and brick tiles.
- For laying non-moisture sensitive natural stone
- For Swimming pools, pool surrounds, wet rooms and cold storage depots
- For substrates such as cement screeds, precast concrete elements, aerated concrete, heated screeds, plaster and existing floors and walls
- For fixing tiles on bonded waterproofing membranes such as MasterSeal 561

## FEATURES AND BENEFITS

**High Performance(C2)** – Can be used for Non-porous ceramic tiles with minimal water absorption

**Non-slip & Excellent grab(T)** – Versatile can be used for horizontal and vertical applications

**Extended Open Time(E)** – Allows longer working time and Faster progress

**Waterproof** – immersion will not affect adhesion

**Thin or Thick bed** - multi-purpose

**High adhesive bond strength** –suitable for large tiles

## PROPERTIES

Aspect	Free Flowing White powder
Water/powder ratio, by wt <sup>1</sup>	0.240 - 0.250
Open time <sup>2</sup> <b>(EN 1346)</b>	>0.5N/mm <sup>2</sup> (30 min)
Working Time <sup>2</sup>	Min. 60 min
Temperature Resistance	Upto 80°C
Maximum Bed thickness	≥ 10mm
Tensile Adhesion Strength	
at Room temperature <b>(EN 1348)</b>	≥1.0 N/mm <sup>2</sup>
After water Immersion <b>(EN1348)</b>	≥1.0 N/mm <sup>2</sup>
After Heat Ageing <b>(EN 1348)</b>	≥1.0 N/mm <sup>2</sup>
Slip <b>(EN 1308)</b>	≤ 0.5 mm
Curing Times <sup>2</sup>	
Walked on after	Approx. 24 hrs
Groutable after	Approx. 24 hrs
Able to bear weight after	Approx. 7 days
1. The water powder ratio can be reduced (to approx. 0.23 to increase the non-sag properties of large-format slabs on the wall.	
2. At +23°C and 50% relative humidity. Higher temperatures reduce; lower temperatures increase the times given. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate and of the materials laid.	

## STANDARDS

**MasterTile 500** meets the requirements of **Class C2TE** as specified in **EN 12004-2007 “Adhesives for Tiles – Requirements, Evaluation of Conformity, Classification & Design”**

## APPLICATION

### Surface preparation

The substrate must be solid, clean and load-bearing. Oil stains, bond-inhibiting surfaces and contaminations must be thoroughly removed. Irregularities on walls are to be leveled with **MasterEmaco N303** or polymer modified mortar using **MasterEmaco 131**.

Highly absorbent cement based substrate and aerated concrete are to be primed with **MasterSeal 511** or **MasterSeal 399**. Allow primer to dry.

# MasterTile<sup>®</sup> 500

Freshly installed cement screeds must not have residual moisture content above 5 %.

Concrete, screeds, renders, and block work should be cured sufficiently to allow for most of the shrinkage movements.

Tiles must be dry, and their surfaces free of contaminants that could impair adhesion. Do not soak tiles in water before laying.

## Mixing

Place gauging water in a clean mixing vessel. Add powder and mix with a suitable mechanical stirrer until a plastic, lumps free consistency is achieved. Required water for 25 Kg bag is 6.0 – 6.25 liter depending on consistency.

## Placing

Apply thin (3 to 6 mm thick) bond coat to the substrate with the straight edge of the trowel, then comb the mortar with the notched edge of the trowel. Only apply as much mortar as can be covered with tiles within the open time. Check the open time by touching the adhesive bed with your fingertip. Apply mixed material in perpendicular direction with respect to grooves on the back of tile.

**MasterTile 500** is strongly recommended to additionally be buttered on the backs of the tiles to ensure full adhesive contact for large tiles (Area > 900 cm<sup>2</sup>).

Position tiles in the adhesive bed and align with a slightly pushing motion, ensuring the tile back achieves full contact with the adhesive.

Adjustments to tiles should be made during the adhesive open time. Remove excess adhesive from face of the tile with a damp sponge or cloth before it sets and rake out joint for subsequent grouting before the adhesive sets.

Ceramic tiles should never be butt jointed. Leave a minimum of 2mm around tiles.

Leave for a minimum of 24 hrs before grouting

## Watch points

- Movement joints should be provided in accordance with normal practice. Refer to published local standards or BS 5385.

- Do not apply at temperatures below +5°C and above 40°C
- In hot weather conditions, pre-condition **MasterTile 500** at 21°C for at least 24 hours and use chilled water for mixing to achieve required open times.
- Substrate must achieve 2% moisture content for safe laying of tiles.
- Stiffened mortar must neither be diluted with water nor with fresh mortar
- Do not apply **MasterTile 500** greater than 10 mm thickness on horizontal surfaces and vertical surfaces.

## ESTIMATING DATA

As a guide the following consumption table can be used.

Required Notch Size*	Tiling Area
6mm	Approximately 2.2 kg / m <sup>2</sup>
8mm	Approximately 2.8 kg / m <sup>2</sup>
10mm	Approximately 3.5 kg / m <sup>2</sup>

\* The consumption rates of dry powder are based on lab trials and might vary subject to variation of subfloor level and surface regularity. The reverse profile of the used ceramic and the surface structure of the substrate to be covered are also important factors, besides the tile size, for the consumption of mortar.

## PACKAGING

**MasterTile 500** is available in 25kg bags

## SHELF LIFE

Store under cover, out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment.

Shelf life is 9 months when stored as above.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

TDS Ref : MasterTile500/04/0817



We create chemistry

# MasterTile<sup>®</sup> 500

---

---

**STATEMENT OF  
RESPONSIBILITY  
(Disclaimer)**

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

® = registered trademark of BASF group in many countries

---

**NOTE**

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

---

**BASF India Limited**  
Construction Chemicals Division  
Plot.No.12,TTC Area  
Thane BelapurRoad,Turbhe  
Navi Mumbai - 400705,India  
Tel: +91 22 67127600, Fax: +91 22 67917358  
E-mail: construction-india@basf.com , www.master-builders-solutions.basf.in

