

MasterGlenium[®] 110M

A high-performance concrete superplasticiser based on modified polycarboxylic ether

DESCRIPTION

MasterGlenium 110M has been primarily developed for applications in the ready mixed and precast concrete industries where the highest durability and performance is required.

MasterGlenium 110M is free from chlorides and complies with ASTM C494 Types B, D and G.

MasterGlenium 110M is compatible with all Portland cements that meet recognised international standards.

- better resistance to carbonation
- lower permeability
- better resistance to aggressive atmospheric conditions
- reduced shrinkage and creep
- increased durability

TYPICAL APPLICATIONS

The excellent dispersion properties of **MasterGlenium 110M** make it the ideal admixture for precast and readymixed concrete where low water cement ratios are required. This property allows the production of very high early and high ultimate strength concrete with minimal voids and therefore optimum density. Due to the strength development characteristics the elimination or reduction of steam curing in precast works may be considered as an economical option.

- high workability without segregation or bleeding
- less vibration required
- can be placed and compacted in congested reinforcement
- reduced labour requirement
- improved surface finish

MasterGlenium 110M may be used in combination with **MasterMatrix** for producing Smart Dynamic Concrete (SDC). The technology produces advanced self compacting concrete, without the aid of vibration. For economic, ecological and ergonomic ready-mix / precast concrete production.

ADVANTAGES

- increased early and ultimate compressive strengths
- increased flexural strength
- higher E modulus
- improved adhesion to reinforcing and stressing steel

PACKAGING

MasterGlenium 110M is available in 210 litre drums and in bulk tanks upon request.

STANDARDS

EN 934-2 Tables 3.1, 3.2, 11.1 and 11.2

APPLICATION GUIDELINES

MasterGlenium 110M is a ready to use admixture that is added to the concrete at the time of batching.

The maximum effect is achieved when the **MasterGlenium 110M** is added after the addition of 50 to 70% of the water. **MasterGlenium 110M** must not be added to the dry materials.

Thorough mixing is essential and a minimum mixing cycle, after the addition of the **MasterGlenium 110M**, of 60 seconds for forced action mixers is recommended.

The normal dosage for **MasterGlenium 110M** is between 0.5 and 1.5 L/100kg of cement (cementitious material).

Dosages outside this range are permissible subject to trial mixes.

MIXING

Conventional superplasticisers, such as those based on sulphonated melamine and naphthalene formaldehyde condensates, at the time of mixing, become absorbed onto the surface of the cement particles. This absorption takes place at a very early stage in the hydration process. The sulphonic groups of the polymer chains increase the negative charge on the surface of the cement particle and dispersion of the cement occurs by electrostatic repulsion.

MasterGlenium® 110M

MasterGlenium 110M is differentiated from conventional superplasticisers in that it is based on a unique carboxylic ether polymer with long lateral chains. This greatly improves cement dispersion. At the start of the mixing process the same electrostatic dispersion occurs as described previously but the presence of the lateral chains, linked to the polymer backbone, generate a steric hindrance which stabilises the cement particles capacity to separate and disperse.

This mechanism provides flowable concrete with greatly reduced water demand.

MasterGlenium 110M must not be used in conjunction with any other admixture unless prior approval is received from BASF Technical Services.

MasterGlenium 110M is suitable for mixes containing:

- Microsilica (Silica Fume)
- Pulverised fuel ash
- GGBS (ground granulated blast furnace slag)

STORAGE AND SHELF LIFE

MasterGlenium 110M should be stored in original containers and at above 5°C. If frozen gradually thaw and agitate until completely reconstituted. The shelf life is 12 months when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF Technical Services Department.

HEALTH AND SAFETY

MasterGlenium 110M contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/GI_110M_11_00/v1/12_13/v2/08_19

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals UAE LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800, Fax: +971 4 8851002
www.master-builders-solutions.basf.ae

Disclaimer: the LRQA mark relates to certified management system and not to the product mentioned on this datasheet



**MASTER®
BUILDERS
SOLUTIONS**