

MasterRoc[®] AGA 370


Liquid high performance accelerator as part of two component annular grout system for TBM tunnels

DESCRIPTION

MasterRoc AGA 370 is a high performance grout accelerator, mainly for use in the annular grouting behind the concrete lining of a Tunnel Boring Machine (TBM). It is a liquid additive whose dosage can be varied to the desired setting and hardening times.

TYPICAL APPLICATIONS

MasterRoc AGA 370 is suitable for all applications where a rapid gel and early strength values are decisive.



ADVANTAGES

- Faster setting and higher early strengths than without set accelerators
- Secures rapid work progress
- Low viscosity
- Easy to mix into the grout
- Low consumption
- Achieves higher final strengths as compared with traditional accelerators

PACKAGING

MasterRoc AGA 370 is supplied in bulk, 1000 litre IBC or 210 litre drums.

TECHNICAL DATA*

Form:	liquid
Colour:	transparent
Density at 25°C:	1.35 – 1.39
pH value:	13.0
Viscosity at +20°C:	30 - 70 MPas
Solubility in water:	total
Thermal stability:	+5°C
Chloride content:	<0.1%
Physiological effect:	irritant to skin and eyes

APPLICATION PROCEDURE

MasterRoc AGA 370 is part of the two component grouting system. The addition of the accelerator will be at a nozzle with non return valve just before injection into the annular gap. Mix designs for Part A and the equipment set up will be specific to the TBM and available raw materials. Consult your local BASF Underground representative for site specific recommendations.

CONSUMPTION

The required setting time and hence the dosage are determined by the type of ground conditions and any water flows. Dosage will be adjusted according to temperature of the material and the reaction time of the cement. According to the required setting time, the consumption of **MasterRoc AGA 370** ranges between 8-12 % by volume of grout.

MasterRoc[®] AGA 370

STORAGE

Minimum storage temperature for **MasterRoc AGA 370** is +5°C. If **MasterRoc AGA 370** has frozen, thaw at +20°C or above and completely reconstitute with a mild mechanical agitation. It is recommended that your local BASF representative be consulted prior to the use of any products that were frozen. Maximum storage temperature is +60°C. Performance tests should always be carried out before use.

If stored in tightly closed original containers and under the above conditions, **MasterRoc AGA 370** has a storage life of at least 12 months.

SAFETY PRECAUTIONS

MasterRoc AGA 370 is an irritant fluid; therefore, any contact with skin and eyes must be avoided. It is essential that Safety glasses and rubber gloves always be worn during handling. The use of a protective barrier cream is recommended. In case of contact with eyes or skin, flush immediately with plenty of water and seek medical advice. For further information refer to the material Safety data sheet.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/Roc_AGA370_07_14/v2/11_15

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.