

# MasterRoc<sup>®</sup> MP 355 1K DW

One component injection foam to stop small to mid-volume water ingress, with a potable water certificate

## DESCRIPTION

**MasterRoc MP 355 1K DW** is a solvent free, single component polyurethane foam which reacts only in contact with humidity or water, and is certified for contact with potable water (DW: Drinking Water).

## FIELDS OF APPLICATION

- Stopping of small to mid-volume water ingress in underground structures
- Also suitable for filling of water bearing voids

## FEATURES AND BENEFITS

- Reacts in moist surroundings
- Good bonding to wet surfaces
- Forms a flexible foam

## PACKAGING

**MasterRoc MP 355 1K DW:** 25 kg cans  
Accelerator for **MasterRoc MP 355 1K DW:** 2.5 kg cans

## TECHNICAL DATA\*

### MasterRoc MP 355 1K DW

Density, 20°C	1.16 g/cm <sup>3</sup>
Viscosity, 23°C	700 mPa.s
Color	Yellowish
Application temperature	+ 5°C to 40°C
Maximum foam expansion rate at 10% accelerator dosage	20-30

### Accelerator for MasterRoc MP 355 1K DW

Density, 20°C	1.10 g/cm <sup>3</sup>
Viscosity, 23°C	70 mPa.s
Color	Clear to yellowish

## APPLICATION PROCEDURE

1. Add the accelerator to **MasterRoc MP 355 1K DW** (up to 10%, depending on the required reaction time), mix quickly and thoroughly.
2. Inject this mixture through a single component injection pump. The moisture / water in the ground will generate a foaming reaction. In the case of dry ground, flush the borehole with water before injecting.

## REACTION TIME

The reaction time depends on the ground and product temperature, as well as the accelerator dosage (see Table 1). Site trials should be performed in advance to establish the required reaction time.

Table 1:

Reaction Times with 10% water and 10% accelerator				
Initial Temperature (°C)	5	10	15	20
Start of reaction (sec)	130	65	30	15
End of reaction (sec)	350	250	120	60
Foam expansion rate (approximately)	20	25	25	30

# MasterRoc<sup>®</sup> MP 355 1K DW

## CLEANING OF INJECTION EQUIPMENT

During short breaks in the injection procedure, the pump and hoses should be filled with non-accelerated resin to avoid blockages. After finishing the injection, pump an appropriate agent or oil which does not contain water through the pump and injection lines.

## STORAGE

**MasterRoc MP 355 1K DW** is not hazardous. However, follow standard safety procedures when handling the product and wear gloves and safety glasses.

Avoid eye and skin contact. If skin contact occurs, wash with plenty of water and soap. In case of eye contact rinse with plenty of water and seek medical advice. For further information refer to Material Safety Data Sheet.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand, and disposed of in accordance with local regulations.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF\_CC-UAE/Roc\_MP3551KDW/v2/07\_14

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.