

# MasterSeal<sup>®</sup> 704AR

## Synthetic membrane of plasticised PVC

### DESCRIPTION

**MasterSeal 704AR** is a synthetic membrane made by the casting process. Made of plastisol layers with different chemical and physical properties and has a layer of 50 g/m<sup>2</sup> glass fiber inserted for dimensional stability. It also has a 200 g/ m<sup>2</sup> non-woven polyester felt, to aid bonding to the substrate with an adhesive. A bitumen resistant grade, with a 300 g/ m<sup>2</sup> non-woven polyester felt, is also available.

### TYPICAL APPLICATIONS

**MasterSeal 704AR** can be applied in the following circumstances:

- Exposed and architectural Roof Structures
- Landscaped areas and Roof Gardens
- Refurbishment of Roofs with existing bitumen waterproofing, using a variant of this membrane.

### ADVANTAGES

- It has superior mechanical characteristics and high resistance to weathering and ultra violet rays
- High mechanical properties and resistance to puncturing
- Dimensionally stable
- Resistant to hot-cold temperature cycles
- Custom colours possible to aid architectural design
- Bitumen resistant variant available
- Long life expectancy

### PACKAGING AND ROLL SIZES

**MasterSeal 704AR** is supplied in various thicknesses with 1.60 metre width and in lengths of 20 metres.

Thickness (mm)	1.2	1.5	1.8	2.0	2.4
Width (m)	1.6	1.6	1.6	1.6	1.6
Length (m)	20	20	20	20	20
Colour	Light Grey				

### APPLICATION PROCEDURE

Usually applied by Specialist Applicator. Please contact BASF Construction Chemicals for specific application assistance.

### WATERTIGHT SYSTEMS & ENGINEERED SOLUTIONS

BASF Construction Chemicals provide systems and engineered solutions, to suit the structure, at the design and construction stages, to ensure water tightness. Various products and elements which form an integral part of a system are manufactured and approved by BASF. The following ranges of products are available;

- **MasterSeal** range - Active and passive joint treatment and preformed membranes
- **MasterSeal** range - Liquid applied membranes and protective coatings
- **MasterFlow** range - High performance grouts
- **MasterEmaco** and **MasterBrace** ranges - Repair materials

### STORAGE

Store out of direct sunlight, clear of the ground and on pallets.

# MasterSeal<sup>®</sup> 704AR

## PHYSICAL/CHEMICAL PROPERTIES\*

Thickness UNI EN 1849 - 2	1.2 mm	1.5 mm	1.8 mm	2.0 mm	2.4 mm
Specific weight UNI EN 1849 – 2	1.70 kg/m <sup>2</sup>	2.00 kg/m <sup>2</sup>	2.35 kg/m <sup>2</sup>	2.60 kg/m <sup>2</sup>	3.10 kg/m <sup>2</sup>
Tensile strength UNI EN 12311 – 2	≥ 650 N/5 cm	≥ 700 N/5 cm	≥ 800 N/5 cm	≥ 900 N/5 cm	≥ 1100 N/5 cm
Elongation at break UNI EN 12311-2	≥ 80 %	≥ 80 %	≥ 80 %	≥ 80 %	≥ 80 %
Tear resistance UNI EN 12310 - 2	≥ 150 N	≥ 170 N	≥ 180 N	≥ 200 N	≥ 220 N
Resistance to impact UNI EN 12691	≥ 450 mm	≥ 800 mm	≥ 900 mm	≥ 1250 mm	≥ 1500 mm
Cold bending UNI EN 495 - 5	≤ -25°C	≤ -25°C	≤ -25°C	≤ -25°C	≤ -25°C
Hydrostatic pressure resistance (6 hours at 5 bar) UNI EN 1928 meth. B	waterproof	waterproof	waterproof	waterproof	waterproof
Dimensional stability (%) after 6 hours at 80°C – UNI EN 1107 - 2	≤ 0.1 %	≤ 0.1 %	≤ 0.1 %	≤ 0.1 %	≤ 0.1 %
Resistance to artificial weathering UNI EN 1297	no cracking	no cracking	no cracking	no cracking	no cracking
Root resistance UNI EN 13948	No penetration	No penetration	No penetration	No penetration	No penetration
Resistance to static punching UNI EN 12730	≥ 20 kg	≥ 20 kg	≥ 20 kg	≥ 20 kg	≥ 20 kg

### NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

### QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

**BASF\_CC-UAE/SI\_704AR\_10\_07/v2/12\_14**

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.