

MasterSeal[®] 707HE

Synthetic membrane of plasticised PVC

DESCRIPTION

MasterSeal 707HE Synthetic membrane of plasticised PVC (two colour version light grey/dark grey) manufactured by co-extrusion. This enables the production, of a single layer of membrane where the two surfaces have different chemical-physical properties. The upper surface (grey and exposed) is characterized by an extremely high resistance to weathering & UV rays, while the lower surface is characterised by an extremely high resistance to puncturing and root penetration.

TYPICAL APPLICATIONS

MasterSeal 707HE can be applied in the following circumstances:

- Water retaining structures
- Water features
- Reservoirs
- Artificial lakes
- Canals

ADVANTAGES

- It has superior mechanical characteristics an extremely high resistance to weathering and ultra violet rays
- High mechanical properties and resistance to puncturing
- Rot-proof
- Dimensionally stable
- Resistant to hot-cold temperature cycles
- Adequate resistance to chemicals when immersed in water
- Resistant to root penetration
- Long life expectancy

PACKAGING AND ROLL SIZES

MasterSeal 707HE is supplied in various thickness with 2.10 meter width and in lengths of 20 meters. Colours available are Light and dark grey.

| | | | |
|----------------|------------------------|------|------|
| Thickness (mm) | 1.5 | 2.0 | 2.2 |
| Width (m) | 2.10 | 2.10 | 2.10 |
| Length (m) | 20 | 20 | 20 |
| Colour | Light grey / dark grey | | |

APPLICATION PROCEDURE

Usually applied by Specialist Applicator. Please contact BASF Construction Chemicals for specific application assistance.

WATERTIGHT SYSTEMS AND ENGINEERED SOLUTIONS

Watertight Systems & Engineered Solutions
BASF Construction Chemicals provide systems and engineered solutions, to suit the structure, at the design and construction stages, to ensure water tightness. Various products and elements which form an integral part of a system are manufactured and approved by BASF. The following ranges of products are available;

- **MasterSeal** range - Preformed membranes
- **MasterSeal** range - Active and passive joint treatment
- **MasterSeal** range - Liquid applied membranes and protective coatings
- **MasterFlow** range - High performance grouts
- **MasterEmaco** and **MasterBrace** ranges - Repair materials

STORAGE

Store out of direct sunlight, clear of the ground and on pallets.

MasterSeal® 707HE

PHYSICAL / CHEMICAL PROPERTIES*

| | | | |
|--|------------------------|------------------------|------------------------|
| Thickness UNI EN 1849 - 2 | 1.5 mm | 2.0 mm | 2.2 mm |
| Specific weight UNI EN 1849 - 2 | 1.95 Kg/m ² | 2.60 Kg/m ² | 2.96 Kg/m ² |
| Tensile strength UNI EN ISO 527 - 3 | ≥ 17.5 N/5cm | ≥ 17.5 N/5cm | ≥ 17.5 N/5cm |
| Elongation to break UNI EN ISO 527 - 3 | ≥ 300 % | ≥ 300 % | ≥ 300 % |
| Puncture resistance DIN 16726 - 5.12 | ≥ 800 mm | ≥ 1100 mm | ≥ 1400 mm |
| Cold bending UNI EN 495 - 5 | ≤ -30°C | ≤ -30°C | ≤ -30°C |
| Hydrostatic pressure resistance (6 hours at 5 bar) UNI EN 1928 meth. B | Waterproof | waterproof | Waterproof |
| Root resistance DIN 4062 | No penetration | No penetration | No penetration |
| Resistance to tearing UNI EN 12310 - 2 | ≥ 80 N/mm | ≥ 80 N/mm | ≥ 80 N/mm |
| Tear Resistance ISO 34 specimen fig. 2 | ≥ 45 N/mm | ≥ 45 N/mm | ≥ 45 N/mm |
| Resistance to static punching (CBR) UNI EN ISO 12236 | ≥ 1800 N | ≥ 2450 N | ≥ 2800 N |
| Resistance to oxidation tensile strength variation UNI EN 14575 | < 25 % | < 25 % | < 25 % |
| Resistance to weathering (12000 h) Tensile strength variation UNI EN 12224 | < 25 % | < 25 % | < 25 % |
| Resistance to leaching UNI EN 14415 meth A & B Tensile strength variation Loss in mass | < 25 % < 5 % | < 25 % < 5 % | < 25 % < 5 % |

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF Construction Chemicals representative.

BASF reserves the right to have the true cause of any liability determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational Health & Safety standards ISO 9001, ISO 14001 and ISO 45001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/SI_707HE_10_07/v2/12_14

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.