

# MasterTop<sup>®</sup> 2200

High strength epoxy repair filler for horizontal cracks and minor repairs in concrete substrates

## DESCRIPTION

**MasterTop 2200** is an epoxy filler compound. It is a two component, fine aggregate filled, fast curing material, ideal for minor horizontal concrete repair applications.

**MasterTop 2200** is an easily workable filler compound that can be applied by either trowel, spatula or knife. It cures to give high mechanical properties typical of epoxy compounds. It is resistant to oils, greases, petroleum, salts, many acids and alkalis and most commonly met corrosive media. It does not shrink on curing, and is designed to be used when cured from below freezing point to 60°C. Its impact resistance, and mechanical strength is greater than that of concrete.

## PRIMARY USES

For surface repairs of fine cracks and spalls to horizontal concrete floor deck substrates in car parks and other flooring applications.

## TYPICAL APPLICATION

- Repairing surface defects such as blowholes and pin holes in concrete floors.
- Dowel bars anchoring.

## ADVANTAGES

- High strength.
- Strong adhesion.
- Impact resistant
- Chemical resistant.
- Non shrink.
- Epoxy based.
- Trowels to a smooth finish.
- Easy to use.
- Supplied in pre-weighed units.
- No bonding agent or primer required.

## PACKAGING

**MasterTop 2200** is available in 7.5 kg units.

## COMPOSITION

Two-component epoxy-based mortar filled with selected fine aggregate.

## TYPICAL PROPERTIES\*

Colour	Cement grey
Mixed density at 25°C	1.7g/cm <sup>3</sup> (approx.)
Flashpoint	N/A
Compressive strength to ASTM C579	>80N/mm <sup>2</sup> at 7 days
Pull off bond strength ASTM D4541/BS 1881 Part 207	>3N/mm <sup>2</sup>
Pot life at 25°C	70 minutes
at 40°C	30-40 minutes
Tack free time at 25°C	7 hours
at 40°C	2 hours 15 minutes
Cure (by compressive strength) at 25°C:	≥ 60N/mm <sup>2</sup> at 7 days
Flexural strength ASTM C580	>30N/mm <sup>2</sup>

## CHEMICAL RESISTANCE

**MasterTop 2200** has excellent resistance to the following: Most aqueous systems, sewage, urine, fresh water, sea water, diluted and concentrated alkalis, diluted acids, sulphur gases, mineral, vegetable and animal oils and fats, ammonia and formaldehyde.

## APPLICATION PROCEDURE

### DESCRIPTION

All loose particles, laitance, dust and grease etc., must be removed prior to application of

**MasterTop 2200**.

### MIXING: RATIO 2 : 1

The 7.5kg pack has been designed to be readily mixed by trowel at the ratio of 2 parts base to 1 part hardener. Where more than one pack is to be mixed at a time, a slow speed mixing drill and sealant paddle is suitable. Mix until a smooth streak-free consistency is achieved.

# MasterTop<sup>®</sup> 2200

## APPLICATION

Knife or trowel **MasterTop 2200** to the required level using the minimum of solvent on the trowel to aid workability. The surface may be finished smooth by use of a paint brush dipped in a suitable Xylene thinners. Where a very deep recess is to be filled, it may be necessary to build up in layers. Repairs may be camouflaged if required by covering surface with cement powder before full cure is affected.

## WORKING TEMPERATURE

**MasterTop 2200** will cure at temperatures as low as 0°C, although at low temperatures cure is retarded.

## COVERAGE

7.5kg is sufficient to cover 4.1 m<sup>2</sup> at 1mm thickness.

## EQUIPMENT CARE

Clean with a suitable Xylene thinners immediately after use.

## SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes mouth, skin and foodstuffs (which can also be tainted with vapour until product fully cured or dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use. For further information refer to the material safety data sheet.

## STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

**BASF\_CC-UAE/Top\_2200\_07\_09/v2/08\_15**

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.