

MasterInject[®] 1333

Low viscosity epoxy resin for injection grouting

DESCRIPTION

MasterInject 1333 is a two component solvent free epoxy resin based Injection grouting system with an extended pot-life, injecting cracks to restore structural integrity

RECOMMENDED USES

MasterInject 1333 is recommended for grouting of fine cracks, cold joints. Voids etc in concrete structural elements which are threatening the structural integrity or water tightness.

Applications include grouting of minute void for repair purposes.

- Cold joints between different concrete pours
- Stabilised cracks in structural elements
- Unfilled voids behind tiles, stone facades and joints
- Fine gaps around anchor bolts loosened due to improper grouting
- Gap behind steel late for epoxy plate bonding

FEATURES AND BENEFITS

- **High elastic modulus** – effective transfer of stresses at bond interface
- **High Heat Deflection Temperature** – resists creep at high service conditions
- **Low Viscosity** - Effective penetration into very fine gaps less than 0.1mm
- **High Bond strength** – renders grouted area monolithic
- **Good Bond to damp surfaces** – advantage in humid environments
- **Long potlife** – sufficient time to penetrate deeply
- **Pre proportioned** – avoidance of site errors
- **Fast Curing** – fast return to service of repaired area.

PROPERTIES

Tensile strength MPa	>12
Compressive strength (astm D695) MPa	>70
E modulus in compression (ASTM D695) MPa	>2300
Flexural strength (ASTM D 695) Mpa	>25
Bond strength	Greater than the tensile strength of concrete

	Part A	Part B
Supply form	Thin liquid	Thin liquid
Colour	Clear	Amber
Mix ratio (A:B by volume)	1.35:1	
Denisty Mixed	1.05-1.09 kg/L	
Viscosity at 25°C	350 cps	
Heat Deflection Temperature	60°C	
Minimum application Temperature	5°C	
Pot life (1L pack) @ 27°C	>2.5 hours	
Cure time (ASTM D 695)	7	

APPLICATION

Surface preparation

Remove all grease, oil, dust, residual curing compound, mould release agent or other contaminant that could impair adhesion of the injection ports. The injection ports should be applied over 6-10mm diameter holes drilled at least 50-75mm into the concrete element. For deeper penetration deeper holes should be considered. Use **MasterEmaco 2200** to adhere the injection ports over the holes ensuring that the adhesive does not block the drilled holes. Allow the **MasterEmaco 2200** to cure before injecting. The ports should follow the crack at intervals of 500mm or a maximum of 1m centres. Inject from the lowest point or furthest point towards the centre checking for resin coming out of the next hole along. For detailed instructions



We create chemistry

MasterInject[®] 1333

on crack injection ask you BASF representative for the "MasterInject guide to crack injection".

Mixing

Proportion part kits accurately mixing only what can be used in less than 30 minutes. Thoroughly stir Part A, add Part B and blend thoroughly using a slow speed mixer fitted with a suitable paddle.

ESTIMATING DATA

Usage will depend on the injection pressure and the size of the cracks and is impossible to estimate

PACKAGING

MasterInject 1333 comes in 8.83 litre pack Part A 5.03L
Part B 3.8L

SHELF LIFE

MasterInject 1333 has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Material Safety Data Sheet (MSDS) from our office or our website.

ID#MasterInject1333v1 ASEAN-0613

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals offices in ASEAN

Singapore Tel: +65-6861-6766 Fax: +65-6861-3186	Malaysia Tel: +60-3-5628-3888 Fax: +60-3-5628-3776	Indonesia Tel :+62-21-2988-6000 Fax :+62-21-2988-5935	Thailand Tel :+66-2769-8564 Fax :+66-2769-8584	Vietnam Tel: +84-650-374-3100 Fax: +84-650-374-3200	Philippines Tel: +63-2-889-4321 Fax: +63-2-889-4361	Hong Kong Tel: +852-24074291 Fax: +852-24067391
--	---	--	---	--	--	--

Website: www.ap.cc.basf.com