

# MasterGlenium<sup>®</sup> ACE 8526

High-range superplasticiser for precast concrete

## DESCRIPTION

**MasterGlenium ACE 8526** is an innovative polycarboxylic ether (PCE) based superplasticiser ideally suited for precast industry. Due to a specifically tailored formulation, this admixture shows excellent dispersion of cement at low water binder ratio. As a result, **MasterGlenium ACE 8526** provides exceptional good early strength development and maintains flowability for a considerable period of time.

The formerly unrivaled combination of early strength, slump retention and final strength development allows **MasterGlenium ACE 8526** to be considered ideally for precast application under difficult condition.

It is formulated to comply with ASTM C494 for Type F admixtures and BS-EN 934-2:2001.

## Compatibility

**MasterGlenium ACE 8526** is compatible and recommended for use with:

- Viscosity Modifying Agents to produce SCC.
- MasterAir, air entraining admixture, to improve freeze-thaw resistance.

**MasterGlenium ACE 8526** is not compatible with the MasterRheobuild superplasticisers.

## FEATURES AND BENEFITS

**MasterGlenium ACE 8526** offers the following benefits for the precast concrete industry:

- High impermeability and strength
- Improved and excellent durability
- Very high workability
- No segregation even at high workability
- Excellent concrete quality
- Produce Rheoplastic and Self Consolidating Concrete with a low w/c ratio.
- Optimize curing cycle by shortening curing time or decreasing curing temperature.
- Eliminate heat curing.
- Eliminate energy required for placing, consolidation and curing.
- Increase productivity.

- Improve surface appearance.
- Produce durable precast concrete elements.
- As compared to the traditional superplasticisers, improve engineering properties such as early and ultimate compressive and flexural strengths.

## APPLICATION

**MasterGlenium ACE 8526** is a liquid admixture to be added to the concrete during the mixing process. The best results are obtained when the admixture is added after all the other components are already in the mixer and after the addition of at least 80% of the total water.

## DOSAGE

The normally recommended dosage rate is 0.60 to 1.5 litres per 100 kg of binder. Other dosages may be used in special cases according to specific job site conditions. In this case, please consult our BASF Construction Chemicals representative.

## PACKAGING

**MasterGlenium ACE 8526** is available in bulk and 205L drums.

## SHELF LIFE

**MasterGlenium ACE 8526** must be stored in a place where the temperature is not below 0°C. In case the product freezes, increase the temperature of the product to 30°C and remix.

## PRECAUTIONS

**Health: MasterGlenium ACE 8526** does not contain any hazardous substances requiring labelling.

It is safe for use with standard precautions followed in the construction industry, such as use of hand gloves, safety goggles, etc.

For detailed Health, Safety and Environmental Recommendations, please consult and follow all instructions on the product Material Safety Data Sheet.



We create chemistry

# MasterGlenium<sup>®</sup> ACE 8526

---

© = registered trademark of BASF group in many countries

MY#MasterGlenium\_ACE\_8526 asean v1-0218

---

**STATEMENT OF RESPONSIBILITY**

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

---

**NOTE**

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

---

#### BASF Construction Chemicals offices

**Singapore**

Tel :+65-6861-6766  
Fax :+65-6861-3186

**Malaysia**

Tel :+60-3-5628-3888  
Fax :+60-3-5628-3776

**Indonesia**

Tel :+62-21-526-2481  
Fax :+62-21-526-2493

**Thailand**

Tel :+66-2769-8564  
Fax :+66-2769-8584

**Vietnam**

Tel :+84-650-3743-100  
Fax :+84-650-3743-200

**Philippines**

Tel :+63-2-811-8000  
Fax :+63-2-838-1025

Website : [www.master-builders-solutions.asiapacific.basf.com](http://www.master-builders-solutions.asiapacific.basf.com)