

MasterGlenium[®] ACE 8529

High-range superplasticiser for precast manufacturing

DESCRIPTION

MasterGlenium ACE 8529 is an innovative polycarboxylic ether (PCE) based superplasticiser ideally suited for precast industry. Due to a specifically tailored formulation, this admixture shows excellent dispersion of cement at low water binder ratio. As a result, **MasterGlenium ACE 8529** provides exceptional good early strength development and maintains workability for a considerable period of time. The product also significantly improves the final strength.

The formerly unrivaled combination of early strength, slump retention and final strength development allows **MasterGlenium ACE 8529** to be considered ideally for precast application under difficult condition.

It is formulated to comply with ASTM C494 for Type F admixtures and BS-EN 934-2:2001.

Compatibility

MasterGlenium ACE 8529 is compatible and recommended for use with:

- Viscosity Modifying Agents to produce SCC.
- MasterAir, air entraining admixture, to improve freeze-thaw resistance.

MasterGlenium ACE 8529 is not compatible with the MasterRheobuild superplasticisers.

CHEMISTRY AND MECHANISM

MasterGlenium ACE 8529 is differentiated from conventional superplasticisers in that it is based on a unique polycarboxylate ether polymer with long lateral chains. This greatly improves cement dispersion. Conventional superplasticisers, such as those based on sulphonated melamine and naphthalene formaldehyde condensates, at the time of mixing, become absorbed onto the surface of the cement particles. This absorption takes place at a very early stage in the hydration process. The sulphonic groups of the polymer chains increase the negative charge on the surface of the cement particle and dispersion of the cement occurs by electrostatic repulsion.

At the start of the mixing process the same electrostatic dispersion occurs as described previously, but the presence of the lateral chains, linked to the polymer backbone, generate a steric

hindrance, which stabilises the cement particles capacity to separate and disperse. This mechanism provides flowable concrete with greatly reduced water demand.

FEATURES AND BENEFITS

MasterGlenium ACE 8529 offers the following benefits for the precast concrete industry:

- High impermeability and strength
- Improve durability of precast concrete elements
- Excellent concrete quality
- Produce Rheoplastic and Self Consolidating Concrete with a low w/c ratio.
- Optimize curing cycle by shortening curing time or decreasing curing temperature.
- Eliminate energy required for placing, consolidation and heat curing
- Improve productivity
- Improve surface appearance
- As compared to the traditional superplasticisers, improve engineering properties such as early and ultimate compressive and flexural strengths.

APPLICATION

MasterGlenium ACE 8529 is a liquid admixture to be added to the concrete during the mixing process. The best results are obtained when the admixture is added after all the other components are already in the mixer and after the addition of at least 80% of the total water.

DOSAGE

The normally recommended dosage rate of **MasterGlenium ACE 8529** is 0.5 to 1.5 litres per 100 kg of binder. Other dosages may be used in special cases according to specific job site conditions. In this case, please consult our BASF Construction Chemicals representative.

PACKAGING

MasterGlenium ACE 8529 is available in bulk and 1000L IBC.



We create chemistry

MasterGlenium[®] ACE 8529

SHELF LIFE

MasterGlenium ACE 8529 can be stored for 12 months if stored at a temperature above 5°C and in tightly sealed original containers. If found to be frozen, thaw it and reconstitute by stirring.

PRECAUTIONS

Health: MasterGlenium ACE 8529 does not contain any hazardous substances requiring labelling.

It is safe for use with standard precautions followed in the construction industry, such as use of hand gloves, safety goggles, etc.

For detailed Health, Safety and Environmental Recommendations, please consult and follow all instructions on the product Material Safety Data Sheet.

® = registered trademark of BASF group in many countries

MY#MasterGlenium ACE 8529 v1-0417

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF Construction Chemicals publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF Construction Chemicals either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF Construction Chemicals, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals offices in ASEAN

Singapore Tel :+65-6861-6766 Fax :+65-6861-3186	Malaysia Tel :+60-3-5628-3888 Fax :+60-3-5628-3776	Indonesia Tel: +62-21-2988-6000 Fax: +62-21-2988-5935	Thailand Tel :+66-2769-8564 Fax :+66-2769-8584	Vietnam Tel :+84-650-3743-100 Fax :+84-650-3743-200	Philippines Tel : +63-2-811-8000 Fax : +63-2-838-1025
--	---	--	---	--	--

Website : www.master-builders-solutions.asiapacific.basf.com