

# MasterCast<sup>®</sup> 763P

**New generation of polycarboxylic ether based plasticizer for Manufactured Concrete Products, specially engineered for use in production hollow-core slabs, masonry and paving blocks**

## DESCRIPTION

**MasterCast 763P** is an innovative multi-purpose plasticizer based polycarboxylic ether polymers specially developed for semi-dry concrete mixes. The product is suitable for the production of hollow-core slabs, masonry and paving blocks. At the same time, **MasterCast 763P** accelerates the strength development and reduces the cycle time whilst the appearance is maintained or even improved.

Due to its unique principle of action on the cement grain, **MasterCast 763P** fully exploits the hydration potential of cement resulting in higher early strengths and shorter curing times.

## FIELDS OF APPLICATION

**MasterCast 763P** is suitable for Manufacturing Concrete Products, especially:

- Pavers
- Blocks
- Hollow-core slabs

## FEATURES AND BENEFITS

**MasterCast 763P** offers the following benefits for the MCP industry to:

- Optimised mix design
- Enhanced productivity due to shorter cycle time
- Higher early strength
- Optimised curing cycles due to shorter curing times

## PACKAGING

**MasterCast 763P** is available in 210 litre drums or bulk.

## APPLICATION PROCEDURE

**MasterCast 763P** is a liquid ready-to-use admixture to be added to the concrete during the mixing process. The best results are obtained when the admixture is added after all the other components are already in the mixer and after the addition of at least 80% of the total water. The water content is adjusted to obtain the desired consistence or workability.

## TYPICAL PROPERTIES\*

|                         |  |
|-------------------------|--|
| Appearance              | Whitish to light brownish coloured liquid. |
| Specific gravity @ 25°C | 1.07                                       |
| pH-value                | 5 - 7                                      |

## STANDARDS

EN 934-2 Table 3.1 and 3.2

## DOSAGE RATE

The normally recommended dosage rate is 0.4 to 1.2 litres per 100kg of cementitious material.

Other dosages may be used in special cases according to specific job site conditions. In this case please consult our Technical Services Department.

## COMPATIBILITY

**MasterCast 763P** is compatible and recommended for use with **MasterCast WP 793**, water repellent, to reduce water absorption (e.g. EN 1338, class 2 B)

**MasterCast 763P** is not compatible with **MasterCast 764** or **MasterRheobuild** superplasticizers.

**MasterCast 763P** is suitable for mixes containing:

- Microsilica (Silica Fume)
- Fly Ash (PFA)
- GGBS (ground granulated blast furnace slag)

## STORAGE

**MasterCast 763P** should be stored out of direct sunlight and protected from extremes of temperature. The shelf life is 1 year when stored as above.

The occurrence of a surface layer with **MasterCast 763P** is normal and will have no effect on the performance of the product.



We create chemistry

# MasterCast® 763P

## SAFETY PRECAUTIONS

**MasterCast 763P** contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF\_CC-UAE/Cast\_763P\_10\_06/v2/03\_16

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals UAE LLC  
P.O. Box 37127, Dubai, UAE  
Tel: +971 4 8090800, Fax: +971 4 8851002  
www.master-builders-solutions.basf.ae

**Disclaimer:** the LRQA mark relates to certified management system and not to the product mentioned on this datasheet



**MASTER®**  
**» BUILDERS**  
**SOLUTIONS**