

MasterCast® 779

New generation polycarboxylate ether based plasticizer for Manufactured Concrete Products, specially engineered for block and paver mixes.

DESCRIPTION

MasterCast 779 is an innovative multi-purpose plasticizer based on polycarboxylate ether polymers specially developed for semi-dry concrete mixes. The product is suitable for the production of blocks and pavers. At the same time, **MasterCast 779** accelerates the strength development and reduces the cycle time whilst the appearance is maintained or even improved.

Due to its unique principle of action on the cement grain, **MasterCast 779** fully exploits the hydration potential of cement resulting in higher early strengths and shorter curing times.

FIT 4 VALUE:

MasterCast 779 is a key component to BASF's FIT 4 VALUE concept.

FIT 4 VALUE considers the four elements essential for MCP Manufactures:

1. FIT for Economics
2. FIT for Performance
3. FIT for Aesthetics
4. FIT for Durability

Here, FIT means meeting every requirement for economics, performance, aesthetics and durability.

FIELDS OF APPLICATION

MasterCast 779 is suitable for Manufacturing Concrete Products, especially:

- Pavers
- Blocks

FEATURES AND BENEFITS

MasterCast 779 offers the following benefits for the MCP industry:

- Optimised mix design
- Enhanced productivity due to shorter cycle time
- Higher early strength
- Optimised curing cycles due to shorter curing times

PACKAGING

MasterCast 779 is available in 210 litre drums or bulk.

APPLICATION PROCEDURE

MasterCast 779 is a liquid ready-to-use admixture to be added to the concrete during the mixing process. The best results are obtained when the admixture is added after all the other components are already in the mixer and after the addition of at least 80% of the total water. The water content is adjusted to obtain the desired consistence or workability.

TYPICAL PROPERTIES*

Appearance	Whitish to light brownish coloured liquid
Specific gravity @ 25°C	1.025
pH-value	4.5 – 6.5

DOSAGE RATE

The normal recommended dosage range is 0.4 to 1.2 litres per 100 kg of cementitious material.

Other dosages may be used in special cases according to specific job site conditions. In this case please consult our Technical Services Department.

COMPATIBILITY

MasterCast 779 is compatible and be for use with:

- **MasterCast 740**, plasticizer.
- **MasterCast WP 793**, water resisting / repellent, to reduce water absorption.

MasterCast 779 is not compatible with **MasterCast 764** or **MasterRheobuild** superplasticizers.



We create chemistry

MasterCast® 779

STORAGE

MasterCast 779 must be stored in a place where the temperature does not drop below 5°C.

If stored in unopened containers according to manufacturer's instructions, the shelf life is 1 year.

HANDLING AND TRANSPORTATION

No special requirements must be observed while the product is used. Protection gloves and glasses are recommended. Do not eat, drink or smoke during the application. **MasterCast 779** is non-flammable, non-toxic or irritant and is not subject to special transport requirements.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

* Properties listed are based on laboratory controlled tests.

BASF_CC-UAE/Cast_779_04_13/v2/07_15

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals UAE LLC
P.O. Box 37127, Dubai, UAE
Tel: +971 4 8090800, Fax: +971 4 8851002
www.master-builders-solutions.basf.ae

Disclaimer: the LRQA mark relates to certified management system and not to the product mentioned on this datasheet



MASTER®
BUILDERS
SOLUTIONS