

MasterRheobuild® 3015

High range, water reducing superplasticiser for concrete including mixes containing GGBS and microsilica

DESCRIPTION

MasterRheobuild 3015 is formulated from synthetic polymers specially designed to impart rheoplastic qualities to concrete, particularly those containing GGBS or microsilica.

A rheoplastic concrete is a fluid concrete with a slump of at least 200 mm, easily flowing, but at the same time free from segregation and having the same water/cement ratio as that of a low slump concrete (25mm) without admixture.

MasterRheobuild 3015 is chloride free.

ADVANTAGES

MasterRheobuild 3015 considerably improves the properties of fresh and hardened concrete.

PRIMARY USES

- Mass concrete pours
- Ready mixed concrete
- Pumped concrete
- Casting in hot climates

To obtain:

- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths.
- Reduced permeability
- Improved durability

COMPATIBILITY

MasterRheobuild 3015 is suitable for use with all types of Portland Cement including OPC (CEM1) SRC and MSRC.

MasterRheobuild 3015 is suitable for mixes containing:

- Microsilica (Silica Fume)
- Fly Ash (PFA)
- GGBS (ground granulated blast furnace slag)

PACKAGING

MasterRheobuild 3015 is available in bulk or in 210 litre drums.

TYPICAL PROPERTIES*

Colour:	Dark brown liquid
Specific gravity:	1.225 at 25°C
Chloride content:	"chloride-free" to EN 934
Freezing point:	0°C

STANDARDS

EN 934-2 Tables 3.1, 3.2, 11.1 and 11.2
ASTM C-494 Type A, B, D, F and G

DOSAGE

Optimum dosage of **MasterRheobuild 3015** should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial. In normal concrete a dosage of between 0.8-2.0 litre / 100kg total cementitious material. In a high performance, low water cement ratio concrete, a dosage of between 1.5-2.5 litre / 100kg total cementitious material. Dependent upon mix requirement, it is possible to use a higher dosage of **MasterRheobuild 3015** without causing any adverse effects upon the concrete. Please consult BASF Construction Chemicals Technical staff for further information.

DISPENSING

MasterRheobuild 3015 is a ready-to-use liquid which is dispensed into the concrete together with the mixing water. The plasticising effect and water reduction are higher if the admixture is added to the concrete after 50 to 70% of the mixing water has been added. The addition of **MasterRheobuild 3015** to dry aggregate or cement is not recommended. Automatic dispensers are available.

MasterRheobuild® 3015

WORKABILITY

MasterRheobuild 3015 ensures that rheoplastic concrete remains workable in excess 3 hours at +20°C.

Workability loss is dependent on temperature, and on the type of cement, the nature of aggregates, the method of transport and initial workability. It is strongly recommended that concrete should be properly cured particularly in hot and dry climates.

STORAGE

MasterRheobuild 3015 must be stored where temperatures do not drop below +5°C. If the product has frozen thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

MasterRheobuild 3015 is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the material safety data sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/Rh_3015_10_15/v1/

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.