

MasterRheobuild[®] 601

High range water reducing / superplasticising concrete admixture

DESCRIPTION

MasterRheobuild 601 is a high range, high performance superplasticiser and water reducing agent. **MasterRheobuild 601** disperses and deflocculates cement particles thereby increasing the workability and flowability of the concrete mixes.

PRIMARY USES

MasterRheobuild 601 is formulated for use by commercial ready-mix operators, who can benefit from its multiple role characteristics.

TYPICAL APPLICATIONS

- In areas of congested reinforcement where high workability will ease placement and compaction.
- Hot weather concreting where extension of workability and controlled delays to initial set are beneficial.
- To effect reductions in the water cement ratio enabling either higher strength or cement economy.

COMPOSITION

A multi-component admixture based upon high molecular weight polymers.

ADVANTAGES

- Effective over high range of cement contents and types.
- Improves pumpability, durability and impermeability.
- Extended slump retention time - maintains workability in excess of concrete produced utilising conventional superplasticisers
- Reduces placing problems in hot weather by improved workability retention in conjunction with controlled setting times.

ACTION

MasterRheobuild 601 acts on the cement particles by its powerful deflocculating and sequestering action to retard and maximise the hydration of the cement paste. Its powerful plasticising action results in high workability concrete which is responsive and cohesive. This action enables concrete with low or reduced water contents to be produced.

PACKAGING

MasterRheobuild 601 is available in bulk or in 210 litre drums.

TYPICAL PROPERTIES*

Colour	dark brown liquid
Specific gravity	1.235 at 25°C
Chloride content	"chloride-free" to EN 934-2
Freezing point	0°C

STANDARDS

ASTM C-494 Types F and G
EN 934-2 Tables 3.1, 3.2, 10.1 and 10.2

DIRECTIONS FOR USE

MasterRheobuild 601 should be added to the concrete mix during the mixing cycle at the same time as the water. Never add **MasterRheobuild 601** to the dry cement.

DOSAGE

The normal range is 0.8 -2.0 litre/100 kg total cementitious material. Higher dosages may be required when certain combinations of materials and conditions are present. In all cases, trial mixes should be carried out to determine the optimum dosage required to achieve the desired concrete property.

MasterRheobuild® 601

COMPATIBILITY

MasterRheobuild 601 can be used with all types of Portland cement including Sulphate Resisting and modified cement (Type II). For use with special cements, contact BASF's Technical Services Department.

MasterRheobuild 601 is suitable for mixes containing:

- Microsilica (silica fume)
- Fly Ash (pulverized fuel ash)
- GGBS (ground granulated blast furnace slag)

MasterRheobuild 601 should not be premixed with other admixtures. If other admixtures are to be used in the concrete containing

MasterRheobuild 601, they must be dispensed separately. Contact BASF's Technical Services Department for further advice.

DISPENSING

MasterRheobuild 601 should be dispensed through a proprietary dispenser, such as is available from BASF. Details available upon request.

SAFETY PRECAUTIONS

MasterRheobuild 601 contains no hazardous substances requiring labelling. For further information, refer to material safety data sheet.

STORAGE

Store under cover, out of direct sunlight and protect from extremes of temperature. Shelf life is up to 2 years when stored as above. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/Rh_601_11_07/v2/07_15

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.