

# MasterSeal<sup>®</sup> 912

## Swelling gasket in paste form

### DESCRIPTION

**MasterSeal 912** is a one component, moisture curing pre-polymer which is reswellable when in contact with water, suitable for the permanent sealing of construction joints in concrete structures.

### ADVANTAGES

- Simple use
- High swelling capacity in contact with water
- Highly resistant to chemicals and saline liquids (see chemical resistance table)
- Good adhesion to dry and moist surfaces (concrete, steel and plastics)
- Reversible swelling process

### FIELDS OF APPLICATIONS

- Construction joints of every kind.
- Connecting joints in sheet pilings or diaphragm walls.
- Sealing of bell butt joints.
- Wall penetration for metal, plastic and concrete pipes, cable bushing.
- Bonding of **MasterSeal 910** swelling waterstops on very uneven or rough surfaces. **MasterSeal 910** swelling waterstops are pressed strongly into the paste bead.
- Surrounding steel reinforcement bars on pile heads.

### USES

- **MasterSeal 912** swelling paste is supplied in ready to use cartridges.
- The substrate must be free of grease, dust and loose particles. Do not apply on frozen surfaces.
- Hardening prior to concreting is min. 24 hours.
- The swelling paste should be protected against premature swelling.
- When concreting, take care to ensure that the expanding paste is fully covered by concrete.

### PACKAGING

310ml cartridge  
6 x 310ml cartridges per carton  
147 cartons = 882 cartridges per pallet  
Available on special requests:  
600ml cartridge  
12 x 600ml sausages per carton

### DIRECTIONS FOR USE

- The paste can be applied with a suitable hand-held caulking gun.
- Puncture and lift the double layer bottom of the cartridge, remove the pellets.
- Puncture the opening of the cartridge and free entire cross section.
- Cut the nozzle diagonally to obtain an opening of 6-10mm and place the cartridge in the caulking gun.
- Direct the caulking gun along the surface at an angle of 45° extrude paste evenly and press the paste bead against the substrate.
- For large jobs and ease of application we recommend pneumatic guns or mechanical guns with high gear.

### PROPERTIES

- On contact with water, the cured swelling gasket paste swells and seals the construction joint against water penetration.
- An increase in volume of up to around 250% produced by storage of water in the paste's molecular structure.

### LAYER THICKNESS

Usually 5-10mm

### YIELD

Depending on substrate approx. 5m per 310 ml cartridge.

# MasterSeal<sup>®</sup> 912

## CHEMICAL RESISTANCE

Test Liquid	Stability	Swelling
Unleaded fuel	resistant / discolouring	~ 45%
Gasoline	resistant / discolouring	~ 2%
Toluene	resistant	~ 140%
Xylene	resistant	~ 85%
Methanol 50%	resistant	~ 400%
Isopropanol 50%	resistant	~ 500%
N-methylpyrrolidone	limited resistant / discolouring	~ 615%
Ethylacetate	resistant	~ 195%
Methylisobutylketone	resistant	~ 85%
Acetic acid 10%	limited resistant	~ 150%
Formol 36%	resistant	~ 500%
Sulphuric acid 10%	resistant	~ 190%
Sulphuric acid 20%	resistant	~ 210%
Sulphuric acid 26%	resistant	~ 25%

## TEMPERATURE

+5° to +40°C

Low temperatures will render more difficult to extrude and retard the hardening process of the paste. During cold weather we recommend to store the paste in warm conditions prior to use.

## STORAGE

Store in a well enclosed, cool and dry place.

## SHELF LIFE

**MasterSeal 912** has a shelf life of 9 months (stored at +5°C to +25°C) if stored in a well enclosed, cool and dry place.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

**BASF\_CC-UAE/SI\_912\_04\_02/v1/12\_13**

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.