

# MasterSeal<sup>®</sup> M 266

## Two-component polyurethane waterproofing coating

### DESCRIPTION

**MasterSeal M 266** is a two-component, polyurethane, liquid applied, waterproof coating. The resulting membrane is an elastomeric waterproofing.

### TYPICAL APPLICATIONS

**MasterSeal M 266** is recommended for waterproofing and damp proofing applications in basements, bathrooms, kitchens, pools, refrigeration storage, roofs and other wet areas.

### ADVANTAGES

- High bond strength
- High tensile strength and elongation
- High build application in a single layer two coat application is recommended
- High solid content
- Chemical cure, does not need the presence of moisture
- Corrosion resistant, mildew proof and frost-resistant

### SYSTEM CHARACTERISTICS

Thickness of coated film: In below ground structures, wet areas and roofs it should not be less than 1.2mm dft.

Where a superior performance is required the material can be reinforced with a layer of woven glass fiber mesh. Each coat encapsulating the mesh should be 1mm dft.

All liquid applications should be applied in at least two coats to achieve the desired thickness.

For vertical applications at high temperatures additional fibres may be required. Please contact BASF Construction Chemicals Technical Services Department for assistance.

### STORAGE

The product should be stored in a dry and shaded area. Shelf life of the product is one year from the date of manufacture.

### PACKAGING

**MasterSeal M 266** is supplied in two components.

Part A: 8kg

Part B: 20kg

### STANDARD

ASTM C836

### PHYSICAL / CHEMICAL PROPERTIES

Tensile strength ASTM D412	3N/mm <sup>2</sup>
Elongation at break ASTM D412	700%
Water impermeability (0.3MPa/30min)	Impermeable
Solid content	≥ 90%
Surface drying (time/hr)	≤ 8
Drying (time/hr)	≤ 24
Bond strength on damp substrate	0.50MPa
Pot life @ 25°C	>70 mins

### APPLICATION PROCEDURE

#### SUBSTRATE PREPARATION

The substrate should be smooth, clean, and free of laitance, grease, oils and standing water.

#### MIXING

The two components should be mixed thoroughly using mechanical means. The mixing should be carried out in a separate container. Part B should be poured in the separate container and Part A should be added while stirring/agitating the Part B. Mix thoroughly until uniform, before applying to the substrate.

# MasterSeal<sup>®</sup> M 266

## PRECAUTIONS DURING APPLICATION

- No obvious water accumulation should be present on the substrate. Any water should be removed at least 24 hours prior to application and the substrate should be substantially dry.
- The application temperature should be between 5°C-40°C. Construction site should be well ventilated.
- After mixing of two components, material should be used within the gel time, this may vary depending on the temperature.

## YIELD

One unit 28kg will yield 21.53 liters, and should cover 16.16 m<sup>2</sup> for a 1.2mm dft.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF Construction Chemicals representative.

BASF reserves the right to have the true cause of any liability determined by accepted test methods.

## QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational Health & Safety standards ISO 9001, ISO 14001 and OHSAS 18001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF\_CC-UAE/SI\_M266\_04\_10/v2/01\_17

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.