

MasterTop[®] 1324 AS

Polyurethane based anti-static low emission flooring system

DESCRIPTION

MasterTop 1324 AS is a conductive, solvent-free system utilising a polyurethane resin bodycoat. For use in rooms where sensitive electronic equipment is used as well as rooms where explosion hazards exists.

MasterTop 1324 AS is a build-up system consisting of:-

- **MasterTop P 617** - a high grade, low-viscosity, two component epoxy resin primer and substrate sealer.
- **MasterTop P 687WAS** - An electrically conductive, water based epoxy primer for use on **MasterTop P 617** primer in combination with **MasterTop BC 375NAS** to produce static conductive floor coating meeting the requirements of DIN 51953 .
- **MasterTop BC 375NAS** - Is a solvent-free, pigmented two component coating based on polyurethane resins that produces hard-wearing anti-static, conductive industrial floors.

PRIMARY USES

As a conductive flooring system in electronic and explosion risk areas.

COVERAGE

MasterTop P 617	0.15-0.30 kg/m ² porous substrates may require additional coats of MasterTop P617
MasterTop P 687WAS	0.08-0.10 kg/m ²
MasterTop BC 375NAS	2.5kg/m ²

THICKNESS

Total 2mm

TYPICAL PROPERTIES*

MasterTop 1324 AS conforms to the following Standards:-

104 – 106 Ohm (EN 1081)

Below 109 Ohm (IEC 61340-5-1)

ESD Approval in Sweden (SP & Ericsson)

PACKAGING

MasterTop 1324 AS is supplied as follows:

MasterTop P 617 18kg

MasterTop P 687WAS 15kg

MasterTop BC 375NAS 30kg

GUIDE TO APPLICATION

PREPARATION

Remove laitance, weak or friable concrete and all contaminants that could affect the bond to the substrate.

Suitable preparation includes light grit blasting, surface grinding etc. Surface defects should be repaired using **MasterTop 2200** or other suitable repair compound from the **MasterEmaco** range.

For full preparation details please refer to our latest BASF Method Statement.

PRIMING

Mix and apply **MasterTop P 617** primer to the prepared dust free surface at approximately 0.15-0.30 kg/m².

Allow to dry.

For the production of anti-static floor coatings, do not broadcast sand into the **MasterTop P 617**. Self-adhesive copper tape with a cross section of 0.09 mm x 19 mm (e.g. 3M Scotch) is firmly applied to the cured **MasterTop P 617** at distances of about 20 m. There should be an earthing point for every 100m² floor area. Floors of less than 100m² should have two earthing points.

MasterTop[®] 1324 AS

Mix the two components of **MasterTop P 687WAS** primer together for at least 3 minutes using a slow running drill. Pour the mixed material into a clean container and re-mix. Application is by means of a lambswool roller to the surface prepared as above.

Do not apply **MasterTop P 687WAS** at temperatures below +12°C and above +30°C. The substrate temperature must be at least 3°C above the dewpoint.

Ensure good ventilation during the application.

Overlay application:

Mark the floor area out in 10 or 20m² areas so that consumption can be checked.

Mix the A and B components of **MasterTop BC 375NAS** together using a slow speed (300-400 rpm), drill fitted with a suitable mixing head. Mix until a uniform streak free colour is obtained. Pour the mixed material onto the floor and spread using a notched trowel to achieve the desired thickness. Roll with a spiked roller to release entrapped air and ensure a smooth surface. Allow to cure.

CHEMICAL RESISTANCE

Contact the Regional BASF Office.

STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

SAFETY PRECAUTIONS

For further information, a material safety data sheet is available to the specialist applicator.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/Top_1324AS_01_99/v3/01_15

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.