







# MasterTop 1326

**Decorative comfort polyurethane system, smooth, matt or satin matt, low emission**  
**Fields of application: UV-stable, decorative indoor floor available in a range of brilliant colours for different decorative effects is required: for example offices, exhibitions and fair grounds, shops, hospitals, schools, cafeterias etc.**

**Consumption:**

	<b>Primer</b>	<b>MasterTop P 617 (or P 615 without broadcast)</b> EP, 2-component, non-solvented (total solid)	0,3-0,5 kg/m <sup>2</sup>
	<b>Sand broadcast</b>	Oven dried silica sand, size Ø 0,3-0,8 mm, uniformly applied, not in excess	0,8-1,0 kg/m <sup>2</sup>
	<b>Optional/ Scratch primer up to 1 mm</b>	<b>MasterTop P 617 (or P 615 without broadcast)</b> EP, 2-component, non-solvented (total solid), 1 : 0,5 filled with oven dried silica sand, size Ø 0,1-0,3 mm	0,6-1,0 kg/m <sup>2</sup> *
	<b>Sand broadcast</b>	oven dried silica sand, size Ø 0,3-0,8 mm	2,0-3,0 kg/m <sup>2</sup>
	<b>Body coat</b>	<b>MasterTop BC 361N</b> pigmented, PU, 2-component, UV- stable, non-solvented, low emission	2,5-3,0 kg/m <sup>2</sup>
	<b>Top coat</b>	<b>MasterTop TC 407W (transparent)</b> transparent, PU, 2-component, water borne, matt, UV-stable	0,12-0,14kg/m <sup>2</sup>
	<b>Total thickness of the system</b>	ca. 2,0-2,5 mm	

**Remark:** Consumptions are indicative and may be higher, depending on substrate roughness, temperature and porosity, as well as waste produced during application.

\* Consumption incl. filler



# MasterTop 1326

## Decorative comfort polyurethane system, smooth, matt or satin matt, low emission

The flooring system fulfills, as minimum requirements, the following properties and technical data determined by internal and external testing:

DIBt General technical approval **Z-156.605-687** according to DIN EN 13813:2003-1 for an utilization indoor in public areas with Health-related Evaluation Procedure for Volatile Organic Compounds Emissions (VOC and SVOC).

EN 13813	SR-B1,5-AR1-IR4-Bfl-s1
Emissions behavior	AgBB conform, AFSSET conform, A+ classification
Taber abrasion	< 50 mg / 1000 R (Taber)
Crack bridging at 23 °C	Class A 3 according to DIN EN 1062-7 requirement > 500 µm, result = 550 µm
Slip resistance	R 9
Fire behavior according to DIN EN 13501-1	Bfl-s1

### CONTACT

Should you require any further information, please do not hesitate to contact your local sales consultant or take directly contact with us:

#### Performance Flooring

BASF Construction Chemicals Europe AG  
Hardmatt 434  
CH-5082 Kaisten  
Tel: +41 62 868 93 60  
Fax: +41 62 868 93 59

BASF Coatings GmbH  
Donnerschweer Str. 372  
D-26123 Oldenburg  
Tel: +49 441 3402 251  
Fax: +49 441 3402 333

Mitglied der






# MasterTop 1326

Decorative comfort polyurethane system, smooth, matt or satin matt, low emission

## CE marking according to EN 13813

	
BASF Coatings GmbH Donnerschweer Str. 372, D-26123 Oldenburg	
09	
132601	
EN 13813: 2002	
EN 13813: SR-B1,5-AR1-IR4	
Synthetic resin screed for internal uses	
Essential characteristics	Performance
Fire behavior	Bfl-s1
Release of corrosive substances	SR
Water permeability	NPD
Wear resistance	< AR 1
Bond strength	> B 1,5
Impact resistance	> IR 4
Impact sound insulation	NPD
Sound absorption	NPD
Heat insulation	NPD
Chemical resistance	NPD
Slip/Skid resistance	R9
Emissions behavior	Ü-Z: Z-156.605-687

NPD = No performance determined

Performance determined in System build-up **MasterTop 1326**



# MasterTop 1326

**Decorative comfort polyurethane system, smooth, matt or satin matt, low emission**

**Disclaimer:**

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with BASF and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.