

MasterRoc[®] MP 303 CE

Formerly MEYCO MP 303 CE

Low viscosity, fast reacting acrylic resin with adjustable reaction speed for permanent water sealing and layer curtaining of concrete and masonry

Product description

MasterRoc MP 303 CE is a highly reactive two-component acrylic sealing resin with a low viscosity for good penetration. The product cures quickly, forming a highly flexible hydrogel with excellent swelling/re-swelling properties.

Fields of application

- Concrete repair – swelling fitted filling of cracks and fissures (EN 1504-5: category S)
- Curtain injection
- Permanent water sealing of tunnel and shaft concrete linings and masonry
- Stopping of minor water inrush through cracks

Features and benefits

- Upon curing forms a highly flexible compact resin with good adhesion properties even on damp or wet surfaces.
- The cured resin is resistant to acidic and alkaline solutions as well as many other solvents.
- Can swell to more than 200% of its initial volume, accommodating structural and ground movement. The swelling is reversible and after dry periods the resin maintains its self-healing properties.
- Good bond strength to fractured rock and concrete, even under wet conditions.
- Very low viscosity (close to water) allows deep penetration at low pressure into very fine cracks or fissures and long flow paths.
- Controlled gel time between 14 seconds and 3 minutes at 20°C. With the retarder the gel time can be prolonged to more than 40 minutes.
- Environmentally friendly: Harmless in contact with groundwater and no emission of dangerous substances.

Packaging

Standard packaging

MasterRoc MP 303 CE Resin:	22.5 kg can
MasterRoc MP 303 CE Accelerator:	1.0 kg can
MasterRoc MP 303 CE Hardener:	1.0 kg can
MasterRoc MP 303 CE Retarder:	1.0 kg can

Technical data

MasterRoc MP 303 CE Resin

Appearance	Clear blue liquid
Viscosity (20°C)	40 mPa·s
Density (20°C)	1.19 kg/l

MasterRoc MP 303 CE Accelerator

Appearance	Clear liquid
Viscosity (20°C)	280 mPa·s
Density (20°C)	1.12 kg/l

MasterRoc MP 303 CE Hardener

Appearance	White solid
Density (20°C)	Approx. 2.6 kg/l

MasterRoc MP 303 CE Retarder

Appearance	Clear yellowish liquid
Viscosity (20°C)	~1 mPa·s
Density (20°C)	1 kg/l

Mixed material (mixing ratio Resin : Part B of 1:1 without retarder)

Appearance	Clear blue liquid
Viscosity (20°C)	5 mPa·s
Density (20°C)	1.14 kg/l
Gel time (20°C)	10 seconds to 3 minutes
Final curing (20°C)	10 to 20 minutes

Application procedure

Premix the Resin (22.5 kg) with 4.5% of Accelerator (1 kg) to activate it prior to use.

To prepare Part B, take 20 l of water and dissolve 0.15% (30 g) to 5% (1 kg) of hardener powder in the water (the same volume of water as of activated resin). The amount of hardener is adjusted to the needed pot life (see Table 1).

MasterRoc[®] MP 303 CE

Formerly MEYCO MP 303 CE

The activated resin and Part B have a pot life of approx. 5 hours at 20 °C. The activated components are injected in the ratio of 1:1 by volume, using a two-component injection pump, equipped with a static in-line mixer. In cases of long open times a one-component pump can also be used.

For steel reinforcement injection, the amount of hardener powder should be limited to 1.5 % (e.g. 300 g).

Table 1: Hardener dosage to adjust gel time

Amount of MEYCO MP 303 CE Hardener		Gel time at 10°C [min]	Gel time at 20°C [min]
[%]	[g] per 20 kg water		
0.2	40	05:00	02:10
0.25	50	04:05	01:58
0.5	100	01:55	00:63
1	200	01:18	00:36
1.5	300	00:50	00:27
3	600	00:38	00:18
5	1000	00:24	00:14

CE certification tests have been carried out with approximately 0.5% of Hardener powder.

For special application where CE certification is not needed, the reaction can be prolonged using MasterRoc MP 303 CE retarder (see Table 2). Simply add 5% of Retarder into the premixed Part B. For the complete set this means 20 l of water, 1 l of Retarder and 30 g to 1 kg of Hardener.

Table 2: Hardener dosage and MasterRoc MP 303 CE Retarder to adjust gel time

Amount of MasterRoc MP 303 CE Hardener		Gel time at 10°C [min]	Gel time at 20°C [min]
[%]	[g] per 20 kg water and 1 kg Retarder		
1	200	103:00	40:57
2	400	40:40	15:16
3	600	21:45	10:25
4	800	12:48	7:02
5	1000	11:18	5:43

Please Note: The reaction time is dependent on the temperature of the components and the ground.

Cleaning of injection equipment

Equipment can easily be cleaned of uncured material using water (if possible with a detergent).

Storage

In unopened, tightly closed containers, the components of MasterRoc MP 303 CE can be stored for up to 12 months, if kept dry and within a temperature range of +10 °C to +30 °C, protected from sunlight.

Safety precautions

Please refer to the Material Safety Data Sheet for further safety measures.

Avoid contact with skin and eyes by using the required personal protective equipment, such as overalls, gloves and safety glasses.

If contact with skin occurs, wash thoroughly using soap and water. If contact with eyes occurs, rinse thoroughly with water and seek medical advice. The cured MasterRoc MP 303 CE is harmless.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand, and disposed of in accordance with local regulations.



We create chemistry

MasterRoc[®] MP 303 CE

Formerly MEYCO MP 303 CE

MEYCO[®] MP 303 CE	
BASF Construction Chemicals Europe Ltd. Im Tiergarten 7, CH-8055 Zurich, Switzerland	
13	
EN 1504-5	
Concrete injection product	
U (S2) W (1) (1/2/3) (5/40)	
Water tightness	7 · 10 ⁵ Pa
Viscosity	≤ 60 mPa.s
Corrosion behaviour	deemed to have no corrosive effect
Volume and weight changes by air drying and water storage	volume change 87 % weight change 76 %
Sensitivity to water	passed
Sensitivity to wet-drying cycles	passed
Compatibility with concrete	passed
Application temperature	+ 5°C to +40°C
Dangerous substances	comply with 5.4

The information given here is true, represents our best knowledge and is based not only on laboratory work but also on field experience. However, because of numerous factors affecting results, we offer this information without guarantee and no patent liability is assumed. For additional information or questions, please contact your local representative.

Headquarters:

BASF Construction Chemicals Europe Ltd

Global Underground Construction
Im Tiergarten 7, 8055 Zurich Switzerland
Phone +41 58 958 22 11
Fax +41 58 958 32 46

For more information: Visit us: www.ugc.basf.com Contact us: ugc@basf.com

BASF Construction Chemicals offices in Russia, Ukraine, Belarus

OOO "BASF Stroitelnye sistemy"

Moscow: +7 495 225 6436

St. Petersburg: +7 812 332 0412

Kazan: +7 843 212 5506

Krasnodar: +7 861 202 2299

Kiev: BASF T.O.V. +380 44 5915595

Minsk: +375 17 202 2471

E-mail: stroysist@basf.com www.master-builders-solutions.basf.ru