

# MasterRoc<sup>®</sup> MP 355 1K DW

Formerly MEYCO MP 355 1K DW

One component injection foam to stop small to mid-volume water ingress, with a potable water certificate.

## Product description

MasterRoc MP 355 1K DW is a solvent free, single component polyurethane foam which reacts only in contact with humidity or water, and is certified for contact with potable water (DW: Drinking Water).

## Fields of application

- Stopping of small to mid-volume water ingress in underground structures
- Also suitable for filling of water bearing voids

## Features and benefits

- Reacts in moist surroundings
- Good bonding to wet surfaces
- Forms a flexible foam

## Packaging

MasterRoc MP 355 1K DW: 25 kg cans  
Accelerator for MEYCO MP 355 1K DW: 2.5 kg cans

## Technical data

### MasterRoc MP 355 1K DW

Density, 20°C	1.16 g/cm <sup>3</sup>
Viscosity, 23°C	700 mPa.s
Color	Yellowish
Application temperature	+ 5°C to 40°C
Maximum foam expansion rate at 10% accelerator dosage	20-30

### Accelerator for MasterRoc MP 355 1K DW

Density, 20°C	1.10 g/cm <sup>3</sup>
Viscosity, 23°C	70 mPa.s
Color	Clear to yellowish

## Application procedure

1. Add the accelerator to MasterRoc MP 355 1K DW (up to 10%, depending on the required reaction time), mix quickly and thoroughly.
2. Inject this mixture through a single component injection pump. The moisture / water in the ground will generate a foaming reaction. In the case of dry ground, flush the borehole with water before injecting.

## Reaction Time

The reaction time depends on the ground and product temperature, as well as the accelerator dosage (see Table 1). Site trials should be performed in advance to establish the required reaction time.

Table 1:

Reaction Times with 10% water and 10% accelerator				
Initial Temperature (°C)	5	10	15	20
Start of reaction (sec)	130	65	30	15
End of reaction (sec)	350	250	120	60
Foam expansion rate (approximately)	20	25	25	30

## Cleaning of injection equipment

During short breaks in the injection procedure, the pump and hoses should be filled with non-accelerated resin to avoid blockages. After finishing the injection, pump an appropriate agent or oil which does not contain water through the pump and injection lines.



We create chemistry

# MasterRoc<sup>®</sup> MP 355 1K DW

---

Formerly MEYCO MP 355 1K DW

## Storage

MasterRoc MP 355 1K DW must be stored in airtight containers in a cool, dry place. If stored in original containers under the above mentioned conditions, it has a shelf life of 12 months. The product must be prevented from freezing.

## Safety precautions

MasterRoc MP 355 1K DW is not hazardous. However, follow standard safety procedures when handling the product and wear gloves and safety glasses.

Avoid eye and skin contact. If skin contact occurs, wash with plenty of water and soap. In case of eye contact rinse with plenty of water and seek medical advice. For further information refer to Material Safety Data Sheet.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand, and disposed of in accordance with local regulations.

The information given here is true, represents our best knowledge and is based not only on laboratory work but also on field experience. However, because of numerous factors affecting results, we offer this information without guarantee and no patent liability is assumed. For additional information or questions, please contact your local representative.

## Headquarters:

### BASF Construction Chemicals Europe Ltd

Global Underground Construction  
Im Tiergarten 7, 8055 Zurich Switzerland  
Phone +41 58 958 22 11  
Fax +41 58 958 32 46

For more information: Visit us: [www.ugc.basf.com](http://www.ugc.basf.com) Contact us: [ugc@basf.com](mailto:ugc@basf.com)

## BASF Construction Chemicals offices in Russia, Ukraine, Belarus

OOO "BASF Stroitelnye sistemy"

Moscow: +7 495 225 6436

St. Petersburg: +7 812 332 0412

Kazan: +7 843 212 5506

Krasnodar: +7 861 202 2299

Kiev: BASF T.O.V. +380 44 5915595

Minsk: +375 17 202 2471

E-mail: [stroysist@basf.com](mailto:stroysist@basf.com) [www.master-builders-solutions.basf.ru](http://www.master-builders-solutions.basf.ru)