

MasterEmaco[®] N 202

A single component cementitious blowhole filler and levelling mortar for cosmetic repairs, and surface levelling to new construction

COMPOSITION

MasterEmaco N 202 is a combination of Portland cement, well graded sands and special additives

When mixed with water **MasterEmaco N 202** produces a smooth cementitious paste ideally suited to filling of small surface defects, blowholes and surface levelling in thin layers of up to 3mm maximum.

TYPICAL APPLICATIONS

Surface leveling and blowhole filling for all concrete elements such as

- Beams, columns, and walls in high rise buildings
- Columns, Piers and cross beams on highway structures
- Cooling towers and chimneys and other industrial structures

BENEFITS

- Excellent workability for easy mixing, and fast application
- Improved bond to substrate
- Compatible with Masterseal protective coatings
- Concrete coloured when cured

PACKAGING

MasterEmaco N 202 is available in 25 kg bags

TECHNICAL DATA

Working time	60 mins @ 25°C
Setting time	90 mins @ 25°C
Density	Approx. 1850kg/m ³

APPLICATION GUIDELINES

SUBSTRATE PREPARATION

All areas to be treated must be clean, sound and free from all dirt dust, loose material and any oil or grease which would impair adhesion.

PRIMING OF THE SUBSTRATE

The substrate should be thoroughly soaked, to a saturated but surface dry condition prior to application of the **MasterEmaco N 202**.

MIXING

It is recommended that only full bags of 25 kg are mixed.

MasterEmaco N 202 should be mixed by mechanical means with a slow speed drill and spiral paddle.

The required amount of gauging water should be placed in the mixing bucket and the **MasterEmaco N 202** powder added and mixed for approximately 3 minutes until a smooth, creamy and lump free consistency is achieved.

The water additions shall be a maximum of 7 litres per 25kg bag

APPLICATION

Following mixing the **MasterEmaco N 202** can be applied by brush or the edge of a steel float and scraped into substrate to fill all blowholes and minor surface defects. A fine mist spray of clean water should be applied to the finished surface. The hardened **MasterEmaco N 202** can then be smoothed using sandpaper.

Alternatively **MasterEmaco N 202** can be applied as a leveling mortar by steel float up to 3 mm thick. The final finishing shall be by steel float or with a damp sponge depending upon the finish required. **MasterEmaco N 202** can be overcoated 24 hours after application.

CURING

Generally curing is not necessary for cosmetic repair mortars however particular care is required in hot and/or windy conditions. Where a curing membrane is specified this can be using a curing membrane from the **MasterKure** range

MasterEmaco[®] N 202

YIELD / COVERAGE

A 25kg bag of **MasterEmaco N 202** will yield approximately 17.3 litres of mortar.
One bag of **MasterEmaco N 202** will cover 17.3 m² at thickness of 1mm. This coverage is theoretical and depends upon the surface profile of the substrate and the wastage.

STORAGE

MasterEmaco N 202 should be stored in dry conditions out of direct sunlight. Shelf life when stored correctly is 12 months.

WATCHPOINTS

During the summer months or where elevated ambient temperatures are encountered the **MasterEmaco N 202** should be mixed using chilled water to ensure that the mixed temperature does not exceed 32°C.
Do not add cement sand, or which may affect its properties.
Do not add water or fresh mortar to material which has begun to set.

SAFETY PRECAUTIONS

Avoid contact with eyes and prolonged contact with skin. In case of contact with eyes immediately flush for at least 15 minutes with fresh clean water. Call a physician.
In case of contact with skin wash skin thoroughly.

QUALITY AND CARE

All products originating from the BASF facility in Dubai are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards ISO 9001, ISO 14001 and OHSAS 18001.

NOTE

Similar to all the other recommendations and technical information, this technical data sheet serves only as a description of the product characteristics, mode of use and applications.

The data and information given are based on our technical knowledge obtained in the bibliography, laboratory tests and in practice. The data on consumption and dosage contained in this data sheet are based on our own experience and are therefore subject to variations due to different work conditions.

BASF reserves the right to modify the composition of the products provided these continue to comply with the characteristics described in the data sheet. In the case of defects in the manufacturing quality of our products we provide a guarantee, any additional claims being exempt and our liability being only to return the value of the goods supplied. The possible reservations with respect to patents or third party rights should be noted.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/Em_N202_10_06/v1/11_13_Ksa 07/2014rev_04-2017

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.