

# MasterEmaco<sup>®</sup> N 907

Two component polymer modified fairing coat and re-profiling mortar

## DESCRIPTION

**MasterEmaco N 907** is a two component acrylic modified blow hole filler and reprofiling mortar. It can be applied between 0 to 10mm.

**MasterEmaco N 907** can be used as a skim coat prior to application of protective coatings.

**MasterEmaco N 907** is specially formulated to produce a shrinkage compensated mortar with no cracking when applied in a thin section. Adhesion to concrete is excellent.

## PRIMARY USES

- As a fairing or skim coat to cover and make good blemishes in concrete surfaces such as slight honeycombing, blowholes, sand runs, grout loss and shutter movement.
- Preparatory treatment to concrete to receive a thin film protective coating.
- To produce a uniform surface over repair areas

## ADVANTAGES

- Precision made, consistent results.
- Pre-gauged liquid, no mixing water.
- Shrinkage compensated.
- Excellent adhesion to concrete.
- Flexible.
- Smooth, easy to finish.
- Low permeability.
- Excellent resistance to freeze/thaw and action and carbonation.
- Reduced ingress of water borne salts.
- Greater economy of applied coatings

## COMPOSITION

**MasterEmaco N 907** is a specially formulated blend of Portland cements, selected aggregates and liquid acrylic in a plastic container. The pre-packed components only require on-site mixing to produce a creamy, easily applied mortar.

## TYPICAL PROPERTIES

Colour	Light grey
Plastic density	1756kg/m <sup>3</sup>
Working life at 25°C	Approx. 45 mins
Working life at 30°C	Approx. 30 mins

## PACKAGING

Powder Component: 16.66 kg Bag  
Liquid Component: 5 kg bottle  
Total: 21.66kg or 12 litre packs

## APPLICATION PROCEDURE

### SURFACE PREPARATION:

Surfaces to receive **MasterEmaco N 907** should be sound, clean and uncontaminated. The surface should be mechanically prepared to remove laitance. The surface should not be contaminated with oil, grease or paint.

### SURFACE CONDITION

Surfaces should be thoroughly soaked prior to application. Excess water should be removed prior to application of **MasterEmaco N 907**.

### DEEP VOIDS:

Deep voids should be filled with the correct product from the **MasterEmaco** range

### MIXING

**MasterEmaco N 907** is formulated to produce an easily mixed mortar. A slow speed drill & paddle can be used or a forced action mixer. Add powder to liquid at a steady rate. Mix for approx 4 minutes. Part mixing can be done provided the ratio of 3.5:1 is observed.

# MasterEmaco<sup>®</sup> N 907

## APPLICATION:

**MasterEmaco N 907** is applied by steel trowel. The finishing should be carried out with the minimum trowelling. A small amount of water can be applied to the surface to aid finishing. Leave the applied material for a short time before applying a final trowel.

## CURING:

Curing is generally not required however during hot, dry and windy conditions the surfaces should be covered to prevent rapid drying. Alternatively the applied material can be cured with **MasterKure 181**. This product is compatible with most subsequent coatings.

Note: In addition to shrinkage compensation, this product has been designed to develop tensile strength sufficient to withstand the internal stress generated by volume change to reduce the incidence of drying shrinkage cracking.

## EQUIPMENT CARE

Tools should be washed with water immediately after use.

## COVERAGE

One unit of mixed **MasterEmaco N 907** will typically yield 12 litres of mortar.

## SPECIFICATION CLAUSE

All slight surface imperfections should be made good by the application of **MasterEmaco N 907** as manufactured by BASF. Applications should be strictly in accordance with the manufacturer's instructions.

## STORAGE

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction. Shelf life is 6 months when stored as above.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All BASF Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and BASF ESHQ recommendations..

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF\_CC-UAE/Em\_N907\_11\_04/v1/11\_13

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.