

# MasterSeal® 610

High solids protective coating and curing membrane based on emulsified bitumen

## DESCRIPTION

**MasterSeal 610** is a non fibrated water based bitumen emulsion. It is dark brown in colour and dries to a black flexible protective coating which also acts as a curing compound. The finished film is tough and waterproof and forms a barrier to water and vapour transmission.

## TYPICAL APPLICATIONS

- General waterproofing and damp proofing of concrete, asbestos cement, roofing felt, slate tiles, wood, etc.
- Metal protection: provides protection for structural steelwork, pipes, etc.
- Insulation: provides a vapour barrier for cold storage rooms, etc.
- Protection to a variety of buried structures such as concrete foundations and retaining walls.
- As a curing compound onto green concrete.
- As a primer for most bitumen membranes.

## ADVANTAGES

- Chemical resistance.
- Versatile.
- Economical
- Easy to apply.
- Cold applied.

## PACKAGING

**MasterSeal 610** is available in 200 litre drums.

## COMPOSITION

A blend of selected asphalts and bitumens emulsified in water.

## APPLICATION PROCEDURE

### SURFACE PREPARATION:

Ensure surface to be treated is sound and free of all oil, grease or conventional curing compounds. **MasterSeal 610** can be applied directly as a protection to concrete surfaces cured utilising non-degradable curing compounds such as **MasterKure 181**.

If the surface is dusty it should be primed with a coat of **MasterSeal 610** diluted with an equal quantity of clean water and allowed to dry, before

applying further coats of **MasterSeal 610**. **MasterSeal 610** can be applied to damp surfaces. although both coating and surface must be allowed to dry before the **MasterSeal 610** will cure to form a waterproof film.

## TYPICAL PROPERTIES

Flashpoint:	Non flammable
Specific gravity:	1.00 @ 25°C
Application temperature:	5°C to 50°C
Service temperature:	-10°C to 85°C (depending on operating conditions)
Chemical resistance:	Excellent to water, dilute acids, alkalis, chloride and sulphate ions
Flexibility:	Provides a firm flexible coating

## STANDARDS

ACI 515 IR-79. Guide to use of waterproofing, damp proofing, protecting and decorative barrier systems for concrete. Chapter 2 Section 2.1.1, 2.1.2., 2.1.3.

## PERFORMANCE

- **MasterSeal 610** will act as a curing compound when applied to green concrete. Apply immediately when formwork is removed.
- Will act as a primer for most bitumen based membranes.
- Concrete coated with **MasterSeal 610** will prevent the absorption of saline solutions. On uncoated surfaces, salts in groundwater will penetrate and can cause reinforcement corrosion and concrete deterioration.

# MasterSeal<sup>®</sup> 610

## APPLICATIONS

**Agitate before use. As settlement can occur, the drum should be rolled before decanting material.**

Apply by brush, broom or squeegee. Apply one or two coats, depending on the degree of protection required. Apply subsequent coats at right angles to the first, allowing 12 to 24 hours between coats. Where being utilised to damp proof solid floors or where a screed is to be applied over **MasterSeal 610**, apply a second coat at right angles and lightly grit to form a key. Allow at least 24 hours before application of concrete screed, ensuring this is greater than 60mm in thickness.

## COVERAGE

2-4 m<sup>2</sup> per litre per coat depending on use and substrate porosity.

## EQUIPMENT CARE

After use, if the **MasterSeal 610** has not dried, it may be possible to clean tools using soapy water. If the **MasterSeal 610** has dried remove as much as possible by physically scraping and then remove remainder with paraffin, white spirit or **MasterTop Thinner No. 2**.

## STORAGE

Store under cover, out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment. As with all bituminous emulsions, some settlement will occur with prolonged storage. It is, therefore, necessary to invert the drums monthly to disperse the settlement.

Shelf life is up to 6 month in unopened containers, when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

## SAFETY PRECAUTIONS

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation. For further information refer to the material safety data sheet.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All BASF Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and BASF ESHQ recommendations.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF\_Saudi\_12\_2009\_09\_2014\_06/18

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.