

# MasterSeal<sup>®</sup> 703RE

Synthetic membrane of plasticised PVC

## DESCRIPTION

**MasterSeal 703RE** is a synthetic membrane made by the co-extrusion process. Made of plastisol layers, with different chemical & physical properties and has a layer of glass fibre inserted, for dimensional stability.

## TYPICAL APPLICATIONS

**MasterSeal 703RE** can be applied in the following circumstances:

- Upstands and exposed areas in conjunction with membranes needing protection
- Covered and inverted Roof Structures
- Landscaped areas and Roof Gardens
- Underground Structures

## ADVANTAGES

- It has superior mechanical characteristics and is resistant to weathering and ultra violet rays
- High mechanical properties and resistance to puncturing
- Rot-proof
- Vapour permeable
- Resistance to root penetration
- If double welded it allows pressure testing of joints
- Good resistance to hydrocarbons and bacterial attack
- Long life expectancy

## PACKAGING AND ROLL SIZES

**MasterSeal 703RE** is supplied in various thicknesses with 1.60 and 2.10 meter width and in lengths of 20 meters.

Thickness (mm)	1.2	1.5	1.8	2.0	2.4
Width (m)	1.60	1.60	1.60	1.60	1.60
Width (m)	2.10	2.10	2.10	2.10	2.10
Length (m)	20	20	20	20	20
Colour	Light grey				

## APPLICATION PROCEDURE

Usually applied by Specialist Applicator. Please contact BASF Construction Chemicals for specific application assistance.

## WATERTIGHT SYSTEMS & ENGINEERED SOLUTIONS

BASF Construction Chemicals provide systems and engineered solutions, to suit the structure, at the design and construction stages, to ensure watertightness. Various products and elements which form an integral part of a system are manufactured and approved by BASF. The following ranges of products are available;

- **MasterSeal** range - Active and passive joint treatment and preformed membranes
- **MasterSeal** range - Liquid applied membranes and protective coatings
- **MasterFlow** range - High performance grouts
- **MasterEmaco** and **MasterBrace** ranges - Repair materials

## STORAGE

Store out of direct sunlight, clear of the ground and on pallets.

# MasterSeal® 703RE

## PHYSICAL/CHEMICAL PROPERTIES\*

Thickness UNI EN 1849 - 2	1.2mm	1.5mm	1.8mm	2.0mm	2.4mm
Specific weight (kg/m <sup>2</sup> ) UNI EN 1849 - 2	1.50	1.80	2.15	2.40	2.90
Tensile strength UNI EN 12311 - 2	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>	≥ 9.0 N/mm <sup>2</sup>
Elongation to break UNI EN 12311 - 2	≥ 200%	≥ 200%	≥ 200%	≥ 200%	≥ 200%
Tear resistance UNI EN 12310 - 2	≥ 110N	≥ 135N	≥ 160N	≥ 170N	≥ 200N
Puncture resistance DIN 16726 - 5.12	≥ 450mm	≥ 800mm	≥ 900mm	≥ 1000mm	≥ 1500mm
Cold bending UNI EN 495 - 5	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C
Hydrostatic pressure resistance (6 hours at 5 bar) UNI EN 1928 meth. B	waterproof	waterproof	waterproof	waterproof	waterproof
Dimensional stability after 6 hours at 80°C – UNI EN 1107 - 2	≤ ± 0.1%	≤ ± 0.1%	≤ ± 0.1%	≤ ± 0.1%	≤ ± 0.1%
Resistance to artificial weathering UNI EN 1297	no cracking	no cracking	no cracking	no cracking	no cracking
Root resistance DIN 4062	No penetration	No penetration	No penetration	No penetration	No penetration
Resistance to hail on rigid substrate NI EN 13583	≥ 25 m/s	≥ 25 m/s	≥ 25 m/s	≥ 25 m/s	≥ 25 m/s
Thermal ageing in air after 168 d at 70°C Cold bending UNI EN 1296	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C	≤ - 25°C
Peel resistance of joints UNI EN 12316 - 2	≥ 150 N/50 mm	≥ 150 N/50 mm	≥ 150 N/50 mm	≥ 150 N/50 mm	≥ 150 N/50 mm
Shear resistance of joints UNI EN 12317 - 2	Breaking out of joint	Breaking out of joint	Breaking out of joint	Breaking out of joint	Breaking out of joint
Resistance to impact UNI EN 12691	20 mm	20 mm	10 mm	10 mm	10 mm
Resistance to static punching UNI EN 12316	≥ 20 kg	≥ 20 kg	≥ 20 kg	≥ 20 kg	≥ 20 kg

### NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

### QUALITY AND CARE

All BASF Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and BASF ESHQ recommendations.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

## BASF\_CC-UAE/SI\_703RE\_10\_07/v2/12\_14

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.