

MasterTop[®] 100

Dry shake floor hardener

DESCRIPTION

MasterTop 100 is a pre-mixed, dry-shake surface hardener and has properties, which contains hydraulic binder and specially graded mineral aggregates.

TYPICAL APPLICATIONS

- Aircraft hangars.
- Basements and cellars.
- Mechanical workshops.
- Garage for light vehicles.
- Storage rooms.
- Corridors and halls.
- Parking areas.
- Loading platforms.

LIMITATIONS

- Not for use where operating and service conditions dictate the use of a metallic-aggregate surface hardener for greater abrasion and impact resistance.
- Not for use in areas exposed to acids and their salts or to materials known to rapidly attack or deteriorate Portland cement concrete.

PACKAGING

MasterTop 100 is packed in 25kg moisture-resistant bags.

TYPICAL PROPERTIES*

Hardness (Aggregate)	7 (Mohs scale of hardness)
Average rate of abrasion (Dorry Abrasion Machine)	0.24 gms/min
Curing:	Required

TYPICAL COMPARATIVE WEAT TESTS RESULTS

DEPTH OF WEAR (THICKNESS LOSS) (MM):

Sample reference	Control average	MasterTop 100 average
5 minutes	0.33	0.20
10 minutes	0.61	0.30
15 minutes	0.77	0.42
20 minutes	0.95	0.50
25 minutes	1.15	0.61
30 minutes	1.34	0.71
35 minutes	1.55	0.81

WEIGHT LOSS (GM):

5 minutes	2.87	2.4
10 minutes	5.3	3.8
15 minutes	7.5	5.0
20 minutes	9.7	6.1
25 minutes	11.9	7.3
30 minutes	14.0	8.4
35 minutes	16.1	9.7

Tests results show that **MasterTop 100** significantly reduces the depth of wear. Tests were undertaken using a Dorry Abrasion Machine.

APPLICATION PROCEDURE

Single Course Monolithic Floors:

THE CONCRETE:

Use a placeable and finishable concrete mix of the required mix design with a minimum slump of 75mm and no more than 3% entrained air.

In accordance with ACI 201 - 2R77 & ACI 302-1 R-89 a well proportioned Concrete Mix Design is essential. The concrete supplier should ensure that cement contents, w:c ratios, slumps are generally in accordance with the following minimum standard:

MasterTop[®] 100

Cement (White OPC): Min 350 kg/m³

W:C ratio: Max. 0.50

Min. 0.40

Slump: Ideally 75mm

Strength: Min 31 N/mm²

Concrete should not segregate and bleed or contain more than 3% air. Do not use microsilica in the concrete as this can lead to problems with crusting when the dry shake is applied.

MasterRheobuild or **MasterPozzolith** water reducing admixtures are recommended for concrete placement and optimum performance. Screeds to which **MasterTop 100** is to be applied, should have a minimum thickness of 75mm. Following placement, concrete should be levelled off with a straightedge and then vibrated. The surface is then floated with a wooden float ensuring that it is not closed. Any bleed water should be removed. (Avoid sponge type absorbents). Thereafter sprinkle **MasterTop 100** along edges of bays (approx. 80mm strips) where expansion and construction joints will be located. Float into surface using a wooden float.

MasterTop 100 is ideally applied to a surface which is neither too wet nor too dry. Ambient temperatures will dictate when the material is to be applied. Generally in temperatures of 35-45°C a waiting period of 30-40 mins is recommended. This may need to be extended in temperatures of less than 35°C.

Using a raised trestle which spans the slab, the material is broadcast by hand onto the wet concrete surface. The application is carried out in two stages.

1. Apply two thirds of the required material to the concrete ensuring uniform distribution.
2. Allow applied material to absorb moisture from the concrete surface; a uniform darker colour will be apparent.
3. Using a wooden float, work **MasterTop 100** into the concrete ensuring material becomes an integral part of the surface.

4. Apply the balance of material. Again wait until material has obtained a darker colour before floating with a wooden float.
5. When surface is sufficiently firm enough to take the weight of a man leaving only minor indentations, **MasterTop 100** should be finished off by means of a power trowel. A smooth slip resistant finish can be obtained, but the surface should not be overworked.
6. If manual finishing with steel trowels is to be undertaken, this should take place before concrete becomes firm enough to take foot traffic.

NOTES:

- For heavy-duty traffic areas, concrete with a minimum strength of 30N/mm² should be used at 28 days. Thickness of the slab and the type and amount of reinforcement are important design considerations.
- To minimise shrinkage cracking, consider the use of BASF water-reducing admixtures.
- Do not use calcium chloride in concrete over which shakes containing metallic aggregate and/or colouring pigments will be applied.
- At temperatures over 29°C, at low humidity or when placing concrete without protection from wind or sun, erect sunshades or windbreaks the use of **MasterKure** curing products is essential.
- Do not use salt water or salt contaminated aggregate in concrete over which shakes containing metallic aggregate or colour will be applied.

APPLICATION RATE:

MasterTop 100 shall be applied at the following rates:

Heavy duty	8-9kg/m ²
Medium duty	6-8kg/m ²
Light duty	4-6kg/m ²

MasterTop[®] 100

CURING:

As soon the surface will not be marred by the application, apply the recommended curing compound for the type of surface and floor use involved:

See separate product selection guide for curing compounds.

FOR PROTECTION:

The area should be barricaded off after the curing compound is applied. As soon as the curing compound has dried, adequately cover the floor surface to prevent staining, discoloration or physical damage which may be difficult to correct. Alert other trades to the need for special protection against rolling or sliding heavy loads across the surface, oil drippings from pipe threaders, spillage of paint, plaster and mortar, acid washing of interior masonry walls, etc. Ensure that the covering is not damaged during the progress of the job.

CLEANING:

Clean with water as soon as the equipment is no longer used and before the cementitious material starts to harden on the blades, trowels, etc.

SAWING JOINTS:

Saw the joints as soon as possible, without damaging the concrete.

STORAGE

Store out of direct sunlight, clear of the ground on pallets protected from rainfall. Avoid excessive compaction. Shelf life is 12 months in the tightly closed original packages stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

SAFETY PRECAUTIONS

- Do not apply over concrete containing calcium chloride or aggregate contaminated with salt or saltwater.
- Do not apply over concrete containing microsilica. Do not apply over concrete containing more than 3% entrained air.
- This product contains cement which may cause irritation. Avoid contact with eyes and prolonged contact with skin. If contact occurs wash thoroughly with water and call a doctor. Keep product out of reach of children.

For further information refer to the material safety data sheet.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All BASF Products are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health and safety standards of ISO 9001 and BASF ESHQ recommendations.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF_CC-UAE/Top_100_06_94/v1/11_13

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.