



We create chemistry

# MasterEmaco<sup>®</sup> A 265

(Formerly known as Albaria<sup>®</sup> Calce Albazzana)

## Natural Hydraulic Lime

### Description of Product

MasterEmaco<sup>®</sup> A 265 is cement-free, natural hydraulic lime burnt at low temperatures (900°C) for lime mortar production.

### Fields of Application

MasterEmaco<sup>®</sup> A 265 is used in following cases as binder of lime mortar;

- Plastering production
- Building of masonry walls
- Building of masonry and natural stone joints

### Features and Benefits

- Cement free
- Burnt with traditional methods at low temperatures
- Can be used in production of different lime mortars compatible with existing building materials
- Does not affect the vapour and moisture permeability of the existing building

### Application Procedure

#### Preparation of Substrate

The surfaces should be free of frost, curing membranes, waterproofing treatments, oil stains, laitance, friable material and dust. The surfaces should be wetted before application. If there is a water leakage it must be drained or properly plugged.

#### Mixing

The work instructions of the restoration project should be followed.

#### Application Method

Fresh mortar should be applied to the prepared surface by using a trowel as mentioned application thickness in instructions. After the mortar finishes its first setting, some water should be sprayed onto the mortar and the surface should be finished with using steel or wooden trowel. For thicker applications first layer should

### Technical Data

Product Chemistry	Natural Hydraulic Lime
Color	Light Brown
Application Temperature	+5°C - +40°C



We create chemistry

# MasterEmaco® A 265

(Formerly known as Albaria® Calce Albazzana)

be wetted after it hardens. Then the new layer application can be done.

Open areas should be protected from the rain, wind, etc. aggressive whether conditions during the first 24-48 hours after finishing repair by using wet clothes, curing membranes etc.

## Coverage

Depends on the mix design of lime mortar.

## Watch Points

- During the application the substrate and environment temperature should be between 5°C-40°C.
- For full curing of material, both the substrate and environment temperature shouldn't be under allowed application temperature.
- Open areas should be protected from the rain, wind, etc. aggressive whether conditions during the first 24-48 hours after finishing application.

## Cleaning

After the application all tools should be cleaned with water. **MasterEmaco® A 265** can be cleaned with only mechanical abrasion after hardening.

## Packaging

25 kg bag

## Storage

Store in original container in cool (+5°C-+35°C) and dry indoor conditions.

## Shelf life

12 months under proper storage conditions after production date.

## Health and Safety Precautions

It is dangerous to get close to the store areas with fire. The store must be well ventilated.

Work clothes, protective gloves, glasses and mask defined in Labour Laws must be used during the application. Avoid from material to contact with skin and eyes. In case of contacting wash your skin with water and go to doctor immediately.

Don't bring any food and drink to the application area. Store the material away from the children. For further information Material Safety Data Sheets should be read.

## Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **BASF Türk Kimya Sanayi ve Tic. Ltd. Şti.** is only responsible for the quality of the product. **BASF Türk Kimya Sanayi ve Tic. Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones (01/2015).