



We create chemistry

MasterRoc® SA 189 (Formerly known as Meyco® SA 189)

Alkali-Free, Liquid High Performance Set Accelerator for Sprayed Concrete

DESCRIPTION OF PRODUCT

MasterRoc® SA 189 is a high performance alkali-free set accelerator for sprayed concrete, whose dosage can be adapted to the desired setting and hardening times.

FIELDS OF APPLICATION

- Temporary and permanent ground support in tunnelling and mining
- Slope stabilization
- Also suitable for acceleration of cementitious grouts, such as for annulus grout in TBM tunnels, cemented ground injection and foam concrete

FEATURES AND BENEFITS

MasterRoc® SA 189 is ideally suited to wet mix sprayed concrete for ground support:

- The quick setting property allows rapid work progress and the ability to construct

- thick sprayed concrete linings via layered application during one construction sequence.
- The unique product formulation provides fast setting, continuous early-age strength development, high durability and good long term strength.
- Very low dust generation during application, and therefore a good working environment.
- Possibility of low rebound application when using the correct nozzle angle and distance.
- Non-aggressive properties provide improved working safety reduced environmental impact and lower handling costs.

APPLICATION PROCEDURE

The substrate should be clean and free from loose particles, and preferably damp from pre-wetting.

It is recommended to use only fresh cement as the age of the cement can influence the setting characteristics of the mix.

MasterRoc® SA 189 has a low sensitivity to the type of cement. Though, with some cements,

TECHNICAL DATA

Form	Suspension
Colour	Beige to White
Density (+20°C)	1.52 ± 0.02 g/ml
pH Value	3.0 ± 0.5
Viscosity ¹⁾	600 ± 250 mPa.s
Thermal Stability	+5°C to +35°C
Chloride Content	< 0.1%
[Na ₂ O] EQV. (%bw)	< 1%

¹⁾ Brookfield, + 20 °C. Viscosity is dependent on degree of product agitation and temperature.





We create chemistry

MasterRoc® SA 189 (Formerly known as Meyco® SA 189)

Alkali-Free, Liquid High Performance Set Accelerator for Sprayed Concrete

increased dosages of **MasterRoc® SA 189** are necessary for a fast setting. We recommended the use of Portland cements (PC/HPC), which often give faster setting than blended or sulphate resistant cement types. However, **MasterRoc® SA 189** also works well with composite cement types (blended cements, fly-ash/slag). In all cases, it is strongly recommended to carry out preliminary tests to check setting times and the 24 h strength of the cements planned for use in a project.

Evaluation of setting and 24 h strength should be carried out on a test mortar in accordance with EFNARC European Specification for Sprayed Concrete (1996), Appendix 1, Clause 6.3.

The following results should be taken as a performance guide only:

Initial set	Final set	24 h strength	Rating
2 min.	6-8 min.	18-20 MPa	good
5 min.	8-12 min.	12-15 MPa	OK
>10 min	>15 min.	<10 MPa	poor

Concrete Mix

When **MasterRoc® SA 189** is used for wet mix spraying, the w/c+b ratio should be below 0.5 and preferably <0.45. When targeting extremely high early strength 0.40 or lower. The lower w/c+b ratios provide faster setting, higher early strength, improved durability, lower accelerator dosage and thicker layers can be applied overhead.

PACKAGING

MasterRoc® SA 189 is supplied in 1500 kg containers or in bulk.

DOSING SYSTEM

MasterRoc® SA 189 is added in the nozzle. It is essential to have a constant and accurate dosage of accelerator into the concrete stream. In order to ensure quality sprayed concrete, follow the pump selection guidelines given below:

Works very well with:

- Mono pumps (stator & rotor pumps)
- Peristaltic pumps (Bredel)

Should not to be used with:

- Piston pumps
- All pumps with ball and seat valves
- Pressure tanks
- Gear pumps

Do not use a filter on the suction hose as this causes obstructions. Preferably draw the material off the bottom of the drum/container.

Compatibility with Other Accelerators

MasterRoc® SA 189 can be interchanged with most of **BASF's** alkali-free accelerators. For advice please contact your local **BASF** representative.

Do not mix or interchange **MasterRoc® SA 189** with any type of accelerator produced by another manufacturer, as this could cause immediate clogging of dosing pumps and hoses.

CONSUMPTION

The consumption of **MasterRoc® SA 189** also depends on the w/c+b ratio, temperature conditions (concrete and ambient), cement reactivity and on required layer thickness, setting



We create chemistry

MasterRoc® SA 189 (Formerly known as Meyco® SA 189)

Alkali-Free, Liquid High Performance Set Accelerator for Sprayed Concrete

time and early strength development. The consumption of **MasterRoc® SA 189** is normally in the range of 3 to 10% of binder weight. Overdosing (>10 %) may result in decreased final strengths.

CLEANING OF DOSING PUMP

After the use of **MasterRoc® SA 189**, the dosing accelerator dosing pump and other parts of the system must be thoroughly cleaned with plenty of water. Failure to do so provokes blockages in the dosing system. Make sure that all operators involved in testing and application are fully informed.

STORAGE

- Must be stored at minimum +5°C and maximum +35°C (optimum temperature for storage and performance +20°C).
- Has to be kept in closed containers made of plastic, glass fiber or stainless steel.
- Must not be stored in normal steel containers.
- Storage in bulk storage tanks requires the use of agitation and/or circulation systems.
- After prolonged storage or transport we recommend to fully agitate prior to use by mechanical stirring or re-circulation pumping.
- If stored in tightly closed original containers under the above given conditions, it has a shelf life of 6 months. Periodical remixing can extend the shelf life further.
- Please contact your local **BASF** representative prior to the use of any product that has been frozen.
- After prolonged storage, performance testing should always be carried out before use.

SAFETY PRECAUTIONS

The same precautions as with handling and use of cementitious products should be observed.

Avoid eye and skin contact and wear rubber gloves and safety glasses. If contact occurs, rinse with plenty of water. In case of eye contact seek medical advice. For further information, refer to the Material Safety Data Sheet or contact your local **BASF** representative.

DISCLAIMER

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **BASF Türk Kimya Sanayi ve Tic. Ltd. Şti.** is only responsible for the quality of the product. **BASF Türk Kimya Sanayi ve Tic. Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.

Contact Information

BASF Türk Kimya San. ve Tic. Ltd. Şti.

Yapı Kimyasalları Bölümü

Tel: 0216 570 34 00

Fax: 0216 570 37 79

Mail: info@master-builders-solutions-turkey.com

www.master-builders-solutions.basf.com.tr

® = Registered trademark of the BASF-Group in many countries of the world

MasterRoc SA 189 Technical Data Sheet - Issue Date: 02/2016