

# MasterPozzolith<sup>®</sup> RMC 10

## Low dosage retarding and plasticising admixture for concrete

### DESCRIPTION

**MasterPozzolith RMC 10** is a liquid admixture which acts on the cement particles in the mix, combining the effects of a powerful plasticiser and deflocculating agent with controlled retardation.

### ADVANTAGES

- Considerably extends vibration limit of concrete mixes thus reducing incidence of honeycombing and cold joints.
- Reduces placing problems in hot weather concreting by improving workability and workability retention.
- Improves trowellability and surface finish.
- Improves pumpability of concrete.
- Considerably reduces permeability.
- Enables economies in mix designs to be achieved.

### PACKAGING

**MasterPozzolith RMC 10** is available in bulk or in 210 litre drums.

### TYPICAL PROPERTIES\*

Colour	Dark brown liquid
Specific gravity	1.168 @ 25°C
Chloride content	"chloride free" to EN 934
Freezing point	0°C

### STANDARDS

EN 934-2 Table 10  
ASTM C-494: Types A, B, & D  
BS 5075: Part 1 (superseded by EN 934-2)

### DIRECTIONS FOR USE

**MasterPozzolith RMC 10** should be added to the concrete mix during the mixing cycle at the same time as the water or the aggregate. Never add **MasterPozzolith RMC 10** to the dry cement. No extension to normal mixing times is necessary.

### DOSAGE

In all cases we recommend trial mixes are carried out to determine the correct levels of admixture required to achieve the desired concrete properties. The following figures should be utilised as a starting point for these trials. For site batched concrete where extended vibration time and improved finishing properties are of prime importance, a dosage of between 160 and 280ml per 100kg of cement should be used as a starting point for the trials. For ready mixed concrete, extended concrete workability is of prime importance, a dosage of between 280 to 420ml per 100kg of cement should be used as a starting point.

Dependent on the desired properties, a dosage of up to 700ml per 100kg of cement may be utilised. Higher dosages may be required when certain combinations of materials and conditions are present.

### SETTING TIME

**MasterPozzolith RMC 10** acts efficiently to give controlled retardation of initial set. Setting times of concrete mixes are related to cement type and ambient temperatures.

### COMPATIBILITY

**MasterPozzolith RMC 10** can be used with all types of Portland cement including Sulphate Resisting compatible with cementitious materials such as silica fume, fly ash and GGBS. For use with other special cements, contact BASF Technical Services Department.

**MasterPozzolith RMC 10** should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing **MasterPozzolith RMC 10**, they must be dispensed separately. Consult BASF Technical Services Department for advice.

# MasterPozzolith® RMC 10

## EFFECTS OF OVER DOSAGE

A severe over dosage of **MasterPozzolith RMC 10** will result in the following:

- Retardation of initial and final set.
- Slight increase in air entrainment.
- Increase in workability.

Providing it is properly cured, the ultimate strength of the concrete will not be adversely affected and will generally be higher than for normal concrete. The retarding effects of very high dosages will be exaggerated with SR cement.

## DISPENSING

**MasterPozzolith RMC 10** should be dispensed through a proprietary dispenser, such as is available from BASF.

## SAFETY PRECAUTIONS

**MasterPozzolith RMC 10** is not a fire or health hazard. Spillages should be washed down immediately with cold water. For further information refer to the material safety data sheet.

## STORAGE & SHELF LIFE

**MasterPozzolith RMC 10** should be stored in closed containers or bulk tanks to protect from extremes of temperature.

Shelf life is up to 2 years when stored as above.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from BASF's Dubai, UAE facility are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

BASF\_CC-UAE/PI\_RMC10\_03\_94/v2/06\_16

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.