

3

03 01 30
Maintenance of Cast-
In-Place Concrete

MasterBrace® 6063UW

Marine epoxy paste for use with the Advanced Pile Encapsulation System

FORMERLY HYDROCOTE 1063

YIELD

- 1/8 in (3.2 mm)
25.6 ft²/2 gal unit (1.18 m²/L)
- 1/4 in (6.4 mm)
12.8 ft²/2 gal unit (0.60 m²/L)
- 1/2 in (3.2 mm)
6.4 ft²/2 gal. unit (0.30 m²/L)

PACKAGING

MasterBrace 6063UW marine epoxy paste is packaged in 2 gal (7.6 L) units.

COLOR

White

SHELF LIFE

18 months when properly stored

STORAGE

Store in unopened containers in a clean, dry area between 50 and 90° F (10 to 32° C) away from direct sunlight, flame, or other hazards.

DESCRIPTION

MasterBrace 6063UW is a two component, nonsag, marine epoxy paste that can be applied to horizontal, vertical and overhead surfaces, above and below the waterline, and in the presence of wave action.

PRODUCT HIGHLIGHTS

- Heavy consistency and rapid set Resists wave action during and after cure
- Marine grade adhesive Will adhere to wood, concrete or steel, above or below water line
- Excellent handling Can be glove applied in thicknesses up to 1 inch (25 mm) in a single application
- Suitable for low-temperature application Cures down to 40° F (4° C)

HOW TO APPLY

SURFACE PREPARATION

Concrete Surfaces

1. New concrete must be fully cured (28 days minimum) before application of MasterBrace 6063UW material.
2. The substrate must be clean and sound. Remove all marine growth, paint, grease, oil or other contaminants by an anchor profile, if possible.

Steel Surfaces

3. Steel surfaces must be cleaned to meet SSPCSP6-63, "No. 6 Commercial Blast Cleaning."

Wood Surfaces

1. Remove all marine growth, paint, grease, oil and other contaminants by sandblasting, waterblasting or rotary abrading. Remove unsound wood.

APPLICATIONS

- Piers
- Bridges
- Offshore structures
- Dams
- Sea walls
- Horizontal
- Vertical
- Overhead
- Underwater
- Primarily used with in conjunction with MasterBrace encapsulation systems
- Can also be used for:
 - Patching spalls in concrete
 - Filling cavities
 - Sealing surfaces for crack injection

SUBSTRATES

- Concrete
- Steel
- Timber

TECHNICAL DATA

COMPOSITION

XXXXXX

PHYSICAL PROPERTIES

PROPERTY	REQUIREMENT
Mix Ratio, by volume	1:1
Form	Thick Paste
Color	Component A White, Component B Black, Mixed Grey
Pot Life	100 min @ 77 ° F (25 ° C)
Cure Times @ 77 ° F (25 ° C)	Initial Cure 5 to 6 hours Full Cure 7 days
Compressive Strength	8000 psi (55.0 MPa) (ASTM 579) 7 days
Tensile Strength	3700 psi (25.5 MPa) (ASTM 638) 7 days
Water Absorption	0.5% maximum (ASTM C 413) 7 days
Tensile Bond Strength	270 psi (1.90 MPa) (ASTM D 4541) 7 days
Shear	2500 psi (17.2 MPa) (ASTM C 882) 7 days
Direct in-situ Bond, Underwater	50 psi (0.35 MPa) Modified Elcometer Method Minimum

NOTES:

The physical properties listed herein are typical and descriptive. Bond strengths are highly dependent on surface preparation and installation conditions. Pot life is temperature related. Cooler temperatures lengthen pot life.

PHYSICAL PROPERTIES

MIXING

1. Mix only the amount of paste that can be placed within the' specified pot life. (Higher temperatures shorten pot life).
2. Place equal parts of A and B on a flat disposable palette (i.e. sheet of cardboard) and mix with a flat bladed scraper or trowel.
3. Mix until all evidence of the original white and black colors has disappeared and a uniform grey color is achieved.
4. Once mixed, MasterBrace 6063UW material may be picked up and handled with gloved hands. Keep gloves thoroughly wet with water to prevent material from sticking to gloves.
5. Material may be rolled into balls or ropes for ease of application.

APPLICATION

1. When applied to surface underwater, it is necessary to "work" the paste on to the surface, using heavy hand pressure, being careful not to entrap water or air bubbles between the' paste and the surface.
2. Hold the paste against the surface for 10–15 seconds to obtain optimum adhesion. When used to cover cracks, work paste into one end of crack and progress along crack to other end, displacing water from the crack. Smooth outer surface of paste with gloved hand.

CLEAN UP

Mixed epoxy is much easier to clean up before it hardens. Solvents such as acetone, methyl ethyl ketone (MEK) and toluene may be used. Commercial epoxy strippers are recommended for hardened epoxy. Consult solvent manufacturer's usage recommendation.

FOR BEST PERFORMANCE

- Make certain the most current versions of product data sheet and SDS are being used; call Customer Service (1-800-433-9517) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and are not for supervising or providing quality control on the jobsite.

MASTERBRACE 6063UW

ANGER – CORROSIVE

Contains: polyamino amide, tetraethylene-pentamine, tris (2,4,6-dimethylaminomethyl) phenol, benzyl alcohol.

HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.basf.us, e-mailing your request to basfbscst@basf.com or calling 1(800)433-9517. Use only as directed. **For medical emergencies only, call ChemTrec® 1(800)424-9300.**

LIMITED WARRANTY NOTICE

Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS,** and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.** BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein

should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

BASF Corporation
Constructions Systems

889 Valley Park Drive, Shakopee, MN 55379
www.master-builders-solutions.basf.us

Customer Service 1(800)433.9517
Technical Service 1(800)243.6739

