

MasterBrace[®] SAT 4700

Low temperature cure epoxy encapsulation resin for the MasterBrace Composite Strengthening System

FORMERLY MBRACE[®] SATURANT LTC

YIELD

MasterBrace FIB 300/50 CFS Fabric

55 ft²/gal (1.3 m²/L)

MasterBrace FIB 600/50 CFS Fabric

45 ft²/gal (1.1 m²/L)

MasterBrace FIB 900/50 FG Fabric

35 ft²/gal (0.85 m²/L)

COVERAGE

Coverage rates are based on square footage (meters) of fabric. Contact a BASF representative for coverage rates for other fabric types.

PACKAGING

Available in 4 gal (15.2 L) units

COLOR

Part A – Blue

Part B – Clear

Mixed – Blue

SHELF LIFE

18 months when properly stored

STORAGE

Store in unopened containers in a clean, dry area between 50 and 90° F (10 to 32° C) away from direct sunlight, flame, or other hazards.

DESCRIPTION

MasterBrace SAT 4700 is a 100% solids, low viscosity epoxy material that is used to encapsulate MasterBrace carbon and glass fiber fabrics. Based on a unique amine curing agent technology, MasterBrace SAT 4700 is designed to cure at ambient temperatures as low as 40° F (5° C) and substrate temperatures as low as 32° F (0° C). When reinforced with MasterBrace fiber fabrics, the MasterBrace SAT 4700 cures to provide a high performance FRP laminate. The resulting FRP laminate can provide additional strength to concrete, masonry, steel, and wood structural elements.

PRODUCT HIGHLIGHTS

- Moderate viscosity Can be applied in vertical and overhead applications, but still adequately saturates MasterBrace fabrics
- 100% solids epoxy Low odor, low VOC's
- Suitable for low-temperature application can be applied if temperature is 40° F and rising; extends application window in cooler conditions

SUBSTRATE

- Concrete
- Masonry
- Steel

APPLICATIONS

- Used to encapsulate any MasterBrace fabric in low temperature environments
- Vertical
- Horizontal
- Exterior
- Interior

TECHNICAL DATA

COMPOSITION

Two component, 100% solids, amine cured epoxy

NOTES:

- (1) Based on testing of cured samples per ASTM D 638 at 72° F (20° C) and 40% relative humidity.
- (2) Based on testing of cured samples per ASTM D 695 at 72° F (20° C) and 40% relative humidity.
- (3) Based on testing of cured samples per ASTM D 790 at 72° F (20° C) and 40% relative humidity.
- (4) Based on testing of cured samples at 72° F (20° C) and 40% relative humidity.

PHYSICAL PROPERTIES

PROPERTY	VALUE
Density	61.3 pcf (983-kg/m ³)

TENSILE PROPERTIES (1)

PROPERTY	VALUE
Yield Strength	2100 psi (14 MPa)
Strain at Yield	1.3%
Elastic Modulus	165 ksi (1138 MPa)
Ultimate Strength	2100 psi (14 MPa)
Rupture Strain	5.3%
Poisson's Ratio	0.40

COMPRESSIVE PROPERTIES (2)

PROPERTY	VALUE
Yield Strength	5200 psi (36 MPa)
Strain at Yield	2.3%
Elastic Modulus	230 ksi (1586 MPa)
Ultimate Strength	5200 psi (36 MPa)
Rupture Strain	5%

FLEXURAL PROPERTIES (3)

PROPERTY	VALUE
Yield Strength	3600 psi (25 MPa)
Strain at Yield	4.5%
Elastic Modulus	80 ksi (552 MPa)
Ultimate Strength	3600 psi (25 MPa)
Rupture Strain	5%

FUNCTIONAL PROPERTIES (4)

PROPERTY	VALUE
CTE	20·10 ⁻⁶ /°F (35·10 ⁻⁶ /°C)
Thermal Conductivity	1.45 Btu·in/hr·ft ² ·°F (0.21 W/m·°K)
Glass Transition Temp, T_g	163 °F (71 °C)

HANDLING PROPERTIES

PROPERTY	VALUE
Mixed Weight	8.2 lb/gal (984 g/L)
VOC Content	25 g/L less water and exempt solvents (EPA Method 24)
Flash Point	Part A: 181 °F (83 °C) Part B: > 200 °F (93 °C) (Pensky-Martens Closed Cup)
Mixed Viscosity	at 50 °F (10 °C) 2400 cps at 77 °F (25 °C) 1150 cps

HOW TO APPLY

SURFACE PREPARATION

1. MasterBrace SAT 4700 should be applied to a substrate prepared with MasterBrace P 3500 and MasterBrace F 2000.
2. The MasterBrace P 3500 and MasterBrace F 2000 can be applied before or after the they have achieved full cure.
3. Surfaces with a tack-free MasterBrace P 3500 / MasterBrace F 2000 coat must be lightly sanded and cleaned of any dust, oils, or other surface contaminants.

MIXING

1. Mix Parts A and B using a low-speed drill (600 rpm) and mixing paddle (e.g., a Jiffy mixer). Carefully scrape the sides and bottom of the container while mixing. Keep the paddle below the surface of the material to avoid entrapping air. Proper mixing will take at least 3 – 5 minutes. Well-mixed material will be free of streaks or lumps.

APPLICATION

1. Apply the MasterBrace SAT 4700 using a 3/8" nap roller or short bristle brush to a wet film thickness of 18 to 22 mils.
2. Apply the desired MasterBrace fabric into the MasterBrace SAT 4700 before the MasterBrace SAT 4700 becomes tacky. (Note some fabrics may require additional MasterBrace SAT 4700 be applied directly onto the fabric prior to placing the fabric.)
3. Apply a second layer of MasterBrace SAT 4700 over the MasterBrace fabric using a 3/8" nap roller or short bristle brush to a wet film thickness of 18 to 22 mils.
4. If additional layers of MasterBrace fabric are required, repeat steps 1 through 3.

CLEAN UP

Use xylene or methyl ethyl ketone. Observe fire and health precautions with solvents.

MAINTENANCE

Periodically inspect the applied material and repair localized areas as needed. Consult a BASF representative for additional information. Visit us on the web for the most current product information and news: www.master-builders-solutions.basf.us.

FOR BEST PERFORMANCE

- Only apply MasterBrace SAT 4700 when the ambient temperature is between 40 and 80° F (5 and 27° C).
- Surfaces subject to UV exposure should be protected with MasterProtect HB 400, MasterProtect HB 300 SB, or equivalent 100% acrylic top coat.
- Interior Surfaces may be coated — consult a BASF representative for available options. Coatings applied over MasterBrace SAT 4700 should be applied within 48 hours.
- If more than 48 hours have passed following application of MasterBrace SAT 4700 the surface shall be lightly abraded and cleaned with a solvent wipe prior to applying the next component.
- Make certain the most current versions of product data sheet and SDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

OBSERVE WORKING TIME LIMITATIONS

- Catalyze no more material than can be applied within the work time period.
- Available work time, temperature and complexity of the application area will determine how much material should be catalyzed at one time.
- Keep material cool and shaded from direct sunlight in warm weather.
- During hot weather, work time can be extended by keeping material cool before and after mixing or by immersing pot in ice water.

HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.basf.us, e-mailing your request to basfbcsst@basf.com or calling 1(800)433-9517. Use only as directed. **For medical emergencies only, call ChemTrec® 1(800)424-9300.**

LIMITED WARRANTY NOTICE

Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names

used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

BASF Corporation
Constructions Systems

889 Valley Park Drive, Shakopee, MN 55379
www.master-builders-solutions.basf.us

Customer Service 1(800)433.9517
Technical Service 1(800)243.6739

