

# MasterEmaco® ADH 327

Paste epoxy concrete bonding adhesive with long pot life

FORMERLY CONCRECISIVE® PASTE LPL

## PACKAGING

1 gallon (3.8 L) kits

## YIELD

SMOOTH SURFACES:  
12 ft<sup>2</sup>/gal (0.29 m<sup>2</sup>/L)

ROUGH SURFACES:  
6 ft<sup>2</sup>/gal (0.15 m<sup>2</sup>/L)

## STORAGE

Store and transport in unopened containers in a cool, clean, dry area. Keep from freezing.

## SHELF LIFE

2 years when properly stored

## VOC CONTENT

0 g/L less water and exempt solvents

## DESCRIPTION

MasterEmaco ADH 327 is a two- component 100% solids non-sag epoxy adhesive. It is designed for use in vertical and overhead bonding and patching applications and for anchoring.

## PRODUCT HIGHLIGHTS

- Non-sag gel ideal for vertical and overhead applications
- Very long working time
- Moisture insensitive bonds to damp concrete surfaces
- May be extended with properly graded sand for more economical applications

## APPLICATIONS

- Interior and exterior
- Horizontal, vertical, and overhead surfaces
- Pinning loose or broken masonry
- Bonding rigid materials like metal, concrete, stone
- Bonding flexible materials like plastics, foam, rubber
- Fairing uneven surfaces, filling gaps and joints
- Bonding fresh to existing concrete
- Grouting bolts, dowels, and rebar into concrete, stone, and masonry
- As a rigid, pick-proof security sealant use

## SUBSTRATES

- Concrete
- Stone
- Metal
- Plastics

## HOW TO APPLY

### SURFACE PREPARATION CONCRETE

1. Substrate may be dry or damp, although dry surfaces produce optimum results. New concrete must be fully cured (28 day minimum).
  2. Remove grease, wax, oil contaminants, and curing compounds by scrubbing with an industrial-grade detergent or a degreasing compound. Follow with mechanical cleaning (refer to ASTM D 4258). Remove weak, contaminated, or deteriorated concrete by shotblasting, bushhammering, gritblasting, scarifying, or other suitable mechanical means.
- ### STEEL

Remove dirt, grease, and oil with a suitable industrial-grade cleaning-and-degreasing compound (SSPC-SP-1). Remove rust and mill scale by gritblasting. Blast steel to white metal. Follow gritblasting with vacuuming or oil-free dry-air blast (refer to SSPC-SP-10 or NACE-2).

## MIXING

1. Precondition all components to 70° F (21° C). Thoroughly stir each component before mixing.
2. The mix ratio is 2:1(A:B). Mix only the amount of material usable before the pot life expires.
3. Measure each component carefully and then add Part B to Part A.

**Technical Data**

**Composition**

MasterEmaco ADH 327 is a two-component 100% solids non-sag epoxy.

**Typical Properties**

COMPONENT	PART A (Resin)	PART B (Hardener)
<b>Form</b>	Paste	Paste
<b>Color</b>	White	Black
<b>Mixing ratio</b> (by volume)	2	1
<b>Mixed color</b>	Gray	

**Test Data**

PROPERTY	RESULTS	TEST METHOD
<b>Tensile strength, psi (MPa)</b>	2,000 (13.8)	ASTM D 638
<b>Elongation at break, %</b>	4	ASTM D 638
<b>Compressive yield strength, psi (MPa)</b>	8,000 (55.2)	ASTM D 695
<b>Compressive modulus, psi (MPa)</b>	4.0 × 10 <sup>5</sup> (2.8 × 10 <sup>3</sup> )	ASTM D 695
<b>Heat deflection temperature, 28 day cure, ° F (° C)</b>	128 (53)	ASTM D 648
<b>Slant shear strength, psi (MPa)</b>	> 5,000 (34.5)	AASHTO T-237
<b>Bond strength, at 14 days, psi (MPa)</b>	1,500 (10.3)	ASTM C 882

Test Temperature: 77° F (25° C), cured 7 days. Properties listed are typical and may be used as a guide for determining suitability for particular applications.

PROPERTY	VALUE		
	60° F (16° C)	85° F (29° C)	105° F (41° C)
<b>Nonsag thickness, in (mm)</b>	¾ (19)	½ (13)	¼ (6)
<b>Initial cure time, days, for 5,000 psi (34.5 MPa) minimum, (AASHTO T-237)</b>	10	6	3
<b>Full cure time, days (ASTM D 695)</b>	20	10	7
<b>Pot life, hrs, 1 gal (3.8 L)</b>	2½	1	½
<b>Open time</b>	3 hr	90 min	40 min

4. Mix using a low-speed drill (600 rpm) and mixing paddle (e.g., a Jiffy mixer). Carefully scrape the sides and bottom of the container while mixing. Keep the paddle below the surface of the material to avoid entrapping air. Proper mixing will take at least 3–5 minutes. Well-mixed material will be free of streaks or lumps and be uniform in color.

#### **APPLICATION**

Application temperature range is 60 to 105° F (16 to 41° C).

#### **GENERAL BONDING**

1. Deep surface irregularities can be faired with a 1-to-1 sand and MasterEmaco ADH 327 mix. Allow this fairing material to set. Within 24 hours, apply neat bonding agent with a trowel in sufficient quantities to fill all gaps between the mated surfaces.
2. The neat bondline thickness should be  $\frac{1}{32}$ – $\frac{1}{8}$ " (0.8–3 mm). Ideally, a small amount of bonding agent should extrude from the joint when the surfaces are mated and pressure is applied. Surfaces must be mated within the open time of the paste.

#### **BONDING FRESH CONCRETE TO EXISTING CONCRETE**

1. The fresh concrete to be bonded should have a relatively low-slump.
2. When bonding concrete containing latex polymer admixtures, check compatibility either by installing a test patch and performing a pull-off test or by conducting a laboratory slant shear test (ASTM C 882).
3. Apply the bonding agent as described in the General Bonding section above. When bonding to lightweight concrete, a second coat may be required if the first coat is absorbed by the substrate. Place fresh concrete within the open time. Be careful when applying the fresh concrete not to damage the bonding layer.
4. For highly irregular surfaces, sand may be used to extend this material. For proper application techniques contact BASF Technical Service.

#### **PATCHING MORTARS AND GROUTS**

1. Use washed, kiln-dried, and bagged graded silica sand. A carefully selected blend of sands with a low void content will require less epoxy for a given volume of mortar compared to ungraded sands. A good "skip" gradation for low void content is a blend by weight of 2 parts #12 or #16 mesh to 1 part #80 or #100 mesh. When graded sands are not available, a good general-purpose sand is #30 mesh silica.
2. The maximum placement depth is 1" (25 mm).

#### **BOLT AND REBAR GROUTING**

1. The hole must be free of water or debris before grouting.
2. Minimum annular space is  $\frac{1}{4}$ ".
3. Pour a measured amount of bonding agent into the hole. Insert the bar, displacing the bonding agent, then secure the bar in the center of the hole. Remove excess bonding agent from around the hole before it hardens. Use pressure grouting for holes deeper than 2 ft (0.6 m).

---

#### **CLEAN UP**

Clean all tools and equipment immediately with xylene or mineral spirits. Cured material must be removed mechanically.

---

#### **FOR BEST PERFORMANCE**

- Do not add solvent, water, or any other material to the bonding agent.
- Non-sag characteristics will diminish at the upper end of the application-temperature range.
- Evaluate sustained load conditions before using this product structurally above a service temperature of 105° F (41° C).
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit [master-builders-solutions.basf.us](http://master-builders-solutions.basf.us) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and are not for supervising or providing quality control on the jobsite.

---

#### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.basf.us](http://www.master-builders-solutions.basf.us), e-mailing your request to [basfbcst@basf.com](mailto:basfbcst@basf.com) or calling 1(800)433-9517. Use only as directed.

**For medical emergencies only,  
call ChemTrec® 1(800)424-9300.**

---

#### LIMITED WARRANTY NOTICE

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.